Research Article

Effect of Structure of Monocyclic Aromatic Solvents on the Packing Density of Fullerene C₆₀ Solvation Shell

E. V. Chubarova and E. Yu. Melenevskaya

Institute of Macromolecular Compounds, Russian Academy of Sciences, Bolshoi Avenue 31, 199004 St. Petersburg, Russia

Correspondence should be addressed to E. V. Chubarova, e.v.chubarova@mail.ru

Received 30 August 2012; Accepted 12 October 2012

Academic Editors: X. C. Li, U. Pal, Y. Ueno, and M. I. M. Wazeer

Copyright © 2012 E. V. Chubarova and E. Yu. Melenevskaya. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Fullerene C₆₀ solutions in various monocyclic aromatic solvents (AS) diluted by tetrahydrofuran (THF) were studied using UV spectroscopy. An algorithm was proposed which made it possible to obtain the data from the UV spectra of (C₆₀+AS) solutions in THF which pointed to the difference between the packing density of AS molecules in solvation shell of C₆₀ and that in the pure AS solvent. The presence of asymmetrical substituents in the AS molecule has been shown to result in loosening of solvent structure in the solvation shell, while the absence of the substituents or presence of symmetrical substituents leads to compacting of solvent structure.

1. Introduction

Donor-acceptor interactions of fullerene C₆₀ with solvent molecules are responsible for its good solubility in numerous organic solvents due to formation of strong solvation shells [1]. Fullerene C₆₀ manifests itself mainly as a π -acceptor [1–3], which predominates its high solubility in aromatic solvents due to formation of fullerene-solvent molecular complexes. The presence of substituents in the aromatic solvent (AS) molecule may be expected to result in the appearance of additional interactions between the AS and C₆₀ during solvation. For example, the spectroscopic study of fullerene solutions in various solvents [4, 5] pointed to the possibility of C₆₀ solvation by *o*-dichlorobenzene owing to both π - π interactions of the benzene ring of AS with the π -system of fullerene and partial charge transfer from the chlorine atom to fullerene. The presence of methyl group as a substituent in the AS molecule may open the way to formation of additional hydrogen-bonding complexes [6]. Interaction of some organic donors with C₆₀ has been shown to result in their coordination with fullerene C₆₀ [7]. The structure of solvation shell would be dependent on the forced coordination of solvent molecules by fullerene. The fullerene ability to structure a solvent was shown in [8]. It seems quite

obvious that the coordination of monocyclic AS molecules by C₆₀ during solvation would depend on the presence of substituents in AS which may interact with fullerene. The forced coordination of solvent molecules by C₆₀ may be proposed to result in the difference between the packing density of AS molecules in the C₆₀ solvation shell and that in the pure AS. The examination of this idea was the aim of the work.

2. Experimental Part

2.1. Materials, Experimental Procedure, and Equipment. Fullerene C₆₀ (purity 99.5 wt%) (Fullerene Technologies, St. Petersburg) was used for preparation of its solutions with specified concentrations in several selected aromatic solvents with various substituents (Table 1) as well as in tetrahydrofuran (THF) and methylene chloride (CH₂Cl₂). All solvents were preliminary purified by distillation.

The weighed amount of C₆₀ solution in AS with the known fullerene concentration was diluted by the weighed amount of THF, which allowed us to calculate the concentration of fullerene (c_F) and of the AS used ($c_{AS,cal}$) in the (C₆₀+AS) solution in THF. No less than three solutions diluted by THF were prepared from the C₆₀ solution in each AS;

TABLE 1: Aromatic solvents used and the number N of excess (positive values) or deficient (negative values) molecules of the aromatic solvent per solvation shell of C_{60} molecule.

Solvent	Structural formula	N
Benzene		+650
Toluene		-110
<i>o</i> -xylene		-240
<i>p</i> -xylene		+940
Chlorobenzene		-190
<i>o</i> -dichlorobenzene		-120

for each (C_{60} +AS) solution in THF the UV spectrum was recorded.

The UV spectra of C_{60} solutions were recorded using a UV VIS SF-2000 spectrophotometer (Russia); quartz cells of 2 mm thickness were used.

2.2. The Procedure of Calculation of the Number of Excess or Deficient Molecules of AS per Solvation Shell of C_{60} Molecule. Tetrahydrofuran is a transparent in the UV-region solvent good for AS and poor for C_{60} . At addition of THF to C_{60} solution in AS, fullerene solvation shell will be defined as the number of AS molecules which C_{60} is able to retain in THF. If the packing density of AS molecules in solvation shell corresponds to that in the pure AS solvent, the concentration $c_{AS,sp}$ calculated from the spectra of the (C_{60} +AS) solution in THF must be equal to the concentration $c_{AS,cal}$ calculated for this solution from the weighed amounts of C_{60} solution in AS and of THF. To calculate $c_{AS,sp}$ concentration, it is necessary to isolate the C_{60} spectrum from the (C_{60} +AS) spectrum in the region of the combined absorbance of AS and C_{60} (at $\lambda < 300$ nm). The following algorithm was developed to

FIGURE 1: Graphic illustration of the procedure of obtaining the AS spectra corresponding to the true value $c_{AS,sp}$ of AS concentration from the spectrum of (1) (C_{60} +AS) solution in THF. (2) is the transformed standard spectrum of C_{60} ; (3) is the spectrum of AS corresponding to $c_{AS,cal}$; (4) is the spectrum of AS obtained as the difference (1) and (2) spectra and corresponding to the required concentration $c_{AS,sp}$ (AS is chlorobenzene; $c_F = 0.0058$ mg/mL, $c_{chlorobenzene,cal} = 1.974$ mg/mL, and $c_{chlorobenzene,sp} = 1.806$ mg/mL).

FIGURE 2: The UV spectra of (C_{60} + CH_2Cl_2) solution in THF obtained by serial dilution. The insert shows the calibration dependence of the integral absorbance IA_F of (C_{60} + CH_2Cl_2) solution in THF on the absorbance value A_F at $\lambda = 329.3$ nm.

evaluate the $c_{AS,sp}$ concentrations of AS from the spectra of (C_{60} +AS) solutions in THF.

The graphic illustration of the algorithm proposed is presented in Figure 1. Curve 1 in Figure 1 corresponds to the spectrum of (C_{60} +AS) solution in THF with known concentration $c_{AS,cal}$ and, supposedly, is a superposition of C_{60} and AS spectra.

To recover the individual C_{60} spectrum, the following calibration procedure was developed. From the UV spectra recorded for C_{60} solution in CH_2Cl_2 under gradual addition of THF (Figure 2), the linear dependence, $IA_F = C \cdot A_F$, of the integral absorbance IA_F of C_{60} (the area under every

FIGURE 3: The UV spectra of C_{60} (1) in THF and (2) in CH_2Cl_2 . The insert shows the normalized UV spectra of (1) C_{60} in THF, (2) $(C_{60}+CH_2Cl_2)$ in THF, and $(C_{60}+AS)$ solutions in THF in the region transparent for C_{60} : (3) AS is toluene, (4) AS is *p*-xylene, and (5) AS is chlorobenzene.

individual spectral curve) in the wavelength range $\lambda = 240 - 365$ nm on the absorbance A_F of C_{60} at $\lambda_{max} = 329.3$ nm was obtained (the insert in Figure 2).

The spectrum of $(C_{60}+CH_2Cl_2)$ solution in THF was taken in the calculations for the standard spectrum of C_{60} , since $(C_{60} + CH_2Cl_2)$ is transparent at $\lambda > 230$ nm (curve 2 in Figure 3), and fullerene does not aggregate in CH_2Cl_2 in contrast to C_{60} in THF (curve 1 in Figure 3) [1, 5]. Besides, the position of the absorption maximum ($\lambda_{max} = 329.3$ nm) of C_{60} band and the width of this band for $(C_{60} + CH_2Cl_2)$ solution in THF coincides with that of the visible C_{60} band for all $(C_{60}+AS)$ solutions in THF (the insert in Figure 3).

Curve 2 in Figure 1 corresponds to the C_{60} spectrum obtained by transformation of the spectrum of $(C_{60} + CH_2Cl_2)$ solution in THF with the known value of integral absorbance (for any spectral curve in Figure 2). The transformation of the selected standard C_{60} spectrum with the known IA_F value to the C_{60} spectrum corresponding to the absorbance value at $\lambda_{max} = 329.3$ nm in the $(C_{60}+AS)$ spectrum was carried out by multiplication of absorbance values of the standard C_{60} spectrum by the ratio of integral absorbance calculated from the calibration dependence $IA_F = C \cdot A_F$ to the integral absorbance of the standard spectrum.

From the UV spectra of AS solutions in THF recorded at specified concentrations c_{AS} of AS (Figure 4) the linear calibration dependences $IA_{AS} = B_{AS} \cdot c_{AS}$ (the insert in Figure 4) were obtained for all aromatic solvents used, where IA_{AS} is the integral absorbance (the area under the spectral curve of AS at c_{AS}) within the absorption range of AS (from λ_1 to λ_2 , Figure 4).

Using the calibration $IA_{AS} = B_{AS} \cdot c_{AS}$, the standard spectrum of AS (the spectrum with a known value of IA_{AS}) in THF was transformed to the AS spectrum corresponding to the respective concentration $c_{AS,cal}$ of AS in the $(C_{60}+AS)$ solution in THF (curve 3 in Figure 1). The spectrum (curve 4

FIGURE 4: The UV spectra of AS solution in THF obtained at different concentrations of AS (AS is chlorobenzene; the UV spectra were obtained at $c_{chlorobenzene} = 0.648, 1.342, 1.799, 2.239$, and 2.692 mg/mL). The insert shows the calibration dependence of the integral absorbance IA_{AS} of AS solution in THF on AS concentration (AS is chlorobenzene; $IA_{chlorobenzene} = 6.853 \cdot c_{chlorobenzene}$; the λ range is $240-280$ nm).

in Figure 1) obtained by subtraction of the absorbance values of C_{60} (curve 2) from the absorbance values of $(C_{60}+AS)$ (curve 1) is the spectrum of AS which corresponds to the true concentration $c_{AS,sp}$ of AS in solution. The integral absorbance $IA_{AS,sp}$ of AS was obtained as the difference between the integral absorbance of $(C_{60}+AS)$ solution and the calculated integral absorbance IA_F of C_{60} . The concentration $c_{AS,sp}$ of AS was calculated from the value of $IA_{AS,sp}$, obtained from the calibration $IA_{AS} = B_{AS} \cdot c_{AS}$.

In accordance with the $c_{AS,cal}$ and $c_{AS,sp}$ values obtained for each $(C_{60}+AS)$ solution in THF, the number N of excess (positive values) or deficient (negative values) molecules of AS per solvation shell of C_{60} molecule was calculated from the relation

$$N = \frac{\Delta c_{AS}}{c_F} \frac{M_F}{M_{AS}}, \quad (1)$$

where $\Delta c_{AS} = (c_{AS,sp} - c_{AS,cal})$, M_F , and M_{AS} are the molecular masses of C_{60} and AS, respectively.

3. Results and Discussion

For all $(C_{60}+AS)$ solutions in THF the AS concentration $c_{AS,sp}$ obtained with the proposed algorithm differed from the $c_{AS,cal}$ value. Thus, the comparison of the chlorobenzene spectrum corresponding to the calculated concentration $c_{chlorobenzene,cal}$ in THF (curve 3 in Figure 5) with the spectrum corresponding to the true concentration of chlorobenzene (curve 4 in Figure 5) shows that the true concentration is lower than the calculated one.

The comparison of the spectrum corresponding to the calculated *p*-xylene concentration $c_{p-xylene,cal}$ (curve 3 in Figure 6) with the spectrum corresponding to the true concentration of *p*-xylene (curve 4 in Figure 6) shows that

FIGURE 5: The UV spectra of (1) (C_{60} +*o*-dichlorobenzene) solution in THF ($c_{o\text{-dichlorobenzene,cal}} = 2.113 \text{ mg/mL}$ and $c_F = 0.0095 \text{ mg/mL}$), (2) the transformed standard spectrum of C_{60} , (3) *o*-dichlorobenzene corresponding to $c_{o\text{-dichlorobenzene,cal}} = 2.113 \text{ mg/mL}$ ($IA_{o\text{-dichlorobenzene}} = 9.598 \cdot c_{o\text{-dichlorobenzene}}$ in the λ range from 245 to 285 nm), and (4) *o*-dichlorobenzene obtained as a difference of (1) and (2) spectra (the calculated value $c_{o\text{-dichlorobenzene,sp}}$ for the spectrum (4) is 1.851 mg/mL). The insert shows the normalized spectrum of *o*-dichlorobenzene in THF (solid line) and the normalized spectra of *o*-dichlorobenzene obtained by subtraction of the C_{60} spectrum from the spectra of (C_{60} +*o*-dichlorobenzene) solutions in THF with various concentrations of *o*-dichlorobenzene and C_{60} : $c_{o\text{-dichlorobenzene,cal}} = 2.113 \text{ mg/mL}$, $c_F = 0.0095 \text{ mg/mL}$ (dash line); $c_{o\text{-dichlorobenzene,cal}} = 2.190 \text{ mg/mL}$, $c_F = 0.0069 \text{ mg/mL}$ (short dash line); $c_{o\text{-dichlorobenzene,cal}} = 1.758 \text{ mg/mL}$, $c_F = 0.0081 \text{ mg/mL}$ (dot line).

the true concentration exceeds considerably the calculated concentration.

The difference between the $c_{AS,cal}$ and $c_{AS,sp}$ values found for each (C_{60} +AS) solution in THF points to the change of solvation shell density with respect to the density of pure solvent. The calculated N values are given in Table 1. The data show that the presence of asymmetrical substituents (chlorine atoms or the methyl group) in the AS molecule results in the loosening of solvent structure in the solvation shell of C_{60} , while the absence of substituents (benzene) or the presence of symmetrical substituents (*p*-xylene) leads to compacting of solvent structure in the C_{60} solvation shell. The insignificant spread in the calculated N values (below 10%) supports the validity of the proposed algorithm for calculation of the true AS concentration from the UV spectroscopic data. The validity of the proposed algorithm is supported as well by the practical identity of the normalized real spectra of AS in THF and of the AS spectra obtained as a difference of spectra of (C_{60} +AS) and C_{60} (see inserts in Figures 5 and 6). The concentration dependences of the integral absorbance of C_{60} in various aromatic solvents (Figure 7) correlate with the data listed in Table 1. Absorption decreases with the increase of packing density of solvent molecules in the solvation shell of C_{60} .

FIGURE 6: The UV spectra of (1) (C_{60} +*p*-xylene) solution in THF ($c_{p\text{-xylene,cal}} = 1.548 \text{ mg/mL}$ and $c_F = 0.0061 \text{ mg/mL}$), (2) the transformed standard spectrum of C_{60} , (3) *p*-xylene in THF corresponding to $c_{p\text{-xylene}} = 1.548 \text{ mg/mL}$ ($IA_{p\text{-xylene}} = 9.013 \cdot c_{p\text{-xylene}}$ in the λ range from 240 to 280 nm), and (4) *p*-xylene obtained as a difference of (1) and (2) spectra (with the calculated value of $c_{p\text{-xylene,sp}} = 2.495 \text{ mg/mL}$). The insert shows the normalized spectrum of *p*-xylene in THF (solid line) and normalized spectra of *p*-xylene obtained by subtraction of the C_{60} spectrum from the spectra of (C_{60} +*p*-xylene) solutions in THF with various concentrations of *p*-xylene and C_{60} : $c_{p\text{-xylene,cal}} = 1.548 \text{ mg/mL}$, $c_F = 0.0061 \text{ mg/mL}$ (dash line); $c_{p\text{-xylene,cal}} = 1.166 \text{ mg/mL}$, $c_F = 0.0063 \text{ mg/mL}$ (short dash line); $c_{p\text{-xylene,cal}} = 1.378 \text{ mg/mL}$, $c_F = 0.0070 \text{ mg/mL}$ (dot line).

FIGURE 7: Concentration dependences of the integral absorbance (in the λ range from 300 to 365.1 nm) of C_{60} in (1) *o*-xylene, (2) toluene, and (3) *p*-xylene.

4. Conclusions

The idea has been examined that the forced coordination of monocyclic molecules with various substituents of aromatic solvents by fullerene C_{60} may result in the difference between

the packing density of AS molecules in the C_{60} solvation shell and that in the pure AS. In this work, the fullerene solvation shell was defined as the number of AS molecules which the molecule of fullerene is able to retain at addition of THF which is a good solvent for AS and poor for C_{60} , to C_{60} solution in AS. The analytical techniques applied for preparation of C_{60} solutions in aromatic solvents and for determination of accurate concentrations c_F and $c_{AS,cal}$ after addition of THF, as well as the developed calibration procedures, made it possible to obtain the data from the UV spectra of (C_{60} +AS) solutions in THF which is the supporting evidence of the difference between the packing density of AS molecules in the solvation shell of C_{60} and that in the pure AS solvent. The data obtained show that the presence of asymmetrical substituents (chlorine atoms or methyl group) in the AS molecule results in the loosening of solvent structure in the solvation shell of C_{60} , while the absence of substituents (benzene) or the presence of symmetrical substituents (*p*-xylene) leads to compacting of solvent structure in the C_{60} solvation shell.

References

- [1] V. N. Bezmel'nitsyn, A. V. Eletskii, and M. V. Okun', "Fullerenes in solutions," *Physics-Uspekhi*, vol. 41, no. 11, pp. 1091–1114, 1998.
- [2] D. V. Konarev and R. N. Lyubovskaya, "Donor—acceptor complexes and radical ionic salts based on fullerenes," *Russian Chemical Reviews*, vol. 68, no. 1, pp. 19–38, 1999.
- [3] H. Imahori, "Creation of fullerene-based artificial photosynthetic systems," *Bulletin of the Chemical Society of Japan*, vol. 80, no. 4, pp. 621–636, 2007.
- [4] E. V. Chubarova and E. Yu. Melenevskaya, "Analysis of interactions in fullerene-solvent-polymer system by UV-spectroscopy," *Fullerenes Nanotubes and Carbon Nanostructures*, vol. 16, no. 5–6, pp. 640–643, 2008.
- [5] E. V. Chubarova and E. Yu. Melenevskaya, "Chain degradation during dissolution of polymer-fullerene nanocomposites as a result of interaction of entangled polymer matrix with the filler," *Journal of Macromolecular Science B*, vol. 49, no. 1, pp. 174–206, 2010.
- [6] J. Catalán, "On the solvatochromism of C_{60} and its color in solutions," *New Journal of Chemistry*, vol. 19, no. 12, pp. 1233–1242, 1995.
- [7] D. V. Konarev, V. N. Semkin, R. N. Lyubovskaya, and A. Graja, "Electronic absorption spectra of the C_{60} complexes with some organic donors," *Synthetic Metals*, vol. 88, no. 3, pp. 225–230, 1997.
- [8] B. M. Ginzburg, S. Tuichiev, S. K. Tabarov, and A. A. Shepelevskii, "Structurization of a solvent interacting with fullerene C_{60} ," *Crystallography Reports*, vol. 50, no. 5, pp. 735–738, 2005.