Dataset Paper

Judd-Ofelt Calculations for Nd^{3+} -Doped Fluorozirconate-Based Glasses and Glass Ceramics

U. Skrzypczak,¹ C. Pfau,¹ C. Bohley,¹ G. Seifert,^{1,2} and S. Schweizer^{2,3}

¹ Centre for Innovation Competence SiLi-nano, Martin Luther University of Halle-Wittenberg, Karl-Freiherr-von-Fritsch-Straße 3, 06120 Halle (Saale), Germany

² Fraunhofer Center for Silicon Photovoltaics CSP, Walter-Hülse-Straße 1, 06120 Halle (Saale), Germany

³ Department of Electrical Engineering, South Westphalia University of Applied Sciences, Lübecker Ring 2, 59494 Soest, Germany

Correspondence should be addressed to G. Seifert; g.seifert@physik.uni-halle.de

Received 12 September 2012; Accepted 8 October 2012

Academic Editors: F. Charra, P. Kluth, F. Song, and H. Yang

Copyright © 2013 U. Skrzypczak et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

A Judd-Ofelt analysis is performed to calculate the optical properties of Nd^{3+} ions embedded in a fluoro-zirconate glass matrix. The changes in the Judd-Ofelt parameters were determined as a function of the size of BaCl_2 nanocrystals grown inside the matrix. From these data, the radiative decay rates and the branching ratios of every transition in the energy range from 25.000 cm^{-1} to the ground state are calculated. This was accomplished for samples containing nanocrystals with average sizes ranging from 10 to 40 nm.

1. Introduction

Photonic glasses doped with rare-earth ions such as erbium, neodymium, or europium gather widespread interest because of their applicability in photonic devices. Application as, for example, the active ion in a laser medium or as frequency converter in up- and downconverters [1, 2] requires efficient radiative decays of the ion with only minor losses to multiphonon relaxation (MPR). Therefore, the ion needs to be embedded in a low phonon energy environment which still remains both stable and transparent. Among appropriate materials are fluoro-zirconate (FZ) glasses with maximum phonon energies of less than 580 cm^{-1} [3–5]. They have already proved to be a convenient choice for several applications.

As shown previously [6, 7], a uniform growth of BaCl_2 nanocrystals inside such glasses can be induced by thermal treatment as soon as additional chloride is introduced at the expense of fluoride. Since BaCl_2 has a maximum phonon energy on the order of 200 cm^{-1} [3, 8], MPR is rendered even less probable and, thus, rare-earth ions tend to favor radiative decays [6, 7, 9].

The optical properties of Nd^{3+} -doped fluoro-chloro-zirconate (FCZ) glasses with differently sized BaCl_2 nanocrystals were studied with Judd-Ofelt theory. The sizes of the embedded nanocrystals were obtained from X-ray diffraction in combination with Scherrer analysis. It is known that Nd^{3+} ions are strongly affected by the BaCl_2 nanocrystals, but until now only speculations were possible as to the location of rare-earth ions at the edge of nanocrystals or even the possible inclusion into them [9, 10].

From Judd-Ofelt [11–13] analysis, the phenomenological Judd-Ofelt parameters can be determined. With them a quantitative measure for the influence of BaCl_2 nanocrystals on the Nd^{3+} can be established (see [14] for a detailed discussion). Here, the radiative decay rates for each transition were calculated and are given in a compressed form.

2. Methodology

Experimental details are as follows. The FCZ glass samples [14] investigated in this study are comprised of 52ZrF_4 - 10BaF_2 - 10BaCl_2 - 19NaCl - 3.5LaF_3 - 3AlF_3 - 0.5InF_3 - 1KCl - 1NdF_3

(values in mol%). The named chemicals were melted under an inert atmosphere, poured into a preheated (200°C) mold to avoid cracks, and then slowly cooled down to room temperature. Subsequently, the glasses were treated thermally at a temperature between 240°C and 270°C for 20 minutes to initiate the growth of BaCl₂ nanocrystals.

The visible and near-infrared transmittance spectra, from which the oscillator strengths were obtained, were recorded at room temperature with a double-beam spectrophotometer (Perkin Elmer Lambda 900).

Judd-Ofelt details are as follows. From the absorption cross-section spectra, the oscillator strengths f_{meas} are calculated with

$$f_{\text{meas}} = \frac{4\pi\epsilon_0}{e^2} \frac{m_e c^2}{\pi} \int_{k_1}^{k_2} \sigma(k) dk, \quad (1)$$

where m_e is the mass of the electron; c , the speed of light; and $\sigma(k)$, the absorption cross section.

The theoretical oscillator strengths feature contributions from electric, f_{ed} , and magnetic dipole transitions, f_{md} . Quadrupole effects are very weak and have been neglected. The dipolar oscillator strengths are of the following form:

$$\begin{aligned} f_{\text{ed}} &= \frac{4\pi\epsilon_0}{e^2} \frac{8\pi^2 m_e \nu}{3h(2J+1)} \chi_{\text{ed}} S_{\text{ed}}, \\ f_{\text{md}} &= \frac{4\pi\epsilon_0}{e^2} \frac{8\pi^2 m_e \nu}{3h(2J+1)} \chi_{\text{md}} S_{\text{md}}, \end{aligned} \quad (2)$$

where ν is the mean frequency and J is the total angular momentum quantum number. From these, the line strengths,

$$\begin{aligned} S_{\text{ed}} &= \sum_{\lambda} \Omega_{\lambda} |\langle i \| U_{\lambda} \| j \rangle|^2, \\ S_{\text{md}} &= \left(\frac{eh}{4\pi m_e c} \right)^2 |\langle i \| L + 2S \| j \rangle|^2, \end{aligned} \quad (3)$$

are calculated, in which $\langle i \| U_{\lambda} \| j \rangle$ are the doubly reduced matrix elements of the electric dipole tensor operator and $\langle i \| L + 2S \| j \rangle$ are the elements of the magnetic dipole operator. These values do not depend much on the host and are given in the literature [13, 15–19]. The local field correction factors are $\chi_{\text{ed}} = (n^2 + 2)^2$ and $\chi_{\text{md}} = n$ [20]. The Gaussian least-squares minimization of

$$f_{\text{meas}} - f_{\text{md}} = f_{\text{ed}}^{(\lambda)} \Omega_{\lambda} \quad (4)$$

yields the evaluation of the intensity parameters Ω_{λ} (with $\lambda = 2, 4, 6$).

The effective refractive index n of a composite material made of an FCZ glass matrix with inclusion of nanometric BaCl₂ crystallites has been calculated involving a Maxwell-Garnett approach [21]:

$$\epsilon_{\text{eff}} = \frac{\epsilon_m (\epsilon_i (1 + 2\delta_i) - \epsilon_m (2\delta_i - 2))}{\epsilon_m (2 + \delta_i) + \epsilon_i (1 - \delta_i)}, \quad (5)$$

where ϵ_m and ϵ_i are the dielectric constants of matrix and inclusion (data taken from [22, 23]).

The radiative emission rates are calculated [14] with

$$A_{ji} = \frac{64\pi^4 \nu^3}{3hc^3 (2J_j + 1)} (\chi_{\text{ed}} S_{\text{ed}} + \chi_{\text{md}} S_{\text{md}}). \quad (6)$$

When i is not only the ground state, the branching ratios $\beta_{ji} = \tau_j A_{ji}$ define the percentage of the rate for each possible relaxation channel.

The tabular data given here are sectioned into samples with different BaCl₂ nanocrystal sizes. This starts with a determination for FZ glass and an untreated FCZ glass for reference and comparison. Then in order of increasing nanocrystal sizes, the different samples are given. For each source level $|i\rangle$, the target levels of the transition $|j\rangle$ along with the radiative decay rates A_{rad} and the corresponding branching ratio β_{ij} are given. This is repeated for each sample.

3. Dataset Description

The dataset associated with this Dataset Paper consists of 6 items which are described as follows.

Dataset Item 1 (Table). Data of the radiative decay parameters in the FZ glass matrix.

Column 1: $|i\rangle$
 Column 2: $|j\rangle$
 Column 3: A_{rad} (s⁻¹)
 Column 4: β_{ij}

Dataset Item 2 (Table). Data of the radiative decay parameters in the untreated FCZ glass matrix.

Column 1: $|i\rangle$
 Column 2: $|j\rangle$
 Column 3: A_{rad} (s⁻¹)
 Column 4: β_{ij}

Dataset Item 3 (Table). Data of the radiative decay parameters in the FCZ glass matrix, thermally treated at 240°C. The average nanocrystal size was determined to be 12 nm [14].

Column 1: $|i\rangle$
 Column 2: $|j\rangle$
 Column 3: A_{rad} (s⁻¹)
 Column 4: β_{ij}

Dataset Item 4 (Table). Data of the radiative decay parameters in the FCZ glass matrix, thermally treated at 250°C. The average nanocrystal size was determined to be 14 nm [14].

Column 1: $|i\rangle$
 Column 2: $|j\rangle$
 Column 3: A_{rad} (s⁻¹)
 Column 4: β_{ij}

Dataset Item 5 (Table). Data of the radiative decay parameters in the FCZ glass matrix, thermally treated at 260°C. The average nanocrystal size was determined to be 25 nm [14].

Column 1: $|i\rangle$
 Column 2: $|j\rangle$
 Column 3: $A_{\text{rad}} \text{ (s}^{-1}\text{)}$
 Column 4: β_{ij}

Dataset Item 6 (Table). Data of the radiative decay parameters in the FCZ glass matrix, thermally treated at 270°C. The average nanocrystal size was determined to be 42 nm [14].

Column 1: $|i\rangle$
 Column 2: $|j\rangle$
 Column 3: $A_{\text{rad}} \text{ (s}^{-1}\text{)}$
 Column 4: β_{ij}

4. Concluding Remarks

A Judd-Ofelt analysis under consideration of the effective- n matrix in an FZ-based glass ceramic with BaCl_2 nanocrystals of different sizes has been performed in order to evaluate the optical properties of Nd^{3+} ions embedded therein. The radiative decay rates and the branching ratios of every transition in the energy range from 25.000 cm^{-1} to the ground state are calculated. This is accomplished for samples containing nanocrystals with average sizes ranging from 10 to 40 nm. Using these data, the dynamics of these systems can be studied using rate equations.

Dataset Availability

The dataset associated with this Dataset Paper is dedicated to the public domain using the CC0 waiver and is available at <http://dx.doi.org/10.1155/2013/236421/dataset>.

Acknowledgments

This work was supported by the FhG Internal Programs under Grant no. Attract 692 034. In addition, the authors would like to thank the German Federal Ministry for Education and Research (Bundesministerium für Bildung und Forschung) for the financial support within the Centre for Innovation Competence SiLi-nano (Project no. 03Z2HN11).

References

- [1] C. Paßlick, B. Henke, I. Császár et al., “Advances in up- and down-converted fluorescence for high efficiency solar cells using rare-earth doped fluorozirconate-based glasses and glass ceramics,” in *Next Generation (Nano) Photonic and Cell Technologies for Solar Energy Conversion*, vol. 7772 of *Proceedings of SPIE*, August 2010.
- [2] B. Ahrens, P. T. Miclea, and S. Schweizer, “Upconverted fluorescence in Nd^{3+} -doped barium chloride single crystals,” *Journal of Physics: Condensed Matter*, vol. 210, no. 12, p. 125501, 2009.
- [3] C. Pfau, C. Bohley, P. T. Miclea, and S. Schweizer, “Structural phase transitions of barium halide nanocrystals in fluorozirconate glasses studied by Raman spectroscopy,” *Journal of Applied Physics*, vol. 109, no. 8, Article ID 083545, 2011.
- [4] B. Bendow, P. K. Banerjee, M. G. Drexhage, J. Goltman, S. S. Mitra, and C. T. Moynihan, “Comparative study of vibrational characteristics of fluorozirconate and fluorohafnate glasses,” *Journal of the American Ceramic Society*, vol. 65, no. 1, pp. C-8–C-9, 1982.
- [5] B. Bendow, M. G. Drexhage, and H. G. Lipson, “Infrared absorption in highly transparent fluorozirconate glass,” *Journal of Applied Physics*, vol. 52, no. 3, pp. 1460–1461, 1981.
- [6] B. Ahrens, P. Löper, J. C. Goldschmidt et al., “Neodymium-doped fluorochlorozirconate glasses as an upconversion model system for high efficiency solar cells,” *Physica Status Solidi A*, vol. 205, no. 12, pp. 2822–2830, 2008.
- [7] C. Pfau, U. Skrzypczak, M. Miclea, C. Bohley, P. T. Miclea, and S. Schweizer, “Low phonon energy BaCl_2 nanocrystals in Nd^{3+} -doped fluorozirconate glasses and their influence on the photoluminescence properties,” in *Proceedings of the Materials Research Society Symposium*, vol. 1404, 2012.
- [8] C. Bohley, J.-M. Wagner, C. Pfau, P.-T. Miclea, and S. Schweizer, “Raman spectra of barium halides in orthorhombic and hexagonal symmetry: an ab initio study,” *Physical Review B*, vol. 83, no. 2, Article ID 024107, 6 pages, 2011.
- [9] U. Skrzypczak, M. Miclea, A. Stalmashonak et al., “Time-resolved investigations of erbium ions in ZBLAN-based glasses and glass ceramics,” *Physica Status Solidi C*, vol. 8, no. 9, pp. 2649–2652, 2011.
- [10] G. Soundararajan, C. Koughia, A. Edgar, C. Varoy, and S. Kasap, “Optical properties of erbium-doped fluorochlorozirconate glasses,” *Journal of Non-Crystalline Solids*, vol. 357, no. 11–13, pp. 2475–2479, 2011.
- [11] B. R. Judd, “Optical absorption intensities of rare-earth ions,” *Physical Review*, vol. 127, no. 3, pp. 750–761, 1962.
- [12] G. S. Ofelt, “Intensities of crystal spectra of rare-earth ions,” *Journal of Chemical Physics*, vol. 37, no. 3, p. 511, 1962.
- [13] B. Walsh, “Judd-Ofelt Theory: Principles and Practices,” in *Advances in Spectroscopy For Lasers and Sensing*, pp. 403–433, Springer, New York, NY, USA, 2006.
- [14] U. Skrzypczak, C. Pfau, C. Bohley, G. Seifert, and S. Schweizer, “Particle size monitoring of BaCl_2 nanocrystals in fluorozirconate glasses,” *Journal of Non-Crystalline Solids*, vol. 363, pp. 205–208, 2013.
- [15] T. Suzuki, H. Kawai, H. Nasu et al., “Spectroscopic investigation of Nd^{3+} -doped ZBLAN glass for solar-pumped lasers,” *Journal of the Optical Society of America B*, vol. 28, no. 8, pp. 2001–2006, 2011.
- [16] R. Caspary, *Applied rare-earth spectroscopy for fiber laser optimization [Ph.D. thesis]*, Technische Universität Braunschweig, 2002.
- [17] A. A. Kaminskii, G. Boulon, M. Buonchristiani, B. di Bartolo, A. Kornienko, and V. Mironov, “Spectroscopy of a new laser garnet $\text{Lu}_3\text{Sc}_2\text{Ga}_3\text{O}_{12}:\text{Nd}^{3+}$,” *Physica Status Solidi A*, vol. 141, no. 2, pp. 471–494, 1994.
- [18] W. T. Carnall, P. R. Fields, and K. Rajnak, “Electronic energy levels of the trivalent lanthanide aquo ions. I. Pr^{3+} , Nd^{3+} , Pm^{3+} , Sm^{3+} , Dy^{3+} , Ho^{3+} , Er^{3+} , and Tm^{3+} ,” *Journal of Chemical Physics*, vol. 49, no. 10, pp. 4424–4442, 1968.
- [19] X. Qiao, X. Fan, J. Wang, and M. Wang, “Luminescence behavior of Er^{3+} ions in glass-ceramics containing CaF_2 nanocrystals,”

Journal of Non-Crystalline Solids, vol. 351, no. 5, pp. 357–363, 2005.

- [20] W. B. Fowler and D. L. Dexter, “Relation between absorption and emission probabilities in luminescent centers in ionic solids,” *Physical Review*, vol. 128, no. 5, pp. 2154–2165, 1962.
- [21] C. F. Bohren and D. R. Huffman, *Absorption and Scattering of Light by Small Particles*, John Wiley & Sons, New York, NY, USA, 1983.
- [22] H. H. Li, “Refractive index of alkaline earth halides and its wavelength and temperature derivatives,” *Journal of Physical and Chemical Reference Data*, vol. 9, no. 1, p. 161, 1980.
- [23] L. Wetenkamp, T. Westendorf, G. West, and A. Kober, “The effect of small composition changes on the refractive index and material dispersion in ZBLAN heavy-metal fluoride glass,” *Materials Science Forum*, vol. 32-33, pp. 471–476, 1991.