Research Article

Characterization of Native and Graft Copolymerized *Albizia* Gums and Their Application as a Flocculant

T. Adeniyi Afolabi and Daniel G. Adekanmi

Department of Chemistry, Federal University of Agriculture, Abeokuta, Nigeria

Correspondence should be addressed to T. Adeniyi Afolabi; niyiafo@yahoo.com

Received 5 April 2017; Accepted 7 May 2017; Published 18 June 2017

Academic Editor: Yves Grohens

Copyright © 2017 T. Adeniyi Afolabi and Daniel G. Adekanmi. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

The functional properties and flocculation efficiency of purified *Albizia saman* (AS) and *Albizia glaberrima* (AG) gum exudates modified by graft copolymerization with acrylamide were investigated. The grafting efficiency of AS and AG was 54 and 58%, respectively. The cold water-insoluble gel of native AS and AG was 38.23 and 35.55%, which increased to 39.75 and 40.55% after graft copolymerization. Graft copolymerization of AS and AG gums reduced their oil binding and emulsion capacity from 4.89 and 3.44% to 3.69 and 2.40%, respectively. The dissolution kinetics of the native gums between 40 and 90°C and 0 and 150 min revealed a steady increase in solubility of the native gums from 6.05 to 9.53 g/L (AS) and 5.90 to 8.78 g/L (AG). The flocculation efficiency of the native AS and AG gums at 50 ppm concentration was 74.30 and 74.73%, which increased to 98.46% and 98.29% in the graft copolymerized gums, respectively.

1. Introduction

The increase in world population has greatly influenced the expansion and sophistication of the industrial growth, with its concomitant environmental hazard. One of these hazards is water pollution by industrial and agricultural waste systems. The generation of wastewater which contains very fine suspended solids, organic and inorganic particles, dissolved solids, metals, and other impurities is harmful to the environment with major health issues in various organisms. These impurities have a very small particle size and rarely settle down; hence their filtration is very difficult and expensive. Among the several traditional and advanced technologies applied for the removal of colloidal particles from wastewater [1], flocculation is one of the most widely used solid-liquid separation process [1–3].

Lee et al. [3] classified flocculants used in wastewater treatments as chemical coagulants/flocculants, natural bio-flocculants, and grafted flocculants. The chemical coagulants/flocculants include coagulants which are inorganic metal salts and flocculants which are synthetic organic polymers. Grafted flocculants (or graft copolymers) include synthetic polymers and natural polymers such as chitosan, cellulose,

starch, and gums. The natural bioflocculants are chitosan, cellulose, sodium alginate, tannin, gums, and mucilage.

The presence of residual metal concentration in treated water and poor flocculating efficiency is the major disadvantage of using inorganic coagulants despite their low cost and ease of use [1]. Similarly, lack of biodegradability and dispersion of monomers residue in treated water negate the wide application of organic polymeric flocculants because of its associated health hazards [4]. Hence, biopolymers based flocculants are gaining much interest by researchers because they are biodegradable and environmentally friendly [1, 3]. One of such biopolymers is gum.

Gums are widely used as flocculants in water treatment because they are nontoxic, biodegradable, and effective [5]. Their efficiency as flocculants is largely dependent on the gum's molecular ability to trap suspended particles to form flocs. Gums are believed to be produced through metabolic activity, as a protective mechanism against pathological conditions or as a consequence of infection on the plant by microorganisms [6]. Gums and other natural flocculants are however needed in large dosage due to their moderate flocculating efficiency and shorter shelf life [3]. Hence, polysaccharides are grafted with synthetic polymers, such as

acrylamide, to obtain tailor-made grafted flocculants with specialized functions [7].

Extensive studies have been carried out on polysaccharide gums because they are sustainable, biodegradable, and biosafe [8, 9]. The most utilized gum with diverse industrial application is gum arabic [9, 10]. The demand for major gums such as gum arabic, guar gum, and xanthan gum for applications in the food, pharmaceutical, and allied industries has led to the concomitant increase in their cost. New inexpensive gum exudates obtained from diverse plants have attracted the attention of researchers for a wide range of industrial applications [8, 9, 11, 12]. Hence, the need to search for gums from lesser known and underutilized plants species such as *Albizia*, which will be economical and readily available, has become expedient.

Albizia (family: Fabaceae; subfamily: Mimosoideae) is a genus of about 150 species of mostly fast growing subtropical and tropical trees and shrubs occurring in Africa, Asia, Australia, and America [13]. *Albizia* trees are a good source of gums, and its gums have been explored as a suitable substitute for gum arabic as a natural emulsifier for foods and pharmaceuticals [14]. Dabhade et al. [15] reported the extraction of proteinaceous trypsin inhibitor from seeds of *Albizia amara* and its potentials as an antimicrobial agent. Leaf extracts from AG [16] and *Albizia gummifera* [17] were investigated for their neuropharmacological and antimicrobial effects, respectively. The phytochemical properties of the roots of AG were investigated [18], while the gums of *Albizia stipulata* were used in the development of controlled-release tablets in cancer therapeutics [19].

AS and AG are tree crops cultivated mainly for timber production in Nigeria, with huge gum exudates that are usually wasted. From literature search, records of characterization and industrial application of AS and AG are scarce; hence the study of the functional properties and their industrial application as flocculants in waste water treatment may provide an efficient and functionally viable gum with industrial appeal.

2. Materials and Methods

2.1. Materials and Gum Purification. Gum exudates from AS and AG were collected at the Federal University of Agriculture, Abeokuta, Nigeria campus. Analar grade ceric ammonium nitrate and acrylamide were used without further purification. Bark-free impure gum exudates from AS and AG were selected and soaked in water overnight, allowing them to hydrate sufficiently. The schematic diagram of the gum purification process is presented in Figure 1.

2.2. Synthesis of Graft Copolymerized Gum. The purified *Albizia* gums (5 g, on dry weight basis) were dissolved in 200 mL distilled water, and 25 g of acrylamide (dissolved in 250 mL water) was added to the dispersion. The suspension was thoroughly mixed for about 10 minutes with a blender and transferred to the reaction vessel, followed by the addition of 2 g ceric ammonium nitrate. The reaction was allowed

to proceed at 65°C (using thermostatic water bath) until a gel-like mass was obtained. Unreacted acrylamide monomer was removed by the addition of excess acetone and methanol. The gel formed (graft copolymer) was collected, dried, pulverized, and sieved. The percentage grafting (% G) and percentage grafting efficiency (% GE) of the synthesized graft copolymers were evaluated:

$$\begin{aligned} \% G &= \frac{\text{Weight of graft copolymer} - \text{Weight of polysaccharide}}{\text{Weight of gum}} \times 100, \end{aligned} \quad (1)$$

$$\begin{aligned} \% GE &= \frac{\text{Weight of graft copolymer} - \text{Weight of gum}}{\text{Weight of monomer}} \times 100. \end{aligned} \quad (2)$$

2.3. FTIR Spectroscopy. The grafting reaction was confirmed by FTIR. The FTIR spectra of the native and acrylamide grafted AS and AG gum samples (using KBr pellets) were obtained with the aid of FTIR spectrometer (Nicolet Magna-IR 750, series II, Thermo Scientific, Portsmouth, NH, USA) at 400 to 4000 cm⁻¹.

2.4. Proximate Composition. The AACC (2000) method was used in determining the ash content, fat (ether extract), and crude fiber of the gum samples. The bulk and tapped density determined gravimetrically was used to calculate the compressibility index, that is, Carr's index (see (3)). Hausner's ratio measures the cohesiveness of the exudate gum powder and was calculated using (4) [20].

$$\begin{aligned} \text{Carr's Index} &= \frac{\text{Bulk density} - \text{Tapped density}}{\text{Bulk density}} \times 100, \end{aligned} \quad (3)$$

$$\text{Hausner ratio} = \frac{\text{Tapped Density}}{\text{Bulk Density}}. \quad (4)$$

The oil binding capacity of the gum was determined gravimetrically using the method of Okezie and Bello [21]. The concentration of five minerals (sodium, manganese, lead, calcium, and magnesium) was determined using an atomic absorption spectrophotometer AAS (Perkin-Elmer 305B).

2.5. Emulsion Capacity. The gum sample (0.25 g) was blended with 10 mL of distilled water at room temperature for 30 seconds. After complete dispersion, 10 mL of oil was added and blended for 5 minutes. The mixture was then quantitatively transferred to a centrifuge tube and centrifuged at 3000 rpm for 5 minutes. The volume of oil separated from the sample after centrifugation was read directly from the tube.

FIGURE 1: Schematic diagram of the *Albizia* gum's purification.

Emulsification capacity, EC, expressed as mL of oil emulsified by 1 g samples, was calculated using

$$EC = \frac{\text{Height of emulsified layer}}{\text{Height of the whole solution in the centrifuge tube}} \times 100. \quad (5)$$

2.6. Cold and Hot Water-Insoluble Gel. A mixture of 1 g gum sample and 100 cm³ distilled water was thoroughly mixed for 1 hour. The mixture was then centrifuged at 1200 rpm for 15 minutes and the clear supernatant liquid discarded. The insoluble fraction was washed by adding distilled water and stirring for 3 minutes and recentrifuged at 1200 rpm for 15 minutes. This procedure was repeated four times, before transferring the insoluble fraction into a preweighed porcelain dish. The insoluble fraction was dried in an oven for 12 hours at 105°C, cooled in a desiccator, and weighed. The difference in weight gives the cold water-insoluble gel (CWIG).

The hot water-insoluble gel (HWIG) determination was carried out by stirring 1 g of gum in 100 mL of distilled water for 30 minutes and heating the mixture in a water bath at 95°C for 1 hour; the mixture was allowed to stand at room temperature for 4 hours. Separation and determination of the HWIG were carried out as described for CWIG.

2.7. Intrinsic Viscosity. The specific viscosity of the 1% gum solutions (native and graft copolymerized AS and AG) was

measured with the Brookfield viscometer at 50, 60, and 100 rpm and calculated as follows:

$$\begin{aligned} \eta_{sp} &= \eta_{rel} - 1, \\ \eta_{red} &= \frac{\eta_{sp}}{C}, \\ \eta_{inh} &= \frac{\ln(\eta_{rel})}{C}. \end{aligned} \quad (6)$$

From the time of flow of polymer solutions (t) and that of the solvent (t_o , for distilled water), relative viscosity ($\eta_{rel} = t/t_o$) was obtained. The reduced viscosity (η_{red}) and the inherent viscosity (η_{inh}) were simultaneously plotted against concentration. “C” represents polymer concentration in g/dL. The intrinsic viscosity was obtained from the point of the intersection after extrapolation of two plots (i.e., η_{red} versus C and η_{inh} versus C) to zero concentration [22].

2.8. Solubility Capacity. A 1% gum solution (2.5 g of gum in 250 cm³ of water) was vigorously shaken in a thermostatically controlled water bath at 30°C for specified time interval (0, 30, 60, 90, 120, or 150 minutes). Then 20 cm³ is drawn out, allowed to cool, and centrifuged at 3000 rpm for 10 minutes. Aliquots (10 cm³) of the supernatant were dried to constant weight at 105°C to determine the mass of the gum dissolved. The above experiment was repeated at 40, 50, 60, 70, and 80°C.

2.9. Flocculation Study. The flocculation test was done using the modified method of Rani et al. [22]. 100 mL of 0.25% Kaolin suspension was added to 10 ppm of the flocculant (native and acrylamide grafted gums). The suspension was

TABLE 1: Physicochemical properties of native (ASN) and graft copolymerized (ASG) *Albizia saman* gums and native (AGN) and graft copolymerized (AGG) *Albizia glaberrima* gums.

Parameter	ASN	ASG	AGN	AGG
Moisture content (%)	10.89 ± 0.01	—	9.91 ± 0.02	—
Crude fibre (g/100 g)	8.59 ± 0.04	—	9.57 ± 0.02	—
Ether extract (g/100 g)	9.81 ± 0.01	—	8.01 ± 0.02	—
Ash content (g/100 g)	7.87 ± 0.02	—	8.60 ± 0.01	—
Bulk density (g/cm ³)	0.710 ± 0.01	0.662 ± 0.07	0.738 ± 0.07	0.694 ± 0.04
Tapped density (g/cm ³)	0.835 ± 0.04	0.740 ± 0.04	0.870 ± 0.04	0.782 ± 0.11
Carr's index	17.535 ± 0.06	11.005 ± 0.07	17.555 ± 0.18	9.480 ± 0.11
Hausner's ratio	1.176 ± 0.01	1.117 ± 0.01	1.179 ± 0.02	1.127 ± 0.13
^a CWIG (%)	40.23 ± 2.47	39.75 ± 0.95	35.55 ± 1.34	40.55 ± 0.14
^b HWIG (%)	8.00 ± 1.41	14.23 ± 1.11	10.96 ± 0.08	15.00 ± 0.07
^c OBC (g)	4.89 ± 0.03	3.69 ± 0.13	3.44 ± 0.00	2.40 ± 0.06
^d EC (%)	40.00 ± 0.00	30.09 ± 0.16	48.58 ± 0.81	19.88 ± 0.18
Intrinsic viscosity (cP)	0.78 ± 0.23	1.29 ± 0.94	1.11 ± 0.85	1.74 ± 1.33
Grafting (%)	550.00 ± 0.04	543.00 ± 0.08	—	—
Grafting yield (%)	54.00 ± 0.06	58.00 ± 0.02	—	—
Grafting efficiency (%)	110.00 ± 0.05	108.00 ± 0.07	—	—

^aCWIG, cold water insoluble gel; ^bHWIG, hot water insoluble gel; ^cOBC, oil binding capacity; ^dEC, emulsion capacity.

stirred at 75 rpm for 3 minutes and 25 rpm for 7 minutes and then allowed to settle for 10 minutes. The absorbance of the supernatant liquids was measured with a UV-Visible spectrophotometer at 600 nm. Low absorbance value is indicative of good flocculation efficacy. The procedure was repeated for 30 and 50 ppm of the flocculants.

2.10. Metal Ion Sorption. Metal ion sorption was carried out by stirring 30 ppm (3 mg of gum in 100 mL of water) of the native and grafted gums and 100 mL solution containing 180 ppm of nickel ion (40 mg of Ni₂SO₄·6H₂O in 100 mL of water) for 20 minutes, which was filtered, and its concentrations were determined with AAS. The metal ion concentration of the filtrate and its retention capacity were determined using (7) and (8), respectively [22].

Metal ion uptake (%)

$$= \frac{\text{Initial conc. of metal ion} - \text{final conc. of metal ion}}{\text{Initial conc. of ion}} \quad (7)$$

$$\times 100\%,$$

Retention Capacity (ppm/mg)

$$= \frac{\text{Initial conc of metal ion} - \text{final conc of metal ion}}{\text{Weight of dry polymer}} \quad (8)$$

where molar mass of Ni₂SO₄·6H₂O and Ni is 262.85 g/mol and 58.7 g/mol, respectively, and conc. is the concentration.

2.11. Statistical Analysis. All determinations were carried out in triplicate and result was reported as the mean ± standard deviation. The swelling and solubility profile were subjected to one-way analysis of variance (ANOVA) using SPSS (Version 16.0 software) to investigate the effect of pH and

TABLE 2: The mineral composition of native *Albizia saman* (ASN) and *Albizia glaberrima* (AGN) gums.

Minerals	ASN	AGN
Calcium (ppm)	64087	99394
Magnesium (ppm)	835.52	964.68
Sodium (ppm)	57842	50436
Lead (ppm)	43.82	42.52

temperature on starch samples. The *Shapiro-Wilk test* of normality and *Levene's tests* of homogenous variance were carried out to assess the assumptions of ANOVA in order to validate the results.

3. Result and Discussion

3.1. Chemical Composition. The physicochemical characteristics of the *Albizia* gums were presented in Table 1. The grafting efficiency of AS (110%) and AG (108%) was similar to that reported for gum ghatti using microwave assisted synthesis (Rani et al., 2012). The 10.89% and 9.9% moisture contents of AS and AG gums, respectively, are within the specification limit of ≤20% for food and pharmaceutical applications [23]. Moisture content determines the storage conditions of materials and the pharmacopeia limit for moisture contents of natural gums is ≤15.0% [24]. The moisture content of AS and AG gums was at par with that reported for xanthan gum and gum arabic but lower than that reported for other *Albizia* species [25, 26]. The 7.87% and 8.60% ash content of AS and AG, respectively, which is higher than that of most commercial gums (Table 2), is indicative of the high mineral content of the gums [25–27].

FIGURE 2: FTIR spectrum of native (ASN) and graft copolymerized (ASG) *Albizia saman* gums.

FIGURE 3: FTIR spectrum of native (AGN) and graft copolymerized (AGG) *Albizia glaberrima* gums.

The CWIG of AS and AG (40.23% and 35.55%) rapidly decreased in hot water to 8.00% and 10.96% (HWIG), respectively. The insoluble gel values observed for AS and AG were higher than that reported for other *Albizia* species [25, 26]. Gums are a complex mixture of polysaccharide with soluble and insoluble fractions; however, the quality of a gum is dependent on the soluble fraction [25].

The emulsifying and oil binding capacity of the AG gum was higher than that of AS (Table 1). Also, the emulsifying capacities of the modified gums were lower than their corresponding native gums. This can be associated with a decrease in percentage protein content due to the presence of acrylamide graft, which probably solubilizes the protein. Polysaccharide contains a small amount of strongly hydrophobic protein component bonded to the polysaccharides [28]. These hydrophobic protein components can adsorb at oil-water interfaces to form stabilizing layers around oil droplets [29]. Hence, the oil binding and emulsifying capacity could be associated with the amount of protein in the polysaccharide.

The bulk density (0.710 and 0.738 g/cm³) of AS and AG (Table 1) is comparable with the 0.721 g/cm³ reported for badam gum [30] but higher than the value of 0.564 g/cm³ for dioclea gum [31] and 0.500 g/cm³ and 0.600 g/cm³ for gum arabic and almond gum [27]. The bulk and tapped densities reduced after graft copolymerization of the gums. The bulk and tapped densities quantify the packing arrangement of the particles of a material and its compaction behavior. The powder flow property is important in the consideration of polysaccharide for industrial use [32]. The flowability of powders can be predicted by its compressibility index (expressed as Carr's index). Compressibility index greater than 26

indicates poor flowability; also, low compressibility index is synonymous with excellent flowability [27, 33]. The 17.535 and 17.555 Carr's index of the *Albizia* gums which reduced after graft copolymerization is indicative of the gum's excellent flowability.

The intrinsic viscosities of the native gums increased from 0.78 and 1.29% for AS and AG gums to 1.11 and 1.74% after graft copolymerization of the gums, respectively (Table 1). AG has a higher intrinsic viscosity (higher molecular weight) than AS. An important property of hydrocolloid is their viscosity which exists due to hydrogen bonding between and within segments of the molecules and also with water molecules. Gums have the ability to influence water many times their own volume significantly. The intrinsic viscosity (which is directly related to molecular weight) increased in the graft copolymerized gums.

The FTIR spectra of the native and grafted copolymerized (modified) AS and AG were presented in Figures 2 and 3, respectively. The spectra of the native gums have broadband around OH band in the 3400–3200 cm⁻¹ range indicating the OH functional group and a peak around 1028–1022 cm⁻¹ indicating the C–O–C functional group. In addition to the above bands, the spectra of the modified gums both have bands for N–H stretch around 3342–3333 cm⁻¹ and for C–N around 1097–1088 cm⁻¹.

The grafted copolymerized gums in addition to being lighter in colour had tougher texture compared with the native gums, which could be as a result of stronger covalent bonds (amide linkage). This is corroborated by the peaks around 1646 cm⁻¹ (ASG) and 1664 cm⁻¹ (AGG) in the spectra which is indicative of presence of amide (Figures 2 and 3).

TABLE 3: The effect of temperature on the solubility of native (ASN) and graft copolymerized (ASG) *Albizia saman* gums and native (AGN) and graft copolymerized (AGG) *Albizia glaberrima* gums over time.

Gum	Time (min)	Temperature				
		40°C	50°C	60°C	70°C	80°C
ASN	0	6.225 ± 0.040	6.175 ± 0.040	6.175 ± 0.04	6.100 ± 0.07	6.050 ± 0.07
ASG	0	5.775 ± 0.040	5.424 ± 0.040	5.775 ± 0.04	5.750 ± 0.07	5.630 ± 0.15
AGN	0	5.900 ± 0.070	5.850 ± 0.070	5.875 ± 0.04	5.875 ± 0.00	5.875 ± 0.04
AGG	0	4.525 ± 0.040	4.425 ± 0.040	4.525 ± 0.04	4.575 ± 0.11	4.225 ± 0.04
ASN	30	6.200 ± 0.000	6.300 ± 0.070	7.075 ± 0.04	7.300 ± 0.07	8.325 ± 0.11
ASG	30	6.075 ± 0.110	6.100 ± 0.070	6.125 ± 0.04	6.075 ± 0.04	7.075 ± 0.04
AGN	30	6.650 ± 0.070	7.050 ± 0.000	7.025 ± 0.04	7.600 ± 0.07	7.025 ± 0.04
AGG	30	5.075 ± 0.040	5.075 ± 0.040	5.500 ± 0.07	5.525 ± 0.04	5.825 ± 0.04
ASN	60	6.225 ± 0.040	6.625 ± 0.04	7.375 ± 0.04	8.125 ± 0.04	8.925 ± 0.11
ASG	60	6.575 ± 0.040	6.775 ± 0.04	7.100 ± 0.00	7.575 ± 0.04	8.275 ± 0.04
AGN	60	7.025 ± 0.040	7.475 ± 0.04	8.100 ± 0.07	8.025 ± 0.11	8.100 ± 0.07
AGG	60	6.050 ± 0.070	6.525 ± 0.11	6.625 ± 0.11	7.775 ± 0.04	8.100 ± 0.07
ASN	90	6.575 ± 0.110	7.475 ± 0.04	8.100 ± 0.07	8.950 ± 0.07	9.475 ± 0.04
ASG	90	6.900 ± 0.140	7.500 ± 0.00	7.800 ± 0.00	8.100 ± 0.07	8.550 ± 0.07
AGN	90	7.800 ± 0.000	7.950 ± 0.07	8.325 ± 0.18	8.200 ± 0.07	8.325 ± 0.18
AGG	90	7.825 ± 0.040	7.075 ± 0.04	7.500 ± 0.14	8.100 ± 0.07	8.275 ± 0.04
ASN	120	7.025 ± 0.040	7.975 ± 0.04	8.975 ± 0.04	9.175 ± 0.11	9.250 ± 0.35
ASG	120	7.775 ± 0.040	8.075 ± 0.04	8.300 ± 0.07	8.575 ± 0.04	9.200 ± 0.07
AGN	120	8.050 ± 0.070	8.300 ± 0.00	8.525 ± 0.04	8.550 ± 0.07	8.525 ± 0.04
AGG	120	7.475 ± 0.040	8.175 ± 0.04	8.075 ± 0.04	8.450 ± 0.04	8.425 ± 0.04
ASN	150	7.575 ± 0.040	8.025 ± 0.04	9.075 ± 0.04	9.300 ± 0.21	9.525 ± 0.04
ASG	150	8.525 ± 0.040	9.075 ± 0.04	9.525 ± 0.04	9.075 ± 0.04	9.350 ± 0.04
AGN	150	8.375 ± 0.040	8.450 ± 0.00	8.775 ± 0.32	8.770 ± 0.14	8.775 ± 0.32
AGG	150	7.975 ± 0.040	8.450 ± 0.07	8.575 ± 0.00	8.770 ± 0.14	8.670 ± 0.11

3.2. Mineral Composition of the Albizia Gums. The mineral composition of the AS and AG is presented in Table 2. The AS and AG gums are richer in calcium and sodium when compared with most of the popular commercial gums such as gum arabic, guar gum, and xanthan gum [25, 26, 34]. Gums contain various metal ions as neutralized atoms; the nature and amount of these constituents depend on the composition of soil upon which the trees grew [35]. Gel formation in certain gums (such as *Khaya grandifoliola*) has been attributed to calcium ions [36].

The AS and AG gums have the essential cations needed by the body (calcium, sodium, and magnesium), and the metal composition trend is $\text{Ca} > \text{Na} \gg \text{Mg}$ trend which is at par with that reported for other *Albizia* gums (Anderson and Morisson, 1990). The *Albizia* gums could be a good gelling agent due to their high calcium content. Lead consumption is dangerous and has a profound effect upon accumulation in the body over a period of time.

3.3. Solubility of the Gums. The effect of temperature (40–80°C) on the solubility profile of the gums is presented in Table 3. As temperature and heating duration increased, the solubility of the gum samples increased. The solubility of the gums at 40°C (within 0–150 minutes) was 6.225–7.575 g/L (ASN) and 5.900–8.375 g/L (AGN); this increased steadily as

the temperature increased; at 80°C, it was 6.050–9.525 (ASN) and 5.875–8.775 g/L (AGN). The graft copolymerized gum's solubility was lower than that of the native gums but also increased with increase in temperature.

The result of the two-way ANOVA test conducted to investigate the effect of temperature (40, 50, 60, 70, and 80°C) and time (0, 30, 60, 90, 120, and 150 minutes) on the gum's solubility is presented in Table 4. The *Shapiro-Wilk* test of normality and *Levene's* tests of homogenous variance were carried out to validate the assumptions of ANOVA in order to authenticate the results. The *Wilk Statistic* for the gum samples is 0.921, 0.953, 0.894, and 0.872 for ASN, ASG, AGN, and AGG, respectively, and its significance was greater than 0.05. *Levene's test* of gum samples was 2.659 with a significance value of 1.64. This result showed that there is a statistically significant interaction between temperature and timing, $F(14, 49) = 19.013$, $p = 0.129$. This suggests that, at lower temperatures, longer time could enhance solubility. An observation of the main effects shows that the two factors, temperature and time, have statistically significant effect on solubility; temperature: $F(3, 49) = 68.099$, $p \leq 0.001$; time: $F(5, 49) = 424.728$, $p \leq 0.001$.

3.4. Flocculation Efficiency of the Gums. The flocculation study in 0.25% kaolin suspension ("jar test" apparatus) for

TABLE 4: Analysis of variation (ANOVA) for the solubility of the *Albizia* gum samples at different temperatures.

Source	Type III sum of squares	Df	Mean square	<i>F</i>	Sig.
Intercept	15252.898	1	15252.898	9.593E4	.000
Time	337.653	5	67.531	424.728	.000
Temp	32.483	3	10.828	68.099	.000
Time * temp	42.319	14	3.023	19.013	.000
Error	10.017	49	.159		

TABLE 5: Flocculation efficiency of native (ASN) and graft copolymerized (ASG) *Albizia saman* and native (AGN) and graft copolymerized (AGG) *Albizia glaberrima* gums at different concentrations in 0.25% kaolin suspension.

Gums	Clarity of kaolin solution (%)		
	10 (ppm)	30 (ppm)	50 (ppm)
ASN	60.76	68.66	74.30
ASG	96.03	98.16	98.29
AGN	60.80	70.07	74.73
AGG	96.38	98.30	98.46

TABLE 6: Ion removal capacity of native (ASN) and graft copolymerized *Albizia saman* (ASG) and native (AGN) and graft copolymerized (AGG) *Albizia glaberrima* gums.

Gums	Initial conc. of Ni ²⁺ (ppm)	Final conc. of Ni ²⁺ (ppm)	Metal ion uptake (%)	Retention capacity (ppm/mg)
ASN	110.000	63.721	42.07	38.760
ASG	110.000	63.342	42.42	38.886
AGN	110.000	62.046	43.59	39.318
AGG	110.000	61.598	44.00	39.467

10, 30, and 50 ppm dosage was presented in Table 5. The flocculation efficiency of the native gums increased after modifications from 60.76% (ASN) to 96.03% (ASG) and 60.80% (AGN) to 96.38% (AGG) at 10 ppm, with significant increase as the dosage increased. The better flocculation efficacy exhibited by the graft copolymerized *Albizia* gums (ASG and AGG) compared with their native gums (ASN and AGN) may be due to their higher intrinsic viscosity as evidenced in Table 1 [22, 37]. AG gum has better flocculant characteristic in the native and the modified gums compared with AS. Branching and molecular weight of polymer chains determine the effectiveness of flocculants [37]. The floc formation is higher in high-molecular-weight branched polysaccharide backbone with flexible grafted polyacrylamide chains.

The ion removal capacity of the native and graft copolymerized AS and AG gums was presented in Table 6. The native and modified AS and AG had high metal ion uptake (42.07–44.00%) and high retention capacity (38.76–39.47 ppm/mg). There was no significant difference in the metal ion uptake and retention capacity of the native and modified *Albizia* gums. However, the native and modified AG gums have better ion removal and retention capacity than the native and modified AS gum, respectively.

4. Conclusion

The AS and AG gums were rich in minerals and contain a higher percentage of insoluble matter compared to most

commercial gums. The gums can also be stored for a long time without losing their integrity and have excellent functional properties comparable with those of most commercial gums. The physicochemical properties of the *Albizia* gums were within the acceptable limits and standards for food pharmaceutical and other industrial applications. A stable graft was formed between acrylamide and the AS and AG gums, with AG gums having higher grafting efficiency. AG gum also has higher flocculation efficiency and ion removal capacity than AS. The modified (acrylamide grafted) *Albizia* gums are better flocculants than the native gums, with the acrylamide grafted AG gum having the best flocculation efficiency.

Conflicts of Interest

The authors declare that there are no conflicts of interest regarding the publication of this paper.

References

- [1] R. Yang, H. Li, M. Huang, H. Yang, and A. Li, "A review on chitosan-based flocculants and their applications in water treatment," *Water Research*, vol. 95, pp. 59–89, 2016.
- [2] M. Manafi, P. Manafi, S. Agarwal et al., "Synthesis of nanocomposites from polyacrylamide and graphene oxide: application as flocculants for water purification," *Journal of Colloid and Interface Science*, vol. 490, pp. 505–510, 2017.

- [3] C. S. Lee, J. Robinson, and M. F. Chong, "A review on application of flocculants in wastewater treatment," *Process Safety and Environmental Protection*, 2014.
- [4] V. H. Dao, N. R. Cameron, and K. Saito, "Synthesis, properties and performance of organic polymers employed in flocculation applications," *Polymer Chemistry*, vol. 7, no. 1, pp. 11–25, 2016.
- [5] N. Thombare, U. Jha, S. Mishra, and M. Z. Siddiqui, "Guar gum as a promising starting material for diverse applications: A review," *International Journal of Biological Macromolecules*, vol. 88, pp. 361–372, 2016.
- [6] K. Ofori-Kwakye, Y. Asantewaa, and S. L. Kipo, "Physicochemical and binding properties of cashew tree gum in metronidazole tablet formulations," *International Journal of Pharmacy and Pharmaceutical Sciences*, vol. 2, no. 4, pp. 105–109, 2010.
- [7] A. M. S. Maia, H. V. M. Silva, P. S. Curti, and R. C. Balaban, "Study of the reaction of grafting acrylamide onto xanthan gum," *Carbohydrate Polymers*, vol. 90, no. 2, pp. 778–783, 2012.
- [8] P. V. Quelemes, A. R. Araujo, A. Placido et al., "Quaternized cashew gum: an anti-staphylococcal and biocompatible cationic polymer for biotechnological applications," *Carbohydrate Polymers*, vol. 157, pp. 567–575, 2017.
- [9] R. M. A. Daoub, A. H. Elmubarak, M. Misran, E. A. Hassan, and M. E. Osman, "Characterization and functional properties of some natural Acacia gums," *Journal of the Saudi Society of Agricultural Sciences*, 2016.
- [10] L. Bai, S. Huan, Z. Li, and D. J. McClements, "Comparison of emulsifying properties of food-grade polysaccharides in oil-in-water emulsions: gum arabic, beet pectin, and corn fiber gum," *Food Hydrocolloids*, vol. 66, pp. 144–153, 2017.
- [11] S. Agnello, L. Gasperini, J. F. Mano et al., "Synthesis, mechanical and thermal rheological properties of new gellan gum derivatives," *International Journal of Biological Macromolecules*, vol. 98, pp. 646–653, 2017.
- [12] A. Rezaei, A. Nasirpour, and H. Tavanai, "Fractionation and some physicochemical properties of almond gum (*Amygdalus communis* L.) exudates," *Food Hydrocolloids*, vol. 60, pp. 461–469, 2016.
- [13] J. B. Lowry, *Trees for Wood and Animal Production in Northern Australia*, Rural Industries Research and Development Corporation. Indooroopilly, Queensland, 2008.
- [14] L. Pachuau and B. Mazumder, "Evaluation of *Albizia procera* gum as compression coating material for colonic delivery of budesonide," *International Journal of Biological Macromolecules*, vol. 61, pp. 333–339, 2013.
- [15] A. R. Dabhadre, N. U. Mokashe, and U. K. Patil, "Purification, characterization, and antimicrobial activity of nontoxic trypsin inhibitor from *Albizia amara* Boiv.," *Process Biochemistry*, vol. 51, no. 5, pp. 659–674, 2016.
- [16] I. F. Adebisin, A. J. Akindele, and O. O. Adeyemi, "Evaluation of neuropharmacological effects of aqueous leaf extract of *Albizia glaberrima* (Leguminosae) in mice," *Journal of Ethnopharmacology*, vol. 160, pp. 101–108, 2015.
- [17] Z. P. Mahlangu, F. S. Botha, E. Madoroba, K. Chokoe, and E. E. Elgorashi, "Antimicrobial activity of *Albizia gummifera* leaf extracts against four *Salmonella* serovars," *South African Journal of Botany*, vol. 108, pp. 132–136, 2017.
- [18] O. P. Noté, S. A. Azouaou, L. Simo et al., "Phenotype-specific apoptosis induced by three new triterpenoid saponins from *Albizia glaberrima* (Schumacher & Thonn.) Benth," *Fitoterapia*, vol. 109, pp. 80–86, 2016.
- [19] V. S. T., L. J. K. Henry, K. Narra, P. Laldusanga, and R. Kandasamy, "Design and development of *Albizia stipulata* gum based controlled-release matrix tablets in cancer therapeutics," *International Journal of Biological Macromolecules*, vol. 92, pp. 972–980, 2016.
- [20] T. A. Afolabi, "Synthesis and physicochemical properties of carboxymethylated bambara groundnut (*Voandzeia subterranean*) starch," *International Journal of Food Science and Technology*, vol. 47, no. 3, pp. 445–451, 2012.
- [21] B. O. Okezie and A. Bello, "Physicochemical and functional properties of winged bean flour and isolate compared with soy isolate," *Journal of Food Science*, vol. 53, no. 2, pp. 450–454, 1988.
- [22] P. Rani, G. Sen, S. Mishra, and U. Jha, "Microwave assisted synthesis of polyacrylamide grafted gum ghatti and its application as flocculant," *Carbohydrate Polymers*, vol. 89, no. 1, pp. 275–281, 2012.
- [23] FAO., "Specification for identity and purity of certain food additives," *Food and Nutrition Paper No. 49*, Rome, 1990.
- [24] R. C. Rowe, P. J. Sheskey, and S. C. Owen, *Hand book of Pharmaceutical Excipients*, Pharmaceutical Press, London, Fifth edition, 2006.
- [25] G. S. Mhinzi, "Properties of gum exudates from selected *Albizia* species from Tanzania," *Food Chemistry*, vol. 77, no. 3, pp. 301–304, 2002.
- [26] M. Faisal, P. P. Singh, and R. Irchaiya, "Review on *Albizia Lebeck*: a potent herbal drug," *International Research Journal of Pharmacy*, pp. 5–11, 3.
- [27] M. Bashir and S. Haripriya, "Assessment of physical and structural characteristics of almond gum," *International Journal of Biological Macromolecules*, vol. 93, pp. 476–482, 2016.
- [28] E. Dickinson, "Emulsifying properties of selected gums," *Food Hydrocolloid*, vol. 17, p. 25, 2003.
- [29] K. S. Chee, P. A. Williams, S. W. Cui, and Q. Wang, "Characterization of the surface-active components of sugar beet pectin and the hydrodynamic thickness of the adsorbed pectin layer," *Journal of Agricultural and Food Chemistry*, vol. 56, no. 17, pp. 8111–8120, 2008.
- [30] V. S. Meka, S. R. Nali, A. S. Songa, and V. R. M. Kolapalli, "Characterization and in vitro drug release studies of a natural polysaccharide *Terminalia catappa* gum (Badam gum)," *AAPS PharmSciTech*, vol. 13, no. 4, pp. 1451–1464, 2012.
- [31] P. F. Builders, C. C. Mbah, and A. A. Attama, "Intrinsic and Functional Properties of a Gelling Gum from *Dioclea reflexa*: a potential pharmaceutical excipient," *British Journal of Pharmaceutical Research*, vol. 2, no. 1, pp. 50–68, 2012.
- [32] E. I. Nep and B. R. Conway, "Physicochemical characterization of grevia polysaccharide gum: Effect of drying method," *Carbohydrate Polymers*, vol. 84, no. 1, pp. 446–453, 2011.
- [33] R. L. Carr, "Evaluating flow properties of solids," *Chemical Engineering Journal*, vol. 72, pp. 163–168, 1965.
- [34] W. Cui and G. Mazza, "Physicochemical characteristics of flaxseed gum," *Food Research International*, vol. 29, no. 3–4, pp. 397–402, 1996.
- [35] R. C. M. De Paula, S. A. Santana, and J. F. Rodrigues, "Composition and rheological properties of *Albizia lebeck* gum exudate," *Carbohydrate Polymers*, vol. 44, no. 2, pp. 133–139, 2001.
- [36] G. S. Mhinzi, "Intra-species variation of the properties of gum exudates from *Acacia senegal* var. *senegal* and *Acacia seyal* var. *fistula* from Tanzania," *Chemical Society of Ethiopia*, vol. 17, pp. 67–74, 2003.
- [37] R. P. Singh, T. Tripathy, G. P. Karmakar et al., "Novel biodegradable flocculants based on polysaccharides," *Current Science*, vol. 78, no. 7, p. 10, 2000.