CERAMIC ON METAL SUBSTRATES PRODUCED BY PLASMA SPRAYING FOR THICK FILM TECHNOLOGY

LESZEK GOŁONKA

*Institute of Electron Technology, Technical University of Wrocław
and*

LECH PAWŁOWSKI

*Institute of Inorganic Chemistry and Metallurgy of Rare Elements, Technical University of Wrocław,
W. Wyspiańskiego 27, 50-370 Wrocław, Poland*

(Received October 3, 1981; in final form October 28, 1981)

The arc plasma spraying process was applied to obtain ceramic coatings on stainless steel substrates. The outer coatings were formed from pure alumina or alumina + 2 wt. % titania mixture. The nichrome intermediate coating was applied to increase adhesion of ceramic coating to stainless steel. The X-ray analysis, metallographic and SEM investigations of the sprayed coatings were also carried out. The effect of interaction of thick film conductor and resistor compositions was studied. Conductor ink P 202 PdAg and resistor ink DP 1321 were evaluated. The TCR, resistance stability were measured as a function of firing cycles. These parameters and the resistivity of sprayed alumina were compared with standard 96% alumina substrate characteristics.

1. INTRODUCTION

The plasma spraying of dielectric coatings onto metallic plates offers the possibility of realization of the substrate for thick film technology. The dielectric coating is the insulator between the metal plate and the thick film circuit and could be also used as the capacitor element. Prepared in this manner substrates have some advantages in comparison with the standard alumina substrates. Smyth *et. al.*¹ showed that in the production of 50,000 substrates the cost of a typical alumina substrate 96% Al₂O₃, size 25 × 25 × 0.65 mm is in the range of US \$ 0.08 for each substrate. The preliminary cost of producing 25 × 25 mm sprayed alumina on kovar substrates could be estimated as US \$0.02. The production rate of plasma sprayed substrates reaching several meters an hour is another important advantage.

The heat conductivity of such substrates can be expressed as:

$$\lambda_s = \lambda_1 \frac{l + d}{d \frac{\lambda_1}{\lambda_2} + l} \quad (1)$$

where: λ — heat conductivity, l — dielectric coatings thickness, d — metal plate thickness, s , 1, 2 — parameters attributed to substrate, dielectric coating, metal plate.

It is obvious from eq. (1) that the application of a thick plate of good heat conducting metal will result in a good heat conducting substrate. Mackay and Muller² have determined the sprayed alumina heat conductivity 18–28 W/(m K) as dependent upon the temperature. Taking from their paper $\lambda_1 \sim 20$ W/(m K) and assuming $l = 0.1$ mm, $d = 0.5$ mm and $\lambda_2 \sim 400$ W/(m K) — as for copper — one can estimate the λ_s value as nearly 100 W/(m K). The value is similar to the heat conductivity of very expensive beryllia ceramics.

The sprayed coatings surface flatness is also better than for conventional sintered alumina substrates. This parameter is important from the screen printing point of view.

Up to now a similar subject was taken up by, apart from the both mentioned above papers, Braguier *et. al.*³ This paper described sprayed alumina coating on copper plates as a dielectric in micro-strips lines. The idea of sprayed ceramic on metal substrates was shown also in a patent.⁴

For over four years porcelain enamelled substrates have been developed for hybrid circuits applications. A lot of papers on this subject have been published at ISHM conferences from 1978. These kind of substrates can be produced following Stein *et. al.*⁵ by:

- dipping, slushing or spraying of a water-based slurry or slip,
- electrophoretic deposition of glass,
- electrostatic spraying of dry powder.

However, these technologies have limits for some application e.g. the firing temperature of the substrate is limited to 700°C. Only Kuzel⁶ has shown the possibility of heating the substrates up to 860°C. Also the heat conductivity of typical enamels is several times lower than that of alumina (Lebailly⁷ had reported the value of 5.15 W/(m K)). Finally one can refer to "brown plague" — the term which describes the shortages between conductor and steel core reported as often appearing in enamelled substrates, by e.g. Allington and Cote⁸ or Schabecker.⁹

Plasma spraying technology offers an opportunity to avoid the above mentioned problems and to be tried for hybrid microelectronic substrate production.

2. MATERIALS

The powders applied in the investigations are characterized in Table I.

TABLE I
Some characteristics of the powders used

Notations	Powder	X-ray phases	Manufacturer	Remarks
01	Al ₂ O ₃ + 2wt.% TiO ₂	α-Al ₂ O ₃	Metco, Inc., Westbury, USA	type 101 SF
OD	Al ₂ O ₃	α-Al ₂ O ₃	Institute of Nuclear Research, Warsaw, Poland	produced by sol-gel method
NC	NiCr(80/20)		Technical Univer- sity of Wroclaw, Poland	produced by liquid metal atomization

Powder OD is spherical in shape (Figure 1b). This shape provides facilities for feeding the powder to the plasma gun. The powder 01 is shown in Figure 1a.

The distributions of used powder diameters, determined by the sedimentation method, are shown in Figure 2.

Stainless steel, type 1H18N9T, was used as the metal plates. The steel was cut into 20 × 30 × 2 mm plates.

FIGURE 1 The shape of alumina powders used, a – 01, b – OD.

FIGURE 2 The distributions of the used powder diameters.

3. TECHNOLOGY OF THE SUBSTRATE PRODUCTION

The steel plates were grit blasted prior to the spraying process. Silica sand with sizes lower than 0.4 mm was used for blasting. The pressure of air, in this process, was equal to 0.6 MPa. The sprayed plates were fixed to the suction cup (Figure 3). This solution was chosen to minimize the residual stresses which could appear in the coating after spraying.

The suction cup was mounted in a swivel. The plasma spraying was conducted using a PN-200 plasma installation. The operational parameters are shown in Table II.

During the spraying process air cooling was used. The NiCr (80/20) subcoat was first deposited and then the alumina coating was applied.

FIGURE 3 Suction cup scheme, 1 – metal plate for spraying, 2 – Ni – NiCr thermocouple, 3 – vacuum pump, 4 – temperature monitor.

TABLE II
Plasma spray parameters

Powder		01	OD	NC
Plasma gases:-				
Primary: Argon	(Ndm ³ /s)	1.2	1.2	1.2
Secondary: Hydrogen	(Ndm ³ /s)	0.12	0.12	0.12
Feeding gas:-				
Argon	(Ndm ³ /s)	0.083	0.083	0.083
Current	(A)	600	600	500
Voltage	(V)	65	65	65
spraying distance	(cm)	10	10	10
sliding velocity	(cm/s)	0.4	0.4	0.4
no. sliding cycles		1	2	1
substrate				
front temperature ^a :-				
prior to spraying	(°C)	150	150	150
after spraying	(°C)	350	450	350

† averaged values

4. RESULTS

The introductory researches were aimed at finding an alumina powder which when sprayed on to a nichrome substrate maintains adhesion up to a temperature of 800°C. In these researches the Al₂O₃ powder, Metco – type 105 SF, was eliminated.

4.1 Physical and Structural Properties of the Alumina Coatings.

The X-ray investigations were carried out using Cu K α radiation. The bias cross-section of sprayed samples were examined using metallographical and Vickers microhardness tests. The tensile bond strength of the sprayed coatings was determined according to the norm.¹⁰ The results of these investigations are shown in Table III.

TABLE III
Some physical properties of plasma sprayed alumina coatings

Coating	X-ray phases ^a	Strongest peaks intensity ratio I_{δ}/I_{α} ^b	Density (kg/m ³)	Vickers micro-hardness (MPa)	Tensile bond strength ^c (MPa)
OD	α -Al ₂ O ₃ δ -Al ₂ O ₃	1.6	3450	12300	18
01	α -Al ₂ O ₃ δ -Al ₂ O ₃	25	—	—	25

^aThe phases were identified using ASTM cards no. 10-174 (α -Al₂O₃) and 16-394 (δ -Al₂O₃).

^bThe strongest observed peak for α -Al₂O₃-d₁₂₄ = 1.404 Å; for δ -Al₂O₃-d_{0.0.12} = 1.939 Å.

^cFailure occurred at the intermediate coating/alumina interface.

The sprayed alumina contains the metastable phase δ -Al₂O₃ which considerably lowers the coating density ($\rho \sim 4000$ kg/m³) for corundum. The microhardness, determined under the load 2N, is also lower than for sintered carborundum (HV ~ 20000 MPa). The coatings sprayed using OD powder have higher corundum content. Therefore they conduct the heat better. The sprayed alumina coatings surface (Figure 4) shows that the sprayed powder grains were molten during impact with the substrate. They had melted on to the surface. The small grains, appearing after large grains had formed on the substrate, are also visible.

There were no visible fractures on the coatings surface. The coating sprayed using 01 powder has a smoother surface than that of OD. The roughness of the first, determined using a ZEISS-ME 10 apparatus, is equal to 3.1 μ m AA.

The metallographical cross-section shown in Figure 5 exhibits some pores and discontinuities in the coating.

FIGURE 4 Sprayed alumina coatings surface, a – OD, b – 01.

FIGURE 5 Sprayed coating cross-section, powder type 01.

4.2 Electrical Properties of the Alumina Coatings.

Two different types of ceramic coatings using OD and 01 alumina powders have been tested. Dielectric properties of the ceramic layers were tested in a capacitor system (Electrode area, $S = 1 \text{ cm}^2$), with stainless steel and thick film electrodes. A thick film, P 202 (PdAg), electrode was fired at 800°C peak temperature for 10 minutes. Surface resistivity was determined for a resistor 105 mm length and 0.5 mm width. The test pattern used is shown in Figure 6. Electrical parameters of the ceramic layers examined are summarized in Table IV. The insulation properties of sprayed OD powder coatings were much better than that of 01 powder. Electrical parameter differences were in 2 or 3 orders of magnitude in favour of the OD powder coatings.

FIGURE 6 Test pattern.

TABLE IV
Electrical properties of plasma sprayed alumina coatings

	OD coating	01 coating
Volume resistivity ($\Omega \text{ cm}$)	$\sim 10^9$	$\sim 10^7$
Surface resistivity ($\Omega/\text{sq.}$)	$\sim 10^{12}$	$\sim 10^9$
Dissipation factor (1.5 kHz)	0.015	3.5
Capacity ^a (pF) (1.5 kHz)	200	800

^aCapacity measured between the metal plate and the thick film electrode, $S = 1 \text{ cm}^2$, coatings thickness: OD $\sim 50 \mu\text{m}$, 01 $\sim 20 \mu\text{m}$.

4.3 Electrical Properties of the Thick Film Resistors.

The properties of a thick film resistor system made on the tested substrates was determined. The conductor ink, P 202 (PdAg), and the resistor ink, Du Pont DP 1321, were evaluated. The resistors and conductors were fired separately. All firings were carried out

FIGURE 7 Multiple firing behaviour of sprayed coatings: OD powder "x", 01 powder "+", 96% alumina substrate "o".

FIGURE 8 Multiple firing behaviour of sprayed coatings: OD powder "x", 01 powder "+", 96% alumina substrate "o".

at 800°C peak temperature for 10 minutes on a profile used for DP 1321 ink on alumina substrates. The tested resistors were 5×5 mm in dimension.

The measured sheet resistivities and hot TCR were in agreement with the manufacturer's data for DP 1321 on the alumina substrates. The sheet resistivities, 70 $\Omega/\text{sq.}$ and 75 $\Omega/\text{sq.}$, were obtained for OD and O1 powder coatings respectively. Hot TCR, 250 ppm/°C and 190 ppm/°C, were determined. The effect of refiring on the resistance and TCR is shown in Figures 7 and 8. For comparison the behaviour of the same resistors on 96% alumina substrates are also shown. The resistors made on OD powder coating substrates had better refiring stability than the resistors on O1 powder coating substrates. The stabilities of the resistors on 96% alumina substrates and OD powder coatings were similar. TCR changes during refiring were comparable for all types of substrates.

5. CONCLUSION

The resistors printed on stainless steel NiCr/Al₂O₃/(OD) substrates show sufficient resistance stability and sheet resistivity comparable to those printed on conventional alumina substrates and a TCR that is only slightly higher. The sheet resistivity and dissipation factor of sprayed ceramics type OD are better than sprayed O1 ceramics but significantly worse than sintered alumina substrates. Therefore, the technology presented permits substrates to be obtained with electrical parameters comparable to conventional sintered alumina ceramics.

ACKNOWLEDGEMENTS

The authors are grateful to Prof. B. Licznarski for the inspiration to do this work and to Prof. A. Czernichowski for many discussions.

REFERENCES

1. R.T. Smyth, F.J. Dittrich, J.D. Weir, "Thermal spraying – a new approach to thick film circuit manufacture", *Proc. Conf. Advances in Surface coating Technology*, London 1978/The Welding Institute, London p. 223 (1979).
2. T.L. Mackay, A.N. Muller, "Plasma spraying dielectric coating for heat sinks in electronic packaging", *Ceramic Bulletin*, **46**, p. 833 (1967).
3. M. Braguier, J. Bejat, R. Tueta, M. Verna, G. Aubin, C. Naturel, "Improvements of plasma spraying process for hybrid microelectronics", *Proc. Conf. on Hybrid Microelectronics*, Kent 1973/I.E.R.E. London p. 251 (1973).
4. Polish patent no. 161863, (1973).
5. S.J. Stein, C. Huang, A.S. Gelb, "Comparison of enamelled steel substrate for thick film use", *Proc. Conf. on Hybrid Microelectronics*, Ghent p. 525 (1979).
6. R. Kuzel, J. Broukal, "Enamelled steel substrates for printed circuits", *Proc. Conf. on Hybrid Microelectronics*, Avignon p. 365 (1981).
7. M. Lebailly, "Steel enamelled substrates", *ibid*, p. 362.
8. T.R. Allington, R.E. Cote, "Characterization of thick films compositions on porcelain steel substrates", *Solid State Technology*, January, 81 1979.
9. R.B. Schabecker, "Porcelain enamelled substrates for hybrid circuits and printed circuits", *Proc. Conf. on Hybrid Microelectronics*, Ghent p. 539 (1979).
10. "Adhesion or cohesive strength of flame-sprayed coatings", ASTM norm, pp 633–69.