

Conference Paper

Study of Structural and Electronic Behavior of BeH₂ as Hydrogen Storage Compound: An Ab Initio Approach

Vikas Nayak, Suman Banger, and U. P. Verma

School of Studies in Physics, Jiwaji University, Gwalior 474 011, India

Correspondence should be addressed to Vikas Nayak; vikas.nayak88@gmail.com

Received 28 January 2014; Accepted 3 March 2014; Published 27 April 2014

Academic Editors: P. Mandal, R. K. Shivpuri, and G. N. Tiwari

This Conference Paper is based on a presentation given by Vikas Nayak at “National Conference on Advances in Materials Science for Energy Applications” held from 9 January 2014 to 10 January 2014 in Dehradun, India.

Copyright © 2014 Vikas Nayak et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

The quantum mechanical calculations based on density functional theory (DFT) have been performed to study ground state structural and electronic properties of BeH₂ and along with doping of two (BeH₂ + 2H) and four (BeH₂ + 4H) hydrogen atoms. The generalized gradient approximation (GGA) has been employed for the exchange correlation energy. The most stable space group of BeH₂ is *Ibam*. Its optimized equilibrium unit cell volume, bulk modulus and its first-order pressure derivative, and electronic properties have been obtained. Our predicted unit cell parameters for BeH₂ $a = 9.2463 \text{ \AA}$, $b = 4.2352 \text{ \AA}$, and $c = 7.8464 \text{ \AA}$ are in very good agreement with the earlier reported experimental and theoretical results. The electronic band structure of BeH₂ shows its behavior as an insulator. The stability of BeH₂ along with doped hydrogen atoms increases, while the energy band gap decreases with the increase in number of doped hydrogen atoms. On these bases, we predict that BeH₂ is a promising material for hydrogen storage.

1. Introduction

Energy storage for the future is a great concern for the researchers and scientists. We need materials like metal hydrides for various potential applications, that is, for hydrogen storage, in fuel cells and internal combustion engines, as electrodes for rechargeable batteries, and in energy conversion devices. The metal hydrides for hydrogen storage need to be able to form hydrides with a high hydrogen-to-metal mass ratio, but they should not be too stable, so that the hydrogen can easily be released without excessive heating. Beryllium and magnesium and beryllium-magnesium-based hydrides contain a relatively high fraction of hydrogen by weight but need to be heated ~250 to 300°C in order to release the hydrogen. The alkali-metal and alkaline-earth-metal hydrides represent series with largely ionic bonding. The high pressure behavior of the alkali-metal monohydrides is expected to parallel of the alkali-metal halides [1]. However,

there is no systematic high-pressure study on the alkaline-earth-metal hydrides. If BeH₂ becomes metallic when subjected to high pressures, one can entertain the possibility that its properties could resemble those of metallic hydrogen. BeH₂ is commonly considered as a covalent hydride with a postulated polymeric crystal structure made up of H-bridged chains. However, mainly owing to experimental difficulties in the synthesis of the material, the structure has long remained unknown [2]. Crystalline BeH₂ has been synthesized and the structure has been established as body centered orthorhombic by synchrotron-radiation-based powder X-ray diffraction [3]. First-principles total-energy calculations were performed for various types of structural variants, among which it was confirmed that the experimentally observed body centered orthorhombic (*Ibam*) structure of BeH₂ has the lowest total energy.

In this paper, we have carried out the first-principles calculations of the ground-state behavior of BeH₂ in *Ibam*

TABLE 1: Calculated structural parameters, bulk modulus B and its pressure derivative B'_0 , and energy for orthorhombic BeH_2 are listed with available references.

Compound	Lattice parameter (in Å)			B (in Gpa)	B'_0	E (in Ry)	Reference
	a	b	c				
BeH_2	9.246	4.235	7.846	53.24	5.0	-191.285	
	9.082	4.160	7.707				[3, 4]
	8.982	4.156	7.645	23.79			[5, 6]
$\text{BeH}_2 + 2\text{H}$	9.475	4.341	8.091	50.42	3.2	-193.202	
$\text{BeH}_2 + 4\text{H}$	10.078	4.616	8.553	40.04	2.9	-194.901	




FIGURE 1: Crystal structures of (a) BeH_2 , (b) $\text{BeH}_2 + 2\text{H}$, and (c) $\text{BeH}_2 + 4\text{H}$ in $Ibam$ phase.

phase. Results for the structural and electronic properties are systematically presented. The calculations have also been extended for extra hydrogen added structures ($\text{BeH}_2 + 2\text{H}$ and $\text{BeH}_2 + 4\text{H}$) in the same phase. The obtained results are discussed in this paper.

2. Computational Details

The structural and electronic properties of the BeH_2 are obtained using density functional theory (DFT) [7, 8]. The full potential-linearized augmented plane wave (FP-LAPW) method has been employed for the calculation as implemented in the Wien2k code [9]. Generalized gradient approximation (GGA) is used to calculate the exchange-correlation functional. We expand the basis function up to $R_{\text{MT}} * k_{\text{max}} = 7$, where R_{MT} is the smallest radius of the muffin-tin (MT) spheres and k_{max} is the maximum value of the reciprocal lattice vectors. The maximum l value for the wave function expansion inside the atomic spheres was confined to $l_{\text{max}} = 10$. The k -points used in the calculations were based on $5 \times 5 \times 5$ Monkhorst-Pack scheme [10]. The iteration process was repeated until the calculated total energy and charge of the crystal converge to less than 0.0001 Ry and $0.001 e^-$, respectively. In order to avoid ambiguities regarding the calculated results, we have used the same value of the energy cutoff as well as k -grid density for convergence for all the structural variants studied. The present theoretical approach has been successfully applied to study ambient- and high-pressure phases computationally.

The bulk BeH_2 exhibits $Ibam$ structure in ground state. The obtained unit cell parameters for this structure of BeH_2

are listed in Table 1. In order to obtain the equilibrium structural parameters, we carried out optimization of the total energy as a function of unit cell volume. Obtained sets of the unit cell volume and corresponding total energy have been fitted to the Murnaghan's equation of state [11]. The bulk BeH_2 has also been studied with added number of hydrogen for the purpose of comparison between the ground state electronic properties of BeH_2 and with the doped hydrogen BeH_2 . The studied variants are $\text{BeH}_2 + 2\text{H}$ and $\text{BeH}_2 + 4\text{H}$. The obtained structural parameters for all the variants have been listed in Table 1.

3. Results and Discussion

3.1. Structural Properties. The ground state of BeH_2 has been synthesized experimentally [3] and studied theoretically [5]. Its orthorhombic unit cell (space group $Ibam$) is composed of twelve BeH_2 formula units as shown in Figure 1(a).

The primitive cell contains six formula units. The Wyckoff positions of different atoms are two Be1 (4a), four Be2 (8j), eight H1 (16k), and four H2 (8j). Each Be1 is surrounded by four H1 atoms to build the tetrahedral structure and each Be2 connects with two H1 atoms and two H2 atoms. Calculated atomic structural parameters for orthorhombic BeH_2 are included in Table 1. The obtained results of BeH_2 are in excellent agreement with the previous theoretical results [5, 6] and available experimental data [3, 4].

BeH_2 also studied with two and four extra added hydrogen atoms. Optimized values for unit cell volume and corresponding energy are fitted to Murnaghan's equation of state [11]. The optimization curve is shown in Figure 2. From




FIGURE 2: Optimization curves for (a) BeH₂ (b) BeH₂ + 2H, and (c) BeH₂ + 4H.

the optimized unit cell volume, we have calculated the lattice parameters of BeH₂ + 2H and BeH₂ + 4H. The obtained unit cell parameters and other constants are listed in Table 1.

It is evident from Table 1 and plots in Figure 2 that the optimized energy of BeH₂ is less than that of BeH₂ + 2H and the energy of BeH₂ + 2H is less than that of BeH₂ + 4H. This indicates clearly that the stability of structures increases with the increase in the number of hydrogen atoms. A plot of total energy as a function of the doped hydrogen atoms is shown in Figure 3(a) and plot of unit cell volume versus number of doped hydrogen atoms is shown in Figure 3(b). The plot in

Figure 3(a) shows linear behavior, while plot in Figure 3(b) is nonlinear.

The band structure of BeH₂ shows insulator behavior as in this case direct energy band gap is ~5.8 eV, while band structure plots for BeH₂ + 2H and BeH₂ + 4H show semiconducting behavior because in these cases indirect energy band gaps are, respectively, ~2.2 eV and ~2.5 eV (Figure 4). It is very interesting to note that below Fermi energy level width of a group of valence-band is ~6.5 eV which is in excellent agreement with earlier reported data [5]. The width of the group of valence-bands increases with




FIGURE 3: A plot between optimized energy and added extra number of hydrogen.




FIGURE 4: Electronic band structures for (a) BeH_2 , (b) $\text{BeH}_2 + 2\text{H}$, and (c) $\text{BeH}_2 + 4\text{H}$.

the increase in number of doped hydrogen atoms. For $\text{BeH}_2 + 2\text{H}$, this width is ~ 6.5 eV and for $\text{BeH}_2 + 4\text{H}$ it is ~ 7.5 eV. The behavior of conduction bands is somewhat different. Corresponding to two doped hydrogen atoms conduction bands near Fermi level are separated, while for 6 doped hydrogen atoms they are further compressed. This shows that number of added hydrogen atoms has significant effect on energy levels.

4. Conclusions

In this work, the structural stability of the Beryllium Hydride, BeH_2 , and doped hydrogen compounds $\text{BeH}_2 + 2\text{H}$ and $\text{BeH}_2 + 4\text{H}$ have been studied by the first-principles calculations. The equilibrium structures of these compounds are obtained from DFT/GGA total energy minimization. The obtained results for BeH_2 are in excellent agreement with



the reported experimental and theoretical results. BeH_2 is an insulator and $\text{BeH}_2 + 2\text{H}$ and $\text{BeH}_2 + 4\text{H}$ are semiconductor. The effect of added hydrogen atoms is very clear. The stability of $\text{BeH}_2 + 4\text{H} > \text{BeH}_2 + 2\text{H} > \text{BeH}_2$. Lower value of total energy in $\text{BeH}_2 + 4\text{H}$ shows that hydrogen storage in BeH_2 is one of very good option (Figure 2).

Conflict of Interests

The authors declare that there is no conflict of interests regarding the publication of this paper.

References

- [1] St. J. Duclos, Y. K. Vohra, A. L. Ruoff, S. Filipek, and B. Baranowski, "High-pressure studies of NaH to 54 GPa," *Physical Review B*, vol. 36, no. 14, pp. 7664–7667, 1987.
- [2] D. R. Armstrong, J. Jamieson, and P. G. Perkins, "The electronic structures of polymeric beryllium hydride and polymeric boron hydride," *Theoretica Chimica Acta*, vol. 51, no. 2, pp. 163–172, 1979.
- [3] G. S. Smith, Q. C. Johnson, D. K. Smith et al., "The crystal and molecular structure of beryllium hydride," *Solid State Communications*, vol. 67, no. 5, pp. 491–494, 1988.
- [4] M. Ahart, J. L. Yarger, K. M. Lantzky, S. Nakano, H.-K. Mao, and R. J. Hemley, "High-pressure Brillouin scattering of amorphous BeH_2 ," *The Journal of Chemical Physics*, vol. 124, no. 1, Article ID 014502, 2006.
- [5] P. Vajeeston, P. Ravindran, A. Kjekshus, and H. Fjellvåg, "Structural stability of BeH_2 at high pressures," *Applied Physics Letters*, vol. 84, no. 1, pp. 34–36, 2004.
- [6] U. Hantsch, B. Winkler, and V. Milman, "The isotypism of BeH_2 and SiO_2 : an ab initio study," *Chemical Physics Letters*, vol. 378, no. 3-4, pp. 343–348, 2003.
- [7] P. Hohenberg and W. Kohn, "Inhomogeneous electron gas," *Physical Review*, vol. 136, no. 3, pp. B864–B871, 1964.
- [8] W. Kohn and L. J. Sham, "Self-consistent equations including exchange and correlation effects," *Physical Review*, vol. 140, no. 4, pp. A1133–A1138, 1965.
- [9] P. Blaha, K. Schwarz, P. Sorantin, and B. Rckey, "Full-potential, linearized augmented plane wave programs for crystalline systems," *Computer Physics Communications*, vol. 59, no. 2, pp. 399–415, 1990.
- [10] H. J. Monkhorst and J. D. Pack, "Special points for Brillouin-zone integrations," *Physical Review B*, vol. 13, Article ID 5188, 1976.
- [11] F. Murnaghan, "The compressibility of media under extreme pressures," *Proceedings of the National Academy of Sciences of the United States of America*, vol. 30, no. 9, pp. 244–247, 1944.



Hindawi

Submit your manuscripts at
<http://www.hindawi.com>

