Editorial

Photocatalysis and Photoelectrochemistry for Solar Fuels

Zhigang Zou,¹ Jinhua Ye,² Michael R. Hoffmann,³ and Wenjun Luo¹

¹Department of Physics, Ecomaterials and Renewable Energy Research Center (ERERC), Nanjing University, Nanjing 210093, China

²International Center for Materials Nanoarchitectonics (MANA), National Institute for Materials Science (NIMS), Tsukuba 3050044, Japan

³Linde-Robinson Laboratories, California Institute of Technology, Pasadena, CA 91125, USA

Correspondence should be addressed to Zhigang Zou; zgrou@nju.edu.cn

Received 21 October 2014; Accepted 21 October 2014; Published 1 December 2014

Copyright © 2014 Zhigang Zou et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

The Sun generates enough energy to power the Earth. However, solar energy should be stored into chemical energy to be conveniently used due to its low energy density and discontinuous radiation. In the last several years, photocatalysis and photoelectrochemistry for solar fuels have reattracted more and more governments' and people's interest from all over the world and become a very hot topic. If we utilize the abundant solar energy to convert CO₂ into hydrocarbon fuels especially, it would address the problems of global climate change and solar energy storage at the same time. Recently, different new materials and ideas have been proposed and steady scientific progress has been done. However, it is still a key challenge to explore visible-light responsive materials with high photocatalytic activities. The special issue contains eight papers, where 6 papers are related to visible-light activity and 2 papers are related to UV activity.

In a paper entitled "*Development of thin film amorphous silicon tandem junction based photocathodes providing high open-circuit voltages for hydrogen production*" by F. Urbain et al., they prepare the a-Si:H/a-Si:H based photocathodes, which exhibit a high photocurrent onset potential of 1.76 V versus the reversible hydrogen electrode (RHE) and a photocurrent of 5.3 mA/cm² at 0 V versus RHE. They provide an efficient and low-cost route to solar hydrogen production.

In a paper entitled "*Bottom-up enhancement of g-C₃N₄ photocatalytic H₂ evolution utilising disordering intermolecular interactions of precursor*" by X. L. Wang et al., they develop a bottom-up strategy to synthesize g-C₃N₄ photocatalysts with improved optical property and chemical structure through using disordered dicyandiamide (D-DCDA) as reaction precursor. The carbon nitride sample condensed

by D-DCDA indicates higher photocatalytic activity for hydrogen evolution due to looser structure and more effective light harvesting and charge separation efficiency.

In a paper entitled "*Structure, optical properties, and photocatalytic activities towards H₂ generation and CO₂ reduction of GaN nanowires via vapor-liquid-solid process*" by H. Pang et al., they synthesize high quality single crystalline GaN nanowires with large aspect ratio on n-type Si (111) substrate via the Au-catalyzed vapor-liquid-solid process. Photocatalytic H₂ evolution and CO₂ reduction over the as-prepared GaN nanowires are also investigated. Their results suggest that the GaN nanowires greatly enhanced capability compared to the GaN powders.

In a paper entitled "*Band-gap engineering of NaNbO₃ for photocatalytic H₂ evolution with visible light*" by P. Li et al., they shift the photoabsorption edge of NaNbO₃ to the visible-light region by La and Co codoping. Moreover, H₂ is successfully generated over the doped NaNbO₃ samples under visible-light irradiation. Density-functional theory calculations show that Co-induced impurity states are formed in the band gap of NaNbO₃, which is considered to be the origin of visible-light absorption upon the doped NaNbO₃ sample.

In a paper entitled "*Sensitization of perovskite strontium stannate SrSnO₃ towards visible-light absorption by doping*" by H. Chen and N. Umezawa, they calculate electronic structures of SrSnO₃ after Cr³⁺, Fe³⁺, and Rh³⁺ and anions N³⁻, N²⁻, and S²⁻ doping. Among all considered cation dopants, Rh³⁺ gives rise to the deep in gap states. The transition from Rh³⁺ to SrSnO₃ conduction band is 0.89 eV lower than the band gap.

In a paper entitled “*Surfactant-free synthesis of single crystalline SnS₂ and effect of surface atomic structure on the photocatalytic property*” by M. Li et al., they prepare sheet like tin disulfide SnS₂ single crystal exposed with well-defined {001} facets and flowerlike SnS₂ mainly exposed with {010} facets through a surfactant-free solvothermal process. The sheet like SnS₂ showed a much higher photocatalytic activity in degradation of methyl orange than flowerlike SnS₂. Theoretical and experimental results reveal that the band structure derived from the surface atomic structure played a more important role than the surface energy in the photocatalytic property.

In a paper entitled “*Preparation of cerium modified titanium dioxide nanoparticles and investigation of their visible light photocatalytic performance*” by J. Liu et al., they prepare CeO_x/TiO₂ by the hydrothermal-calcination method. The Ce ions have the two valence states, Ce³⁺ and Ce⁴⁺, which can act as the electron acceptor to improve the separation efficiency of the photogenerated electron-hole pairs.

In a paper entitled “*Visible-light degradation of dyes and phenols over mesoporous titania prepared by using anthocyanin from red radish as template*” by Z. Yan et al., they prepare highly crystalline mesoporous titania by using a natural pigment from red radish as template. The prepared mesoporous titania photocatalyst exhibited significant activity under visible-light irradiation for the degradation of dyes and phenols due to its red shift of band-gap-absorption onset and visible-light response as a result of the incorporation of surface carbon species.

Acknowledgment

We would like to thank all of the authors and the reviewers for their contributions to this special issue.

Zhigang Zou
Jinhua Ye
Michael R. Hoffmann
Wenjun Luo