Editorial

1D Nanomaterials

Raymond L. D. Whitby,¹ Steve F. A. Acquah,² Renzhi Ma,³ and Yanqiu Zhu⁴

¹ *Nanoscience & Nanotechnology Group, School of Pharmacy and Biomolecular Sciences, University of Brighton, Lewes Road, Brighton BN2 4GJ, UK*

² *The Kroto Group, Department of Chemistry & Biochemistry, Florida State University, Tallahassee, FL 32306-4390, USA*

³ *Soft Chemistry Group, International Center for Materials Nanoarchitectonics (MANA), National Institute for Materials Science (NIMS), Namiki 1-1, Tsukuba, Ibaraki 305-0044, Japan*

⁴ *College of Engineering, Mathematics, and Physical Sciences, University of Exeter, North Park Road, Exeter EX4 4QF, UK*

Correspondence should be addressed to Raymond L. D. Whitby, r.whitby@brighton.ac.uk

Received 18 August 2010; Accepted 18 August 2010

Copyright © 2010 Raymond L. D. Whitby et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

The advent of nanoscience and nanotechnology is widely regarded as coming to fruition at the result of two key papers. The first in 1985 reported an intriguing artefact of stabilisation of carbon clusters from high temperature plumes [1], though fullerene molecules have since been discovered created by shockwave in a 1.28 billion-year-old impact site [2]. The second in 1991 reported detailed images of what was later termed carbon nanotubes [3], although a comprehensive search of past papers [4] uncovered reports of carbon nanotubes in 1976 and 1952 [5, 6] and a further discovery that a seventeenth century Damascus steel sword contained carbon nanotubes [7]. Whilst it is important to properly ascertain the history of nanoscience, the papers of Kroto et al. and Iijima are no less deserving of their estimable renown.

It should be without any doubt that nanoscience and nanotechnology has had a significant global impact in redefining existing and developing novel research avenues over the last two decades. Where bottom-up assembly meets conventional top-down refinements, nanomaterials proffer the necessary bridge between atomistic processes and useable macroscale devices. Focus has largely been towards preparative methods with specific interest in controlling the fundamental properties and architecture, where the inextricable link between size & geometry and properties of one-dimensional (1D) nanomaterials, for example, nanotubes, nanowires, nanorods, reveals a wide variety of promising applications. It is hoped this will in turn unlock the potential of such nanomaterials in devices. In this special issue on

1-dimensional nanomaterials, we have invited a number of authors to address such matters and thus provide an up-to-date consideration of the field.

The first paper, by Sivakumar et al. [8], appraises the synthesis of carbon nanotubes via chemical vapour deposition (CVD) techniques. They explore the different types of CVD growth available, the influence of catalytic particles and reaction conditions. The second paper, by Hu et al. [9], report the use of “green” chemistry in the non-toxic and non-hazardous large scale CVD synthesis of carbon nanotubes with uniform diameters. This facile approach should prove useful for industrial scale-up in an increasingly environmentally conscious market. The third paper, by Liu et al. [10], examines carbon nanotube-metal oxides composites, where the formed MgO nanorods are determined to facilitate the growth of the encapsulating carbon nanotube. This is an important avenue of exploration where control over the length, diameter and geometry of carbon nanomaterials is important.

Template growth of nanomaterials has proven a useful methodology for controlling the architecture and in turn the properties of nanomaterials [11]. The fourth paper, by Dai et al. [12], explores such a route in the formation of coaxial CdSe-SiO_x nanocomposites with the potential of controlling the final electronic properties. The fifth paper, by Suzuki et al. [13], presents a removable template growth of silica and titania in a one-pot approach that promises to be useful for the generation of nanosize systems. Temporary

templates have also been demonstrated to prove useful for nucleation of nanomaterials where Gan et al. [14], in the sixth paper, explored the biomimetic assembly of ZnO on top of gelatin, which then spontaneously formed into 3-dimensional nanostructures.

A number of other approaches have been investigated for the formation of inorganic nanostructures [15]. The seventh paper, by Ding et al. [16], investigates the co-precipitation of indium tin oxide nanoparticles. Thermal evaporation heightens the stochastic energetics of chemical fragments, which has the greatest potential of diversifying nanoscale architecture on cooling. The eighth paper, by Peng et al. [17] and ninth paper, by Ban et al. [18], uses thermal evaporation techniques leading to the generation of elegant hierarchical ZnO and MoO₃ nanostructures respectively.

Both high temperature and high pressure treatment on existing nanomaterials can alter their crystal phase, which is potentially useful for a range of purposes from heterogeneous catalysis to piezoelectronics [19]. The tenth paper, by Ou et al. [20], addresses high temperature crystal phase alterations for titanate and its resulting enhancement of its photocatalytic degradation of chlorinated hydrocarbons. The eleventh paper, by Gao et al. [21], looks at the density functional treatment of ZnO nanowires at high pressures, converting from wurtzite to a rocksalt structure. The phase transformation should prove useful in exploring electronic, piezoelectric and photoconducting applications. Bao et al. [22] in the twelfth paper investigate the high temperature chemical transformation of orthorhombic GaOOH nanorods into wurtzite GaN nanorods, a useful compound for optical devices operating at blue and ultraviolet wavelengths and in high-temperature electronic devices.

At the other end of the scale, the development of red-emitting phosphors and field emission display devices shows great promise from the synthesis of Eu-doped Gd₂O₃ nanowires. Liu et al. [23], in the thirteenth paper, explore the use of solvothermal techniques for the formation of these doped nanomaterials, which (along with hydrothermal techniques) represents a facile approach that could be used to synthesize other rare earth oxide materials. This is demonstrated in the fourteenth paper, by Han et al. [24], in the formation of Mn-doped ZnSe nanowires and also by Yu et al. [25], in the fifteenth paper, where a review of phosphate nanowires doped with rare earth elements are considered. These composites exhibit great promise in the development of biological probes, photonic crystals and optical communication devices.

The final paper, by Yang et al. [26], looks at the fundamental correlation of magnetism with the size of Co nanowires, revealing that the magnetic property can be adjusted through changing the diameter of the nanowire. This is an important discovery for the fabrication of high-density magnetic recording devices.

The breadth of advancement of nanomaterials and their incorporation into useable products has been both extensive and intensive since their inception [27]. Whilst this special issue could not cover every aspect, it endeavours to provide exciting insight into a number of key avenues.

Acknowledgments

The editors would like to express their sincere appreciation and thanks to all the authors and coauthors for their scientific contribution to this special issue. They convey their gratitude to all the reviewers for their time and dedication.

Raymond L. D. Whitby
Steve F. A. Acquah
Renzhi Ma
Yanqiu Zhu

References

- [1] H. W. Kroto, J. R. Heath, S. C. O'Brien, R. F. Curl, and R. E. Smalley, "C-60-Buckminsterfullerene," *Nature*, vol. 318, pp. 162–163, 1985.
- [2] L. Becker, J. L. Bada, R. E. Winans, J. E. Hunt, T. E. Bunch, and B. M. French, "Fullerenes in the 1.85-billion-year-old Sudbury impact structure," *Science*, vol. 291, pp. 1530–1533, 2001.
- [3] S. Iijima, "Helical microtubules of graphitic carbon," *Nature*, vol. 354, pp. 56–58, 1991.
- [4] M. Monthieux and V. L. Kuznetsov, "Who should be given the credit for the discovery of carbon nanotubes?" *Carbon*, vol. 44, pp. 1621–1623, 2006.
- [5] A. Oberlin, M. Endo, and T. Koyama, "Filamentous growth of carbon through benzene decomposition," *Journal of Crystal Growth*, vol. 32, pp. 335–349, 1976.
- [6] L. V. Radushkevich and V. M. Lukyanovich, "O strukture ugliroda, obrazujucesja pri termiceskom razlozenii okisi ugliroda na zeleznom kontakte " About the structure of carbon formed by thermal decomposition of carbon monoxide on iron substrate," *Zhurnal Fizicheskoi Khimii*, vol. 26, pp. 88–95, 1952.
- [7] M. Reibold, P. Paufler, A. A. Levin, W. Kochmann, N. Patzke, and D. C. Meyer, "Materials-Carbon nanotubes in an ancient Damascus sabre," *Nature*, vol. 444, pp. 286–286, 2006.
- [8] S. V. Sivakumar, A. R. Mohamed, A. Z. Abdullah, and S.-P. Chai, "Role of reaction and factors of carbon nanotubes growth in chemical vapour decomposition process using Methane—a highlight," *Journal of Nanomaterials*, vol. 2010, Article ID 395191, 11 pages, 2010.
- [9] Y. Hu, T. Mei, L. Wang, and H. Qian, "A facile and generic strategy to synthesize large-scale carbon nanotubes," *Journal of Nanomaterials*, vol. 2010, Article ID 415940, 5 pages, 2010.
- [10] J. Liu, C. Guo, X. Ma, C. Sun, F. Li, and Y. Qian, "One-step route to synthesize multiwalled carbon nanotubes filled with MgO Nanorods," *Journal of Nanomaterials*, vol. 2010, Article ID 671863, 5 pages, 2010.
- [11] R. L. D. Whitby, W. K. Hsu, Y. Q. Zhu, H. W. Kroto, and D. R. M. Walton, "Novel nanoscale architectures: coated nanotubes and other nanowires," *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences*, vol. 263, pp. 2127–2142, 2004.
- [12] G. Dai, S. Yang, M. Yan et al., "Simple synthesis and growth mechanism of core/shell CdSe/SiO_x nanowires," *Journal of Nanomaterials*, vol. 2010, Article ID 427689, 6 pages, 2010.
- [13] N. Suzuki and Y. Yamauchi, "Fabrication of mesostructured silica and titania rods on substrates by using polycarbonate membranes," *Journal of Nanomaterials*, vol. 2010, Article ID 382043, 4 pages, 2010.

- [14] Y. Gan, F. Gu, D. Han, Z. Wang, and G. Guo, "Biomimetic synthesis of zinc oxide 3D architectures with gelatin as matrix," *Journal of Nanomaterials*, vol. 2010, Article ID 289173, 7 pages, 2010.
- [15] X. G. Hu and S. J. Dong, "Metal nanomaterials and carbon nanotubes - synthesis, functionalization and potential applications towards electrochemistry," *Journal of Materials Chemistry*, vol. 18, pp. 1279–1295, 2008.
- [16] Z. Ding, C. An, Q. Li et al., "Preparation of ITO nanoparticles by liquid phase coprecipitation method," *Journal of Nanomaterials*, vol. 2010, Article ID 543601, 5 pages, 2010.
- [17] D. Peng, Y. Huang, K. Yu, L. Li, and Z. Zhu, "Synthesis and field emission properties of hierarchical ZnO nanostructures," *Journal of Nanomaterials*, vol. 2010, Article ID 560409, 5 pages, 2010.
- [18] D. Ban, S. Deng, N. Xu, J. Chen, J. She, and F. Liu, "Improved field emission characteristics of large-area films of molybdenum trioxide microbelt," *Journal of Nanomaterials*, vol. 2010, Article ID 136860, 6 pages, 2010.
- [19] B. Gilbert, H. Z. Zhang, F. Huang, M. P. Finnegan, G. A. Waychunas, and J. F. Banfield, "Special phase transformation and crystal growth pathways observed in nanoparticles," *Geochemical Transactions*, vol. 4, pp. 20–27, 2003.
- [20] H.-H. Ou, S.-L. Lo, and C.-H. Liao, "Determination of Xray diffraction on the phase transformation of microwaveassisted titanate nanotubes during thermal treatment," *Journal of Nanomaterials*, vol. 2010, Article ID 837384, 5 pages, 2010.
- [21] Z. Gao, Y. Gu, and Y. Zhang, "First-principles studies on the structural transition of ZnO nanowires at high pressure," *Journal of Nanomaterials*, vol. 2010, Article ID 462032, 5 pages, 2010.
- [22] K. Bao, X. Liu, W. Mao et al., "Synthesis of GaN nanorods by a solid-state reaction," *Journal of Nanomaterials*, vol. 2010, Article ID 271051, 6 pages, 2010.
- [23] G. Liu, S. Zhang, X. Dong, and J. Wang, "Solvothermal synthesis of $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ luminescent nanowires," *Journal of Nanomaterials*, vol. 2010, Article ID 365079, 5 pages, 2010.
- [24] D. Han, C. Song, and X. Li, "Synthesis and fluorescence property of Mn-doped ZnSe nanowires," *Journal of Nanomaterials*, vol. 2010, Article ID 290763, 4 pages, 2010.
- [25] L. Yu and H. Liu, "The progress of photoluminescent properties of rare-earth-ions-doped phosphate one-dimensional nanocrystals," *Journal of Nanomaterials*, vol. 2010, Article ID 461309, 6 pages, 2010.
- [26] Y. Yang, Y. Chen, Y. Wu, X. Chen, and M. Kong, "Diameter-controllable magnetic properties of Co nanowire arrays by pulsed electrodeposition," *Journal of Nanomaterials*, vol. 2010, Article ID 793854, 4 pages, 2010.
- [27] B. Bhushan, Ed., *Springer handbook of nanotechnology*, Springer, Berlin, 2nd edition, 2007.