Review Article

Arc-Induced Long Period Fiber Gratings

Gaspar Rego^{1,2}

¹*Instituto Politécnico de Viana do Castelo, Escola Superior de Tecnologia e Gestão, Avenida do Atlântico, 4900-348 Viana do Castelo, Portugal*

²*Center for Applied Photonics (CAP), INESC TEC (Formerly Known as UOSE, INESC-Porto), Rua do Campo Alegre 687, 4169-007 Porto, Portugal*

Correspondence should be addressed to Gaspar Rego; gmrego@fc.up.pt

Received 28 October 2015; Revised 22 December 2015; Accepted 31 December 2015

Academic Editor: Stefania Campopiano

Copyright © 2016 Gaspar Rego. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Long period fiber gratings produced by the electric arc technique have found an increasing interest by the scientific community due to their ease to fabricate, virtually enabling the inscription in any kind of fiber, low cost, and flexibility. In 2005 we have presented the first review on this subject. Since then, important achievements have been reached such as the identification of the mechanisms responsible for gratings formation, the type of symmetry, the conditions to increase fabrication reproducibility, and their inscription in the turning points with grating periods below 200 μm . Several interesting applications in the sensing area, including those sensors working in reflection, have been demonstrated and others are expected, namely, related to the monitoring of extreme temperatures, cryogenic and high temperatures, and high sensitivity refractometric sensors resulting from combining arc-induced gratings in the turning points and the deposition of thin films in the transition region. Therefore, due to its pertinence, in this paper we review the main achievements obtained concerning arc-induced long period fiber gratings, with special focus on the past ten years.

1. Introduction

The concept of long period fiber gratings (LPFGs) was introduced in 1996 by Vengsarkar et al. in which a periodic modulation of the core refractive index was induced by UV laser radiation [1]. Since the grating periodicity is of the order of hundreds of micrometers several techniques have been used for LPFGs fabrication not only through exposure to UV, CO₂, and IR femtosecond laser radiation [1–3] but also based on ion beam implantation, etching, mechanical arrangements, acoustic waves, broadband UV light, and electric arc discharges [4, 5]. Among the different available techniques the electric arc has paved its way during the past two decades since it is a simple, flexible, and low cost technique that enables the writing of gratings in all kinds of fibers. Furthermore, as is the case for CO₂ and IR femtosecond laser radiation, the arc discharge technique also overcomes several limitations of the technique based on UV laser radiation [6] and enables the fabrication of several optical fiber components [7]. In fact, based on the number of publications, arc-induced gratings compares well with those fabricated by using laser radiation. Presently, and apart from

Africa, it is a technique spread all over the world (see Figure 1; there are also some traces of research activity in Turkey and Iraq). More than two-tenths of research groups, by their own or in consortiums, have been studying LPFGs produced by the electric arc technique (in Figure 1 the flags dimensions are proportional to the number of publications in international journals and conferences) resulting in more than 250 papers. INESC TEC, in Portugal, accounts for about 40% of the publications (see Figure 2). It can be said that the fabrication of LPFGs started in 1994 by Poole et al. where they have used a two-step process involving ablation of the fiber cladding by CO₂ radiation followed by annealing through arc discharges [8]. LPFGs based solely on arc discharges are due to Dianov et al. in 1997 [9]. In the following years a scarce number of publications were registered and despite the peak in 1998, the take-off occurred in 2001 by Rego et al. [6] followed by Humbert and Malki [10] that led to an increasing interest until 2007, also with important contributions from research groups in Japan [11], UK [12], and Brazil [13]. From 2008 up to 2012 there was a decrease in the number of publications despite the contribution of research groups from Mexico [14] and Canada/Poland [15]. In the past three years we have been

FIGURE 1: Worldwide research on arc-induced gratings.

FIGURE 2: Publications concerning arc-induced gratings in international journals and conferences.

climbing the technique's notoriety with growing interest in Asia, namely, in Malaysia [5].

In the early days, publications were essentially related to the fabrication in different kinds of fibers, the study of the gratings properties, and the discussion of the mechanisms of formation, being those issues reviewed in 2005 [4]. In the last decade we registered the consolidation of the knowledge concerning the formation mechanisms, the improvement of the reproducibility of the technique, the implementation of several sensors, namely, for the simultaneous measurement of temperature and strain, the development of refractometric sensors based on coated LPFGs and, more recently, to the inscription of arc-induced gratings in the turning points. At these points, the slope of the phase matching curves, for each cladding mode resonance, reaches its maximum value. On the other hand, near the turning points the slope steeply

increases and changes from positive to negative and, for each grating period, there are two resonance wavelengths for each cladding mode. These are the regions where LPFGs show the highest sensitivities [16]. Therefore, by properly addressing issues related to the reproducibility of the technique associated with electrodes degradation and environmental parameters that impact the optimum arc discharge conditions and also the required LPFG engineering development associated with their intrinsic cross sensitivities to other physical parameters such as temperature, strain, and bending, it is expected that arc-induced gratings continue their worldwide spreading leading, in the near future, to commercial devices in the sensing area.

In the following sections, we begin by reviewing the underlying mechanisms of arc-induced gratings formation. Afterwards, the fabrication of long period fiber gratings, in particular, in the turning points is discussed. The main properties of LPFGs, which include the thermal behavior and the dependence on the external refractive index, are also presented. Finally, we analyze three important applications in the sensing area, namely, the simultaneous measurement of temperature and strain, flow measurement, and refractometric sensors.

2. Mechanisms of Gratings Formation

A long period fiber grating is a wavelength selective filter whose transmission spectra exhibit several resonances resulting from coupling between the core mode and the different copropagating cladding modes at wavelengths that obey the resonance condition [1]: $\lambda_{\text{res}} = (n_{\text{co}}^{\text{eff}} - n_{\text{cl},m}^{\text{eff}})\Lambda$, where λ_{res} represents the resonance wavelengths, Λ represents the grating period, and $n_{\text{co}}^{\text{eff}}$ and $n_{\text{cl},m}^{\text{eff}}$ represent the effective

FIGURE 3: (a) Temperature profile in the fiber during the arc discharge and (b) and its time dependence (it corresponds to a 50 μm Pt/Rh thermocouple inserted in a 56/125 μm silica capillary) [23].

refractive index of the core mode and the effective refractive index of the cladding modes, respectively. The theoretical equations governing the intrinsic properties of LPFGs, such as, transmission loss and resonance wavelengths or their temperature and external refractive index dependence, can be found elsewhere [5, 17–20]. For almost two decades that the underlying mechanisms of arc-induced gratings are under debate and in this context the estimation of the temperature reached by the fiber during an arc discharge allowed a proper discussion on the mechanisms responsible for their formation [21–23]. Figure 3 shows that for the typical fabrication parameters used, namely, electric current and time of the arc discharge, the fiber reaches a peak temperature of about 1400°C in less than half a second (estimated from Figure 3(b)) [23]. The latter result is also important in order to limit heat diffusion along the fiber since it prevents the use of short grating periods, due to overlap of the effects caused by the adjacent arc discharges.

Several works have been published focused on stress and refractive index profile measurements [24–28]. The main conclusions are that the arc discharge (considering typical fabrication parameters) relaxes intrinsic stresses in the fiber core and cladding but in regions that are larger than the grating period being, therefore, the refractive index modulation not enough to explain the grating formation. On the other hand, an increase of the refractive index of the cladding and a decrease of the core-cladding difference were observed which impacts the position of the resonance wavelengths. The conclusions concerning the core region are not so straightforward and results may depend on the fiber and also on the fabrication conditions. In 2006, it was demonstrated through simulation and by measuring the near field intensity distributions that depending on the fiber, LPFGs could couple to cladding modes of different symmetries [29]. Further studies revealed that the arc discharge is directional, possessing a temperature gradient that induces asymmetric

microdeformations in the fiber [30]. These microdeformations can account for the formation of the gratings and, simultaneously, the average reduction of the fiber cross section also leads to a displacement towards shorter wavelengths of the resonances (see Figure 4(a)). It should be stressed that five years earlier the periodic modulation of the fiber was already pointed out as a potential origin of LPFGs formation [31, 32], although in the case of a symmetric perturbation it would require a severe deformation of the fiber cross section ($\sim 17\%$) in order to obtain strong gratings [17]. Therefore, both changes, the geometrical and the refractive indices, caused by the arc, need to be taken into account for the correct simulation of arc-induced gratings (see Figure 4(b)).

In the case of the B/Ge codoped fibers typical cladding modes are symmetric (Figure 5(a)), unless the fiber is placed under tension in a region of the arc with lower average temperature and higher temperature gradient (which is also an optimum point to increase the reproducibility of the technique) where, with optimized fabrication parameters, gratings with different symmetries are written simultaneously [33]. In Figure 5(b), the resonances at shorter wavelengths belong to asymmetric cladding modes whilst the others are due to coupling to symmetric cladding modes, in accordance with the simulations. Moreover, the latter modes vanish at higher temperatures, so they are not a consequence of permanent geometrical changes. These superimposed gratings showing a dual set of resonances results from two different mechanisms: microdeformations and densification [34].

In the case of pure silica-core fibers it was also demonstrated that microdeformations can be responsible for the formation of the gratings [35]. During these investigations the knowledge regarding mechanically induced LPFGs was very important for the sake of comparison between both types of gratings [36]. Figure 6 shows the dispersion curves for symmetric and asymmetric modes being the latter at shorter wavelengths in accordance with the theory. For our particular

FIGURE 4: (a) Resonance wavelengths as a function of the geometric modulation and (b) transmission spectrum of an asymmetric 540 μm LPFG induced in the SMF28 fiber: experimental (solid line) and simulation (dashed line) [32].

FIGURE 5: (a) Spectrum of a symmetric 415 μm LPFG induced in the B/Ge codoped fiber using an external tension of 5.1 g and 60 discharges with 8.5 mA and 0.5 s; (b) spectrum of a 540 μm grating with a dual set of resonances inscribed simultaneously in the B/Ge codoped fiber after downshifting $\sim 20 \mu\text{m}$ the fiber relatively to the arc and using an external tension of 23 g and 60 discharges of 9 mA and 0.5 s [33].

setup, where the arc discharge is directional, and considering Ge-doped fibers such as the SMF28 from Corning, coupling occurs for asymmetric cladding modes. The comparison between arc-induced and mechanical-induced gratings (MLPFGs) is presented in Figure 7. It can be observed that the resonances of arc-induced gratings are located at shorter wavelengths, which can be attributed to the changes caused by the arc in terms of a reduction of the average core diameter and also due to annealing of intrinsic stresses that lead to a change of the refractive index of the core and cladding regions, as discussed previously. As far as the inscription of LPFGs in photonic crystal fibers is concerned this topic is discussed, for instance, in [11, 37].

3. Fabrication and Characterization of Arc-Induced LPFGs

Generally speaking, arc-induced gratings are fabricated by placing an uncoated fiber, under tension, between the electrodes of a splicing machine [6], being it then submitted to an arc discharge with an electric current of 7 to 15 mA and a duration ranging from 200 ms up to 2 s. Afterwards the fiber is displaced by the grating period, typically from 400 μm to 700 μm , and the whole process arc discharge/fiber displacement is repeated 20 to 50 times. Along the years several modifications to the set-up were implemented, in part, to increase the reproducibility [17, 30]. Other improvements

FIGURE 6: Resonant wavelength versus grating period for the lowest cladding modes. The experimental data was fitted considering both types of perturbations: symmetric and asymmetric [17].

FIGURE 7: Resonance wavelengths, corresponding to coupling to asymmetric cladding modes, as a function of the grating period [36].

were also claimed by other researchers through modification of commercial fiber splicers [15, 38–43] or by developing their own high voltage power supply [31, 32, 44–46]. All advancements led us to a compactness, flexible and reproducible technique that enables the fabrication, virtually in all kinds of fibers, of low loss LPFGs with considerable short grating periods. However, as far as high sensitivity LPFGs based sensors are concerned, it was necessary to inscribe LPFGs in the turning points and this goal was reached in the last couple of years, first by Smietana et al. [47, 48] by writing LPFGs below $200\ \mu\text{m}$ in B/Ge codoped fibers and later by Colaço et al. [49] that were able to inscribe LPFGs below $200\ \mu\text{m}$ in the SMF28e fiber and below $150\ \mu\text{m}$ in the 1250/1550 B/Ge

FIGURE 8: Experimental set-up (mechanical arrangement and high voltage power supply) used to fabricate arc-induced gratings in the turning points.

codoped fiber, establishing a new record for the shortest grating period achieved for arc-induced gratings. This goal resulted from the development of a dedicated high voltage power supply (see Figure 8).

Figure 9 shows the spectra of gratings arc-induced in the SMF28e fiber and also in the B/Ge codoped fiber. The fabrication parameters were set as electric current of 12.7 mA, 600 ms arc duration, 2 g pulling weight, and 400 arc discharges, for the SMF28e fiber. It should be stressed that we are working in the limits of the electric arc technique since it was only possible to write a weak grating even after 400 arc discharges. Even so, this result is quite impressive since previously in this fiber the shortest period was larger than $300\ \mu\text{m}$ [15]. For the grating inscribed in the Fibercore fiber we used the following fabrication parameters: electric current of 13.8 mA, 308 ms arc duration, 2 g pulling weight, and 142 arc discharges. Note, however, that we have also produced gratings ($\Lambda = 180\ \mu\text{m}$) in this fiber with resonance strength of about 20 dB by applying only 122 arc discharges (see Figure 10).

LPFGs have been arc-induced in different types of fibers including Ge-free fibers [24, 50, 51], photonic crystal fibers [52–58], flat cladding fibers [59], and cladding-etched fibers [14, 60, 61] and in adiabatic tapers [62]. Modifications to the technique include applying no tension, applying compression, or even pressurizing the hollow core fibers during the arc discharges [5, 19, 55, 63]. LPFGs have been produced with random period [64], superimposed with different periods [65] or with phase-shifts resulting from changing the fabrication parameters during their inscription [66]. In B/Ge codoped fibers the choice of the fabrication parameters also allowed fabricating simultaneously LPFGs with different symmetry [33].

Arc-induced LPFGs have been characterized as a function of the variation of physical parameters such as strain and temperature [40, 66–72], bending and torsion [73], pressure [74, 75], and external refractive index [76–86]. They were also exposed to gamma radiation [51]. The polarization dependence loss was also investigated [87] and the results demonstrate why they have a minute success in optical communications. As far as sensing is concerned three important characterizations were performed. First, one of the major potential applications of arc-induced gratings

FIGURE 9: Transmission spectra of LPFGs near the turning points, inscribed in the (a) SMF28 fiber, (b) B/Ge codoped fiber [49].

FIGURE 10: Transmission spectra of a 180 μm -LPFGs inscribed in the B/Ge codoped fiber.

FIGURE 11: Evolution of the grating spectrum during the heat treatment at 1000°C for 12 days [68].

results from their ability to resist to high temperatures as was demonstrated by the fact that they survived at temperatures of 1000°C for about two weeks (see Figure 11). Further improvements are nevertheless expected by isolating the grating from external environment (to prevent in-diffusion of oxygen at high temperatures) and avoiding the use of unwanted external pulling tensions. This can be reached by inserting the grating into a silica capillary [68].

On the other hand, it was recently demonstrated that arc-induced gratings are also good candidates to perform at cryogenic temperatures [72]. A phase-shifted LPFG, working in reflection, was produced by polishing the fiber after cutting it at a distance from the grating of about a quarter of the period (Figure 12(a)). As can be observed in Figure 12(b), the temperature sensitivity obtained in the 4 K–30 K range

is considerably higher than for other approaches such as embedded FBGs. Currently, further research is ongoing in order to improve their sensitivity and reproducibility.

Another intrinsic property of LPFGs is their dependence on the external refractive index which affects the effective refractive index of the cladding modes and, therefore, in particular, changes their resonance wavelengths [18]. The gratings sensitivity depends on the order of the cladding modes and reaches its maximum close to the so-called turning points. In these regions the slope of the phase matching curves changes from positive to negative, and for each grating period, there are two resonance wavelengths for each cladding mode. This is due to the dependence on wavelength of the core and cladding effective refractive indices. For

FIGURE 12: (a) Reflection spectrum of the phase-shifted LPFG at room temperature; (b) wavelength of the two Dips and the Peak of the phase-shifted LPFG working in reflection, inscribed in the B/Ge codoped fiber, as a function of temperature [72].

a particular grating period, the phase matching condition can be satisfied for more than one resonance wavelength since as the wavelength increases the effective refractive index of the cladding mode decreases faster than that of the core [88]. An arc-induced inscribed in the B/Ge codoped fiber in the turning points was characterized as a function of water-glycol mixtures and a sensitivity of about 1000 nm/RIU was obtained by considering the shift of the resonance at shorter wavelengths (Figure 13). Further improvements are expected as will be discussed in the next section.

4. Applications of Arc-Induced Gratings

LPFGs find application in optical communications and sensing areas. However, as far as arc-induced gratings are concerned only few works related to optical communications have been published, namely, those related to their performance as filters in optical sources and in the equalization of optical fiber amplifiers [39, 89–92]. The reason may lay in the fact they are intrinsically polarization dependent [87], therefore, impacting negatively in communication systems. A way to mitigate this issue would be the fabrication of helical arc-induced gratings, since, as demonstrated for LPFGs fabricated by CO₂ laser radiation, they exhibit low polarization dependent loss (PDL) [93–95]. Clearly this topic requires further study and, therefore, in this section we shall present only applications in the sensing area. In this field a diversity of applications have been published, namely, related to the measurement of physical parameters, such as temperature and strain [66, 96, 97], displacement [98], bending [99–102], torsion [73], or pressure [103, 104]. An important achievement related to arc-induced gratings is

FIGURE 13: Transmission spectra as a function of the external refractive index for a LPFGs in the turning points, inscribed in the B/Ge codoped fiber ($\Lambda = 192 \mu\text{m}$) [49].

concerned with the demonstration that by changing the fabrication parameters not only the resonance wavelengths change but also their sensitivity to physical parameters are modified. Based on that, a sensor for the simultaneous measurement of temperature and strain was implemented by changing the fabrication parameters during the grating inscription, that is, for the first 15 discharges, an external tension of 22.8 g and a current of 9 mA during 1 s were used followed by 40 discharges using an external tension of 1.2 g

FIGURE 14: Evolution of the grating spectrum during the fabrication process: (dash line) normal grating spectrum obtained after 15 arc discharges; (solid line) phase-shifted grating obtained after 40 more arc discharges but with different fabrication parameters [66].

FIGURE 15: Sensor head used for air flow measurement [106].

and an electric current of 11 mA during 1 s. This resulted in a phase-shifted grating in which two neighbor resonances, in the third telecommunication window, exhibited different sensitivities to temperature and strain [66]. Figure 14 shows the evolution of the grating spectrum during the fabrication process, where the fabrication parameters used are also presented.

Other more unusual applications include sensors performing as inclinometers [105] and flowmeters [106]; they have been used for the determination of metal thermal conductivity [107] and oxidation [108] and also to follow reactive ion etching processes [109]. The optical flowmeter [106] is a particular interesting application that comprises the use of an LPFG, a FBG, and a metallic thin film. Figure 15 shows the sensing head used to measure the air flow. The LPFG couples light to the cladding at a wavelength that is absorbed by the metallic film in which, being in the FBG region, its resonance shifts towards longer wavelengths due to the heating process. Afterwards, the air flow removes the heat from the film at a rate that depends on the air velocity and that translates into the movement of the FBG signature. Topics concerning interrogation techniques are discussed in [110–115].

LPFGs are intrinsically sensitive to changes of the external refractive index and, therefore, they are used as refractometers [14, 18, 47, 48, 61, 65, 81, 116–151]. As discussed in [18] standard arc-induced LPFGs are limited to resolutions of about 10^{-3} in changes of the refractive index and, therefore, several techniques such as tapering, etching, and bending or by implementing interferometric configurations have been applied in order to improve their resolution. Another limitation is related to the value of the ambient refractive index to be monitored since the sensitivity increases as it approaches the cladding refractive index but, in general, one works with aqueous solutions with a refractive index around 1.33. Moreover, the resonance wavelengths do not change for external medium with a refractive index above that of the cladding. These constraints can be overcome by using thin films and recently several applications based on coated arc-induced LPFGs have been proposed [123–134]. Some examples include monitoring the quality of fried oils [125] and olive oil [126], measure humidity [127], CO_2 [131], or detect the presence of *E. coli* [132]. Figure 16 exemplifies the use of titanium dioxide coatings in order to be able to detect changes in olive oil which possesses a refractive index above that of the cladding.

FIGURE 16: LPFG coated with a TiO_2 thin film [126].

Another recent milestone was the possibility to arc-induce gratings in the turning points [47, 48] with periods as short as $148\ \mu\text{m}$ [49]. Therefore, and despite the fact that cross sensitivity issues need to be properly addressed, the combination of strong arc-induced gratings in the vicinity of the turning points coated with thin films in the transition region opens the possibility of reaching resolutions of the order of 10^{-6} [135]. Furthermore, it was demonstrated that the initial coupling strength of the grating is determinant in order to avoid the fading out of the resonance in the transition region [136]. Recently, Del Villar also demonstrated that additionally to the previous methods, the etching of the fiber cladding can be used to further increase the sensitivity of the gratings reaching potential sensitivities of the order of $1.4 \times 10^5\ \text{nm/RIU}$ [137]. Smietana et al. demonstrated the possibility of tuning the characteristics of LPFGs coated with diamond-like carbon nano-layers by using reactive ion etching [138, 139]. Finally, it should be stressed that these gratings can work in reflection configuration [72]. Thus, we have now all means to produce high sensitivity optical refractometers based on coated arc-induced gratings.

5. Conclusions

In this paper we review the issues related to arc-induced gratings, addressing both the research groups that are working worldwide with the technology and their main achievements. In particular, we highlighted the issues concerning the reproducibility of the technique, the mechanisms of gratings formation, and the possibility of inscribing LPFGs in the turning points. We are now in the presence of a technology with a degree of development that enables the fabrication, at a reduced cost, of high sensitivity refractometric sensors and also temperature sensors for extreme environments, namely, to perform at cryogenic and high temperatures. On the other hand, the mass production of sensors based on arc-induced gratings will require the control of the environment where the discharges occur, in order to prevent or mitigate electrodes degradation, and the intrinsic gratings cross sensitivity to

other physical parameters also demands for some product engineering attention.

Conflict of Interests

The author declares that there is no conflict of interests regarding the publication of this paper.

Acknowledgments

This work is financed by the ERDF, European Regional Development Fund, through the Operational Programme for Competitiveness and Internationalisation, COMPETE 2020 Programme, and by National Funds through the FCT, Fundação para a Ciência e a Tecnologia (Portuguese Foundation for Science and Technology) within Project “POCI-01-0145-FEDER-006961.” The author would like to thank O. Ivanov, P. Caldas, C. Colaço, and J. L. Santos for their contribution and valuable comments. The author also would like to thank L. Coelho for supplying Figure 16.

References

- [1] A. M. Vengsarkar, P. J. Lemaire, J. B. Judkins, V. Bhatia, T. Erdogan, and J. E. Sipe, “Long-period fiber gratings as band-rejection filters,” *Journal of Lightwave Technology*, vol. 14, no. 1, pp. 58–64, 1996.
- [2] J. M. P. Coelho, C. Silva, M. Nespereira, M. Abreu, and J. Rebordão, “Writing of long period fiber gratings using CO_2 laser radiation,” in *Advances in Optical Fiber Technology: Fundamental Optical Phenomena and Applications*, chapter 9, pp. 287–314, InTech, Rijeka, Croatia, 2015.
- [3] F. Ahmed, H.-E. Joe, B.-K. Min, and M. B. G. Jun, “Characterization of refractive index change and fabrication of long period gratings in pure silica fiber by femtosecond laser radiation,” *Optics & Laser Technology*, vol. 74, pp. 119–124, 2015.
- [4] G. Rego, P. V. S. Marques, J. L. Santos, and H. M. Salgado, “Arc-induced long-period gratings,” *Fiber and Integrated Optics*, vol. 24, no. 3-4, pp. 245–259, 2005.

- [5] S.-Y. Tan, Y.-T. Yong, S.-C. Lee, and F. Abd Rahman, "Review on an arc-induced long-period fiber grating and its sensor applications," *Journal of Electromagnetic Waves and Applications*, vol. 29, no. 6, pp. 703–726, 2015.
- [6] G. Rego, O. Okhotnikov, E. Dianov, and V. Sulimov, "High temperature stability of long-period fiber gratings produced using an electric arc," *Journal of Lightwave Technology*, vol. 19, no. 10, pp. 1574–1579, 2001.
- [7] G. Rego, "Review paper: fibre optic devices produced by arc discharges," *Journal of Optics*, vol. 12, no. 11, Article ID 113002, 2010.
- [8] C. D. Poole, H. M. Presby, and J. P. Meester, "Two-mode fibre spatial-mode converter using periodic core deformation," *Electronics Letters*, vol. 30, no. 17, pp. 1437–1438, 1994.
- [9] E. M. Dianov, V. I. Karpov, M. V. Grekov et al., "Thermo-induced long-period fibre gratings," in *Proceedings of the 23rd European Conference on Optical Communications (ECOC '97)*, pp. 53–56, Edinburgh, UK, September 1997.
- [10] G. Humbert and A. Malki, "Electric-arc-induced gratings in non-hydrogenated fibres: fabrication and high-temperature characterizations," *Journal of Optics A: Pure and Applied Optics*, vol. 4, no. 2, pp. 194–198, 2002.
- [11] K. Morishita and Y. Miyake, "Fabrication and resonance wavelengths of long-period gratings written in a pure-silica photonic crystal fiber by the glass structure change," *Journal of Lightwave Technology*, vol. 22, no. 2, pp. 625–630, 2004.
- [12] H. Dobb, K. Kalli, and D. J. Webb, "Temperature-insensitive long period grating sensors in photonic crystal fibre," *Electronics Letters*, vol. 40, no. 11, pp. 657–658, 2004.
- [13] R. Falate, R. C. Kamikawachi, M. Müller, H. J. Kalinowski, and J. L. Fabris, "Fiber optic sensors for hydrocarbon detection," *Sensors and Actuators B: Chemical*, vol. 105, no. 2, pp. 430–436, 2005.
- [14] A. Martinez-Rios, D. Monzon-Hernandez, and I. Torres-Gomez, "Highly sensitive cladding-etched arc-induced long-period fiber gratings for refractive index sensing," *Optics Communications*, vol. 283, no. 6, pp. 958–962, 2010.
- [15] M. Smietana, W. J. Bock, P. Mikulic, and J. Chen, "Increasing sensitivity of arc-induced long-period gratings—pushing the fabrication technique toward its limits," *Measurement Science and Technology*, vol. 22, no. 1, Article ID 015201, 2011.
- [16] X. Shu, L. Zhang, and I. Bennion, "Sensitivity characteristics of long-period fiber gratings," *Journal of Lightwave Technology*, vol. 20, no. 2, pp. 255–266, 2002.
- [17] G. Rego, *Arc-induced long-period fibre gratings: fabrication and their applications in optical communications and sensing [Ph.D. thesis]*, University of Porto, Porto, Portugal, 2006.
- [18] G. Rego, "A review of refractometric sensors based on long period fibre gratings," *The Scientific World Journal*, vol. 2013, Article ID 913418, 14 pages, 2013.
- [19] J. M. Estudillo-Ayala, R. I. Mata-Chávez, J. C. Hernández-García, and R. Rojas-Laguna, "Long period fiber grating produced by arc discharges," in *Fiber Optic Sensors*, chapter 12, pp. 295–316, InTech, Rijeka, Croatia, 2012.
- [20] P. S. André, R. A. Sá Ferreira, C. M. L. Correia, H. Kalinowshy, X. Xiang-Jun, and J. L. Pinto, "Demodulating the response of optical fibre long-period gratings: genetic algorithm approach," *Chinese Physics Letters*, vol. 23, no. 9, pp. 2480–2482, 2006.
- [21] G. Rego, L. M. N. B. F. Santos, B. Schröder, P. V. S. Marques, J. L. Santos, and H. M. Salgado, "In situ temperature measurement of an optical fiber submitted to electric arc discharges," *IEEE Photonics Technology Letters*, vol. 16, no. 9, pp. 2111–2113, 2004.
- [22] G. M. Rego, P. V. S. Marques, J. L. Santos, and H. M. Salgado, "Estimation of the fibre temperature during the inscription of arc-induced long-period gratings," *Optics Communications*, vol. 259, no. 2, pp. 620–625, 2006.
- [23] G. Rego, L. M. N. B. F. Santos, and B. Schröder, "Estimation of the fibre temperature during an Arc-discharge," *Microwave and Optical Technology Letters*, vol. 50, no. 8, pp. 2020–2025, 2008.
- [24] F. Dürr, G. Rego, P. V. S. Marques et al., "Tomographic stress profiling of arc-induced long-period fiber gratings," *Journal of Lightwave Technology*, vol. 23, no. 11, pp. 3947–3953, 2005.
- [25] G. Rego, F. Dürr, P. V. S. Marques, and H. G. Limberger, "Strong asymmetric stresses arc-induced in pre-annealed nitrogen-doped fibres," *Electronics Letters*, vol. 42, no. 6, pp. 334–335, 2006.
- [26] B. Sévigny, M. Leduc, M. Faucher, N. Godbout, and S. Lacroix, "Characterization of the large index modification caused by electrical discharge in optical fibers," in *Proceedings of the Conference on Lasers and Electro-Optics (CLEO '07)*, pp. 1–2, IEEE, Baltimore, Md, USA, May 2007.
- [27] F. Abrishamian, N. Dragomir, and K. Morishita, "Refractive index profile changes caused by arc discharge in long-period fiber gratings fabricated by a point-by-point method," *Applied Optics*, vol. 51, no. 34, pp. 8271–8276, 2012.
- [28] G. Rego, J. C. C. Carvalho, P. V. S. Marques, A. Fernandez Fernandez, F. Dürr, and H. G. Limberger, "Stress profiling of arc-induced long-period gratings written in pure-silica-core fibers," in *17th International Conference on Optical Fibre Sensors*, vol. 5855 of *Proceedings of SPIE*, pp. 884–887, Bruges, Belgium, August 2005.
- [29] C. Rego, O. V. Ivanov, and P. V. S. Marques, "Demonstration of coupling to symmetric and antisymmetric cladding modes in arc-induced long-period fiber gratings," *Optics Express*, vol. 14, no. 21, pp. 9594–9599, 2006.
- [30] O. V. Ivanov and G. Rego, "Origin of coupling to antisymmetric modes in arc-induced long-period fiber gratings," *Optics Express*, vol. 15, no. 21, pp. 13936–13941, 2007.
- [31] C. Chung and H. Lee, "Wavelength characteristics of arc-induced long-period fiber grating by core and cladding diameter modulation," in *Proceedings of the 14th Annual Meeting of the IEEE Lasers and Electro-Optics Society (LEOS '01)*, vol. 2, pp. 778–779, San Diego, Calif, USA, November 2001.
- [32] M. W. Kim, D. W. Lee, B. I. Hong, and H. Y. Chung, "Performance characteristics of long-period fiber-gratings made from periodic tapers induced by electric-arc discharge," *Journal of the Korean Physical Society*, vol. 40, no. 2, pp. 369–373, 2002.
- [33] G. Rego and O. V. Ivanov, "Two types of resonances in long-period gratings induced by arc discharges in boron/germanium co-doped fibers," *Optics Letters*, vol. 32, no. 20, pp. 2984–2986, 2007.
- [34] V. Grubsky and J. Feinberg, "Rewritable densification gratings in boron-doped fibers," *Optics Letters*, vol. 30, no. 11, pp. 1279–1281, 2005.
- [35] G. Rego and O. Ivanov, "Investigation of the mechanisms of formation of long-period gratings arc-induced in pure-silica-core fibres," *Optics Communications*, vol. 284, no. 8, pp. 2137–2140, 2011.
- [36] G. Rego, "Long-period fiber gratings mechanically induced by winding a string around a fiber/grooved tube set," *Microwave and Optical Technology Letters*, vol. 50, no. 8, pp. 2064–2068, 2008.
- [37] J. S. Petrović, D. J. Webb, V. Mezentssev, H. Dobb, K. Kalli, and I. Bennion, "Nondestructive index profiling of long period

- gratings in photonic crystal fibres,” *Optical and Quantum Electronics*, vol. 38, no. 9, pp. 913–920, 2006.
- [38] S. H. Nam, C. Zhan, J. Lee et al., “Bend-insensitive ultra short long-period gratings by the electric arc method and their applications to harsh environment sensing and communication,” *Optics Express*, vol. 13, no. 3, pp. 731–737, 2005.
- [39] I. Cacciari, M. Brenici, R. Falciai, G. Nunzi Conti, S. Pelli, and G. C. Righini, “Reproducibility of splicer-based long-period fiber gratings for gain equalization,” *Optoelectronics Letters*, vol. 3, no. 3, pp. 203–206, 2007.
- [40] M. Smietana, W. J. Bock, and P. Mikulic, “Comparative study of long-period gratings written in a boron co-doped fiber by an electric arc and UV irradiation,” *Measurement Science and Technology*, vol. 21, no. 2, Article ID 025309, 2010.
- [41] L. A. García-de-la-Rosa, I. Torres-Gómez, A. Martínez-Ríos, D. Monzón-Hernández, and J. Reyes-Gómez, “Background loss minimization in arc-induced long-period fiber gratings,” *Optical Engineering*, vol. 49, no. 6, Article ID 065001, 2010.
- [42] G. Yin, Y. Wang, C. Liao et al., “Long period fiber gratings inscribed by periodically tapering a fiber,” *IEEE Photonics Technology Letters*, vol. 26, no. 7, pp. 698–701, 2014.
- [43] G. Yin, Y. Wang, C. Liao et al., “Improved arc discharge technique for inscribing compact long period fiber gratings,” in *23rd International Conference on Optical Fiber Sensors, 91577X1*, vol. 9157 of *Proceedings of SPIE*, June 2014.
- [44] S. In, C. Chung, and H. Lee, “The resonance wavelength-tuning characteristic of the arc-induced LPFGs by diameter modulation,” in *Proceedings of the 15th International Conference on Optical Fiber Sensors*, vol. 1, pp. 131–134, IEEE, Portland, Ore, USA, May 2002.
- [45] S. C. Lee, Y. T. Yong, K. H. Yeap, and F. A. Rahman, “An asymmetric tapered long period fiber grating: fabrication and characterization,” in *Proceedings of the IEEE 4th International Conference on Photonics (ICP '13)*, pp. 21–24, Melaka, Malaysia, October 2013.
- [46] M. P. Cho, H. S. Lin, Y. T. Yong, Y. N. Phua, T. K. Yong, and F. A. Rahman, “Characterisation of continuous arc discharge system as a fusion heat source for fused fiber components,” in *Proceedings of the 4th Annual IEEE International Conference on Cyber Technology in Automation, Control, and Intelligent Systems (IEEE-CYBER '14)*, pp. 270–273, IEEE, Hong Kong, June 2014.
- [47] M. Smietana, A. K. Debowska, P. Mikulic, and W. J. Bock, “Refractive index sensing with high temperature nano-coated electric arc-induced long-period gratings working at dispersion turning point,” in *Proceedings of the 18th Microoptics Conference (MOC '13)*, pp. 1–2, Tokyo, Japan, October 2013.
- [48] A. K. Debowska, M. Smietana, P. Mikulic, and W. J. Bock, “High temperature nano-coated electric-arc-induced long-period gratings working at the dispersion turning point for refractive index sensing,” *Japanese Journal of Applied Physics*, vol. 53, no. 8, Article ID 08ME01, 2014.
- [49] C. Colaço, P. Caldas, R. Chibante, and G. Rego, “Arc-induced gratings in the turning points,” in *24th International Conference on Optical Fibre Sensors*, vol. 9634 of *Proceedings of SPIE*, Curitiba, Brazil, September 2015.
- [50] G. Rego, R. Falate, J. L. Santos et al., “Arc-induced long-period gratings in aluminosilicate glass fibers,” *Optics Letters*, vol. 30, no. 16, pp. 2065–2067, 2005.
- [51] G. Rego, A. Fernandez Fernandez, A. Gusarov et al., “Effect of ionizing radiation on the properties of arc-induced long-period fiber gratings,” *Applied Optics*, vol. 44, no. 29, pp. 6258–6263, 2005.
- [52] H. Dobb, K. Kalli, and D. J. Webb, “Measured sensitivity of arc-induced long-period grating sensors in photonic crystal fibre,” *Optics Communications*, vol. 260, no. 1, pp. 184–191, 2006.
- [53] J. S. Petrovic, H. Dobb, V. K. Mezentsev, K. Kalli, D. J. Webb, and I. Bennion, “Sensitivity of LPGs in PCFs fabricated by an electric arc to temperature, strain, and external refractive index,” *Journal of Lightwave Technology*, vol. 25, no. 5, pp. 1306–1312, 2007.
- [54] S. Kim, G. H. Kim, K.-J. Hwang et al., “Investigation of an arc-induced long period fiber grating inscribed in a photonic crystal fiber with two large air holes,” *Journal of the Optical Society of Korea*, vol. 13, no. 4, pp. 428–433, 2009.
- [55] A. Iadicicco, S. Campopiano, and A. Cusano, “Long-period gratings in hollow core fibers by pressure-assisted arc discharge technique,” *IEEE Photonics Technology Letters*, vol. 23, no. 21, pp. 1567–1569, 2011.
- [56] A. Iadicicco, R. Ranjan, and S. Campopiano, “Fabrication and characterization of long-period gratings in hollow core fibers by electric arc discharge,” *IEEE Sensors Journal*, vol. 15, no. 5, pp. 3014–3020, 2015.
- [57] T. B. Iredale, P. Steinvurzel, and B. J. Eggleton, “Electric-arc-induced long-period gratings in fluid-filled photonic bandgap fibre,” *Electronics Letters*, vol. 42, no. 13, pp. 739–740, 2006.
- [58] W.-B. Huang, L.-W. Liu, Y.-L. Wang, W.-F. Liu, and C.-L. Lee, “Dispersion control in liquid core arc-induced long-period fiber gratings,” in *Proceedings of the 15th OptoElectronics and Communications Conference (OECC '10) Technical Digest*, pp. 655–657, Sapporo, Japan, July 2010.
- [59] Z.-Z. Zheng, C.-M. Li, C.-L. Lee, and J.-S. Horng, “Arc-induced long period fiber gratings based on flat-clad fibers,” in *Proceedings of the Progress in Electromagnetics Research Symposium (PIERS '13)*, pp. 525–527, Taipei, Taiwan, March 2013.
- [60] M. Z. R. M. Zulkifly, F. A. Rahman, and H. Y. Wong, “Arc-induced long period fiber gratings (LPFG) characterization: comparison between cladding etched and non-etched LPFG,” in *Proceedings of the 1st International Conference on Photonics (ICP '10)*, pp. 1–3, IEEE, Langkawi, Malaysia, July 2010.
- [61] A. Iadicicco, S. Campopiano, A. Cutolo, M. L. K. Pawlowski, W. J. Bock, and A. Cusano, “Refractive index sensitivity in thinned UV and arc induced long-period gratings: a comparative study,” *International Journal on Smart Sensing and Intelligent Systems*, vol. 1, no. 2, pp. 354–369, 2008.
- [62] A. Martínez-Ríos, D. Monzón-Hernández, and G. Salceda-Delgado, “Arc-induced long-period fiber gratings inscribed in asymmetric adiabatic tapers,” in *Optical Components and Materials X*, vol. 8621 of *Proceedings of SPIE*, San Francisco, Calif, USA, March 2013.
- [63] R. I. Mata-Chávez, A. Martinez-Rios, I. Torres-Gomez, J. A. Alvarez-Chavez, R. Selvas-Aguilar, and J. Estudillo-Ayala, “Wavelength band-rejection filters based on optical fiber fattening by fusion splicing,” *Optics & Laser Technology*, vol. 40, no. 4, pp. 671–675, 2008.
- [64] A. Martinez-Rios, I. Torres-Gomez, D. Monzon-Hernandez, G. Salceda-Delgado, V. M. Duran-Ramirez, and G. Anzueto-Sanchez, “Random period arc-induced long-period fiber gratings,” *Optics & Laser Technology*, vol. 44, no. 4, pp. 1176–1179, 2012.
- [65] G. E. Silva, P. J. C. Santos, and J. L. Santos, “Optical fiber refractive index sensor with reduced thermal sensitivity based on superimposed long-period gratings,” in *23rd International*

- Conference on Optical Fiber Sensors, 91571S*, vol. 9157 of *Proceedings of SPIE*, p. 1, June 2014.
- [66] G. Rego, R. Falate, O. Ivanov, and J. L. Santos, "Simultaneous temperature and strain measurements performed by a step-changed arc-induced long-period fiber grating," *Applied Optics*, vol. 46, no. 9, pp. 1392–1396, 2007.
 - [67] G. Rego, "Long-period gratings arc-induced in B/GE codoped fibers. Thermal behavior and uniform exposure to UV-radiation," *Microwave and Optical Technology Letters*, vol. 50, no. 1, pp. 68–71, 2008.
 - [68] G. Rego, P. Caldas, O. Ivanov, and J. L. Santos, "Investigation of the long-term stability of arc-induced gratings heat treated at high temperatures," *Optics Communications*, vol. 284, no. 1, pp. 169–171, 2011.
 - [69] G. Rego, "Annealing of arc-induced gratings at high temperatures," *Electronics Letters*, vol. 45, no. 19, pp. 972–974, 2009.
 - [70] R. I. Mata-Chávez, A. Martínez-Rios, J. M. Estudillo-Ayala et al., "High temperature optical fiber sensor based on compact fattened long-period fiber gratings," *Sensors*, vol. 13, no. 3, pp. 3028–3038, 2013.
 - [71] T. Geng, D. Zi, W. Yang, and C. Tong, "The LPFG temperature characteristic research based on electric heating method," in *Proceedings of the IEEE International Conference on Optoelectronics and Microelectronics (ICOM '13)*, pp. 29–32, Harbin, China, September 2013.
 - [72] R. Martins, P. Caldas, B. Teixeira et al., "Cryogenic temperature response of reflection-based phase-shifted long-period fiber gratings," *Journal of Lightwave Technology*, vol. 33, no. 12, pp. 2511–2517, 2015.
 - [73] P. Caldas, G. Rego, O. V. Ivanov, and J. L. Santos, "Characterization of the response of a dual resonance of an arc-induced long-period grating to various physical parameters," *Applied Optics*, vol. 49, no. 16, pp. 2994–2999, 2010.
 - [74] W. J. Bock, J. Chen, P. Mikulic, and T. Eftimov, "A novel fiber-optic tapered long-period grating sensor for pressure monitoring," *IEEE Transactions on Instrumentation and Measurement*, vol. 56, no. 4, pp. 1176–1180, 2007.
 - [75] J. Sadeghi, M. I. Zibaii, M. Kheiri, A. Ahmadi, H. Latifi, and M. H. Ghezalaigh, "Hybrid long period fiber grating for measuring refractive index and pressure in downhole application," in *Optical Sensors and Biophotonics III*, vol. 8311 of *Proceedings of SPIE*, November 2011.
 - [76] V. Guzman-Ramos, D. E. Ceballos-Herrera, and R. Selvas-Aguilar, "Numerical analysis of GeO₂-concentration effects in arc-induced long-period fiber gratings under external refractive-index changes," *Optical Review*, vol. 21, no. 2, pp. 143–149, 2014.
 - [77] R. C. Kamikawachi, G. R. C. Possetti, M. Muller, and J. L. Fabris, "Influence of the surrounding refractive index on the thermal and strain sensitivities of a cascaded long period grating," *Measurement Science and Technology*, vol. 18, no. 10, pp. 3111–3116, 2007.
 - [78] R. C. Kamikawachi, G. R. C. Possetti, R. Falate, M. Muller, and J. L. Fabris, "Influence of surrounding media refractive index on the thermal and strain sensitivities of long-period gratings," *Applied Optics*, vol. 46, no. 15, pp. 2831–2837, 2007.
 - [79] G. M. Rego, J. L. Santos, and H. M. Salgado, "Refractive index measurement with long-period gratings arc-induced in pure-silica-core fibres," *Optics Communications*, vol. 259, no. 2, pp. 598–602, 2006.
 - [80] M. Smietana, J. Szmids, M. L. Korwin-Pawlowski, W. J. Bock, and J. Grabarczyk, "Application of diamond-like carbon films in optical fibre sensors based on long-period gratings," *Diamond and Related Materials*, vol. 16, no. 4–7, pp. 1374–1377, 2007.
 - [81] M. Śmietana, M. Myśliwiec, P. Mikulic, B. S. Witkowski, and W. J. Bock, "Capability for fine tuning of the refractive index sensing properties of long-period gratings by atomic layer deposited Al₂O₃ overlays," *Sensors*, vol. 13, no. 12, pp. 16372–16383, 2013.
 - [82] M. Smietana, W. J. Bock, and P. Mikulic, "Effect of high-temperature plasma-deposited nano-overlays on the properties of long-period gratings written with UV and electric arc in non-hydrogenated fibers," *Measurement Science and Technology*, vol. 24, no. 9, Article ID 094016, 2013.
 - [83] P. Pilla, M. Giordano, M. L. Korwin-Pawlowski, W. J. Bock, and A. Cusano, "Sensitivity characteristics tuning in tapered long-period gratings by nanocoatings," *IEEE Photonics Technology Letters*, vol. 19, no. 19, pp. 1517–1519, 2007.
 - [84] M. Smietana, W. J. Bock, and P. Mikulic, "Temperature sensitivity of silicon nitride nanocoated long-period gratings working in various surrounding media," *Measurement Science and Technology*, vol. 22, no. 11, Article ID 115203, 2011.
 - [85] P. Caldas, P. A. S. Jorge, F. M. Araújo, L. A. Ferreira, G. Rego, and J. L. Santos, "Geometrical effects on the refractive index sensitivity of Mach-Zehnder fibre modal interferometers based on long-period gratings," *Measurement Science and Technology*, vol. 20, no. 7, Article ID 075201, 2009.
 - [86] P. Caldas, P. A. S. Jorge, F. M. Araújo, L. A. Ferreira, G. Rego, and J. L. Santos, "Effect of fiber tapering in LPG-based Mach-Zehnder modal interferometers for refractive-index sensing," in *20th International Conference on Optical Fibre Sensors*, vol. 7503 of *Proceedings of SPIE*, Edinburgh, UK, October 2009.
 - [87] G. M. Rego, J. L. Santos, and H. M. Salgado, "Polarization dependent loss of arc-induced long-period fibre gratings," *Optics Communications*, vol. 262, no. 2, pp. 152–156, 2006.
 - [88] V. Grubsky and J. Feinberg, "Long-period fiber gratings with variable coupling for real-time sensing applications," *Optics Letters*, vol. 25, no. 4, pp. 203–205, 2000.
 - [89] G. Anzueto-Sánchez, A. Martínez-Rios, and J. Castellon-Urbe, "Tuning and wavelength switching erbium-doped fiber ring lasers by controlled bending in arc-induced long-period fiber gratings," *Optical Fiber Technology*, vol. 18, no. 6, pp. 513–517, 2012.
 - [90] I. Trifanov, P. Caldas, L. Neagu et al., "Combined neodymium—ytterbium-doped ASE fiber-optic source for optical coherence tomography applications," *IEEE Photonics Technology Letters*, vol. 23, no. 1, pp. 21–23, 2011.
 - [91] F. Abrishamian and K. Morishita, "Cascade connection of two long-period fiber gratings with a π -phase shift to expand the rejection bandwidths," *IEICE Transactions on Electronics*, vol. 98, no. 6, pp. 512–517, 2015.
 - [92] G. Rego, "Optical filters for fiber lasers and amplifiers," *Microwave and Optical Technology Letters*, vol. 50, no. 4, pp. 890–894, 2008.
 - [93] S. Oh, K. R. Lee, U.-C. Paek, and Y. Chung, "Fabrication of helical long-period fiber gratings by use of a CO₂ laser," *Optics Letters*, vol. 29, no. 13, pp. 1464–1466, 2004.
 - [94] V. I. Kopp, V. M. Churikov, J. Singer, N. Chao, D. Neugroschl, and A. Z. Genack, "Chiral fiber gratings," *Science*, vol. 305, no. 5680, pp. 74–75, 2004.
 - [95] V. I. Kopp, V. M. Churikova, G. Zhang et al., "Chiral fiber gratings: perspectives and challenges for sensing applications," in *3rd European Workshop on Optical Fibre Sensors (EWOFS)*

- '07), 66190B, vol. 6619 of *Proceedings of SPIE*, p. 1, Napoli, Italy, July 2007.
- [96] O. Frazão, L. M. Marques, S. Santos, J. M. Baptista, and J. L. Santos, "Simultaneous measurement for strain and temperature based on a long-period grating combined with a high-birefringence fiber loop mirror," *IEEE Photonics Technology Letters*, vol. 18, no. 22, pp. 2407–2409, 2006.
- [97] G. Rego, "Simultaneous measurement of temperature and strain based on arc-induced long-period fiber gratings. A case study," *Microwave and Optical Technology Letters*, vol. 50, no. 9, pp. 2472–2474, 2008.
- [98] J. M. Baptista, S. F. Santos, G. Rego, O. Frazão, and J. L. Santos, "Micro-displacement or bending measurement using a long-period fibre grating in a self-referenced fibre optic intensity sensor," *Optics Communications*, vol. 260, no. 1, pp. 8–11, 2006.
- [99] O. Frazão, R. Falate, J. M. Baptista, J. L. Fabris, and J. L. Santos, "Optical bend sensor based on a long-period fiber grating monitored by an optical time-domain reflectometer," *Optical Engineering*, vol. 44, no. 11, Article ID 110502, 2005.
- [100] R. Falate, O. Frazão, G. Rego et al., "Bending sensitivity dependent on the phase shift imprinted in long-period fibre gratings," *Measurement Science and Technology*, vol. 18, no. 10, pp. 3123–3130, 2007.
- [101] O. Frazão, J. Viegas, P. Caldas et al., "All-fiber Mach-Zehnder curvature sensor based on multimode interference combined with a long-period grating," *Optics Letters*, vol. 32, no. 21, pp. 3074–3076, 2007.
- [102] Z. Wu, N. Zhang, P. Shum et al., "Curvature sensor based on long-period grating in dual concentric core fiber," in *Proceedings of the Conference on Lasers and Electro-Optics: Applications and Technology (CLEO-AT '15)*, ATu1M.5, San Jose, Calif, USA, May 2015.
- [103] M. Smietana, W. J. Bock, P. Mikulic, and J. H. Chen, "Pressure sensing in high-refractive-index liquids using long-period gratings nanocoated with silicon nitride," *Sensors*, vol. 10, no. 12, pp. 11301–11310, 2010.
- [104] A. Kos, J. H. Chen, W. J. Bock, and P. Mikulic, "Tapered long-period grating (TLPG) with Teflon AF coating for pressure sensing applications," in *Proceedings of the Canadian Conference on Electrical and Computer Engineering (CCECE '08)*, pp. 861–866, IEEE, Niagara Falls, Canada, May 2008.
- [105] O. Frazão, R. Falate, J. L. Fabris, J. L. Santos, L. A. Ferreira, and F. M. Araújo, "Optical inclinometer based on a single long-period fiber grating combined with a fused taper," *Optics Letters*, vol. 31, no. 20, pp. 2960–2962, 2006.
- [106] P. Caldas, P. A. S. Jorge, G. Rego et al., "Fiber optic hot-wire flowmeter based on a metallic coated hybrid long period grating/fiber Bragg grating structure," *Applied Optics*, vol. 50, no. 17, pp. 2738–2743, 2011.
- [107] G. E. Silva, P. Caldas, J. C. Santos, and J. L. Santos, "All-fiber sensor based on a metallic coated hybrid LPG-FBG structure for thermal characterization of materials," in *23rd International Conference on Optical Fibre Sensors (OFS '14)*, vol. 9157 of *Proceedings of SPIE*, June 2014.
- [108] L. Coelho, D. Viegas, J. L. Santos, and J. M. M. de Almeida, "Real time monitoring oxidation of transition metals with long period fiber gratings," in *24th International Conference on Optical Fibre Sensors*, vol. 9634 of *Proceedings of SPIE*, Curitiba, Brazil, September 2015.
- [109] M. Šmietana, M. Koba, P. Mikulic, and W. J. Bock, "Measurements of reactive ion etching process effect using long-period fiber gratings," *Optics Express*, vol. 22, no. 5, pp. 5986–5994, 2014.
- [110] J. P. Carvalho, L. Coelho, M. J. Pontes et al., "Long-period gratings dynamic interrogation with modulated fiber bragg gratings and optical amplification," *IEEE Sensors Journal*, vol. 12, no. 1, pp. 179–183, 2012.
- [111] J. P. Carvalho, L. Coelho, J. M. Baptista, J. L. Santos, and O. Frazão, "Dynamic interrogation for optical fibre sensors based on long-period gratings," *Measurement Science and Technology*, vol. 22, no. 6, Article ID 065201, 5 pages, 2011.
- [112] O. Frazão, C. Correia, J. M. Baptista, M. B. Marques, and J. L. Santos, "Ring fibre laser with interferometer based in long period grating for sensing applications," *Optics Communications*, vol. 281, no. 22, pp. 5601–5604, 2008.
- [113] D. Viegas, J. P. Carvalho, L. Coelho, J. L. Santos, F. M. Araújo, and O. Frazão, "Long-period grating fiber sensor with in situ optical source for remote sensing," *IEEE Photonics Technology Letters*, vol. 22, no. 20, pp. 1533–1535, 2010.
- [114] P. Caldas, P. A. S. Jorge, F. M. Araújo et al., "Fiber modal Michelson interferometers with coherence addressing and heterodyne interrogation," *Optical Engineering*, vol. 47, no. 4, Article ID 044401, 2008.
- [115] Y. Yong, S. Lee, and F. A. Rahman, "Sensitization of hybrid LPFG-FBG refractometer using double-pass configuration," *Optics Communications*, vol. 338, pp. 590–595, 2015.
- [116] R. Falate, O. Frazão, G. Rego, J. L. Fabris, and J. L. Santos, "Refractometric sensor based on a phase-shifted long-period fiber grating," *Applied Optics*, vol. 45, no. 21, pp. 5066–5072, 2006.
- [117] C. Silva, J. M. P. Coelho, P. Caldas, O. Frazão, P. A. S. Jorge, and J. L. Santos, "Optical fiber sensing system based on long-period gratings for remote refractive index measurement in aqueous environments," *Fiber and Integrated Optics*, vol. 29, no. 3, pp. 160–169, 2010.
- [118] C. Jesus, P. Caldas, O. Frazão, J. L. Santos, P. A. S. Jorge, and J. M. Baptista, "Simultaneous measurement of refractive index and temperature using a hybrid fiber bragg grating/long-period fiber grating configuration," *Fiber and Integrated Optics*, vol. 28, no. 6, pp. 440–449, 2009.
- [119] J. Linesh, T. M. Libish, M. C. Bobby, P. Radhakrishnan, and V. P. N. Nampoori, "Periodically tapered LPFG for ethanol concentration detection in ethanol-gasoline blend," *Sensors and Transducers*, vol. 125, no. 2, pp. 205–212, 2011.
- [120] K. P. Chan, C. S. Tan, W. S. Teng, F. A. Rahman, S. C. Soon, and Z. R. Zulkifly, "Feasibility study of long period grating as an optical biosensor for dengue virus detection—an alternative approach to dengue virus screening," in *Proceedings of the IEEE EMBS Conference on Biomedical Engineering and Sciences (IECBES '10)*, pp. 38–42, Kuala Lumpur, Malaysia, December 2010.
- [121] M. C. Loh, F. A. Rahman, H. Kuramitz, and Y. T. Yong, "Method to sensitize an arc-induced LPFG-based sensor using double-pass configuration," *Microwave and Optical Technology Letters*, vol. 56, no. 12, pp. 2766–2769, 2014.
- [122] M. Loh, Y. T. Yong, H. Kuramitz, P. C. Teh, and F. Abd-Rahman, "Double-pass configuration to enhance the sensitivity of a polyelectrolyte-coated arc-induced long-period fiber grating," *Journal of Electromagnetic Waves and Applications*, vol. 29, no. 14, pp. 1908–1916, 2015.
- [123] E. Simões, I. Abe, J. Oliveira, O. Frazão, P. Caldas, and J. L. Pinto, "Characterization of optical fiber long period grating

- refractometer with nanocoating,” *Sensors and Actuators B: Chemical*, vol. 153, no. 2, pp. 335–339, 2011.
- [124] I. M. Nascimento, C. Gouveia, S. Jana et al., “High refractive index and temperature sensitivity LPGs for high temperature operation,” in *8th Iberoamerican Optics Meeting and 11th Latin American Meeting on Optics, Lasers, and Applications*, vol. 8785 of *Proceedings of SPIE*, November 2013.
- [125] I. Abe, J. Oliveira, E. Simões, P. Caldas, and O. Frazão, “Monitoring the quality of frying oils using a nanolayer coated optical fiber refractometer,” *Talanta*, vol. 83, no. 1, pp. 291–293, 2010.
- [126] L. Coelho, D. Viegas, J. L. Santos, and J. M. de Almeida, “Detection of extra virgin olive oil thermal deterioration using a long period fiber grating sensor coated with titanium dioxide,” *Food and Bioprocess Technology*, vol. 8, no. 6, pp. 1211–1217, 2015.
- [127] D. Viegas, J. Goicoechea, J. L. Santos et al., “Sensitivity improvement of a humidity sensor based on silica nanospheres on a long-period fiber grating,” *Sensors*, vol. 9, no. 1, pp. 519–527, 2009.
- [128] L. Coelho, D. Viegas, J. L. Santos, and J. M. M. M. Almeida, “Characterization of zinc oxide coated optical fiber long period gratings with improved refractive index sensing properties,” *Sensors and Actuators B: Chemical*, vol. 223, pp. 45–51, 2016.
- [129] L. Coelho, D. Viegas, J. L. Santos, and J. M. M. M. D. Almeida, “Enhanced refractive index sensing characteristics of optical fibre long period grating coated with titanium dioxide thin films,” *Sensors and Actuators B: Chemical*, vol. 202, pp. 929–934, 2014.
- [130] L. Coelho, R. B. Queirós, J. L. Santos et al., “DNA-Aptamer optical biosensors based on a LPG-SPR optical fiber platform for point-of care diagnostic,” in *Plasmonics in Biology and Medicine XI*, 89570K, vol. 8957 of *Proceedings of SPIE*, March 2014.
- [131] C. Gouveia, K. Balogh, J. M. Baptista, B. Kovacs, and P. A. S. Jorge, “LPG based fiber optic sensor for carbon dioxide,” in *22nd International Conference on Optical Fiber Sensors (OFS '12)*, vol. 8421 of *Proceedings of SPIE*, Beijing, China, October 2012.
- [132] R. B. Queirós, C. Gouveia, J. R. A. Fernandes, and P. A. S. Jorge, “Evanescent wave DNA-aptamer biosensor based on long period gratings for the specific recognition of *E. coli* outer membrane proteins,” *Biosensors and Bioelectronics*, vol. 62, pp. 227–233, 2014.
- [133] A. Czapla, T. R. Woliński, W. J. Bock, E. Nowinowski-Kruszelnicki, R. Dąbrowski, and J. Wójcik, “Long-signature: highlighting sparse salient regions,” *Molecular Crystals and Liquid Crystals*, vol. 502, no. 1, pp. 65–76, 2009.
- [134] P. A. S. Jorge, S. O. Silva, C. Gouveia et al., “Review: fiber optic-based refractive index sensing at INESC Porto,” *Sensors*, vol. 12, no. 6, pp. 8371–8389, 2012.
- [135] P. Pilla, C. Trono, F. Baldini, F. Chiavaioli, M. Giordano, and A. Cusano, “Giant sensitivity of long period gratings in transition mode near the dispersion turning point: an integrated design approach,” *Optics Letters*, vol. 37, no. 19, pp. 4152–4154, 2012.
- [136] F. Zou, Y. Liu, C. Deng, Y. Dong, S. Zhu, and T. Wang, “Refractive index sensitivity of nano-film coated long-period fiber gratings,” *Optics Express*, vol. 23, no. 2, pp. 1114–1124, 2015.
- [137] I. Del Villar, “Ultrahigh-sensitivity sensors based on thin-film coated long period gratings with reduced diameter, in transition mode and near the dispersion turning point,” *Optics Express*, vol. 23, no. 7, pp. 8389–8398, 2015.
- [138] M. Smietana, M. Koba, P. Mikulic, and W. J. Bock, “Tuning properties of long-period gratings by plasma post-processing of their diamond-like carbon nano-overlays,” *Measurement Science and Technology*, vol. 25, no. 11, Article ID 114001, 2014.
- [139] M. Smietana, M. Koba, P. Mikulic, and W. J. Bock, “Enhancing sensitivity of long-period gratings by combined fiber etching and diamond-like carbon nano-overlay deposition,” in *24th International Conference on Optical Fiber Sensors*, 963456, vol. 9634 of *Proceedings of SPIE*, Curitiba, Brazil, September 2015.
- [140] H. J. Patrick, A. D. Kersey, and F. Bucholtz, “Analysis of the response of long period fiber gratings to external index of refraction,” *Journal of Lightwave Technology*, vol. 16, no. 9, pp. 1606–1612, 1998.
- [141] X. Lan, Q. Han, J. Huang et al., “Turn-around point long-period fiber grating fabricated by CO₂ laser for refractive index sensing,” *Sensors and Actuators, B: Chemical*, vol. 177, pp. 1149–1155, 2013.
- [142] R. Garg, S. M. Tripathi, K. Thyagarajan, and W. J. Bock, “Long period fiber grating based temperature-compensated high performance sensor for bio-chemical sensing applications,” *Sensors and Actuators B: Chemical*, vol. 176, pp. 1121–1127, 2013.
- [143] J. Huang, X. Lan, A. Kaur, H. Wang, L. Yuan, and H. Xiao, “Reflection-based phase-shifted long period fiber grating for simultaneous measurement of temperature and refractive index,” *Optical Engineering*, vol. 52, no. 1, Article ID 014404, 4 pages, 2013.
- [144] N. D. Rees, S. W. James, R. P. Tatam, and G. J. Ashwell, “Optical fiber long-period gratings with Langmuir-Blodgett thin-film overlays,” *Optics Letters*, vol. 27, no. 9, pp. 686–688, 2002.
- [145] I. M. Ishaq, A. Quintela, S. W. James, G. J. Ashwell, J. M. Lopez-Higuera, and R. P. Tatam, “Modification of the refractive index response of long period gratings using thin film overlays,” *Sensors and Actuators B: Chemical*, vol. 107, no. 2, pp. 738–741, 2005.
- [146] I. D. Villar, I. R. Matías, F. J. Arregui, and P. Lalanne, “Optimization of sensitivity in long period fiber gratings with overlay deposition,” *Optics Express*, vol. 13, no. 1, pp. 56–69, 2005.
- [147] A. Cusano, A. Iadicicco, P. Pilla et al., “Mode transition in high refractive index coated long period gratings,” *Optics Express*, vol. 14, no. 1, pp. 19–34, 2006.
- [148] I. Del Villar, M. Achaerandio, I. R. Matías, and F. J. Arregui, “Deposition of overlays by electrostatic self-assembly in long-period fiber gratings,” *Optics Letters*, vol. 30, no. 7, pp. 720–722, 2005.
- [149] S. Korposh, R. Selyanchyn, W. Yasukochi, S.-W. Lee, S. W. James, and R. P. Tatam, “Optical fibre long period grating with a nanoporous coating formed from silica nanoparticles for ammonia sensing in water,” *Materials Chemistry and Physics*, vol. 133, no. 2–3, pp. 784–792, 2012.
- [150] S. M. Tripathi, W. J. Bock, P. Mikulic et al., “Long period grating based biosensor for the detection of *Escherichia coli* bacteria,” *Biosensors and Bioelectronics*, vol. 35, no. 1, pp. 308–312, 2012.
- [151] J. Kanka, “Long-period gratings in photonic crystal fibers operating near the phase-matching turning point for evanescent chemical and biochemical sensing,” in *Fiber Optic Sensors and Applications IX*, vol. 8370 of *Proceedings of SPIE*, pp. 1–11, May 2012.