Research Article

Synthesis and Photocatalytic Properties of ZnWO_4 Nanocrystals via a Fast Microwave-Assisted Method

Jing Yan, Yanhua Shen, Feng Li, and Taohai Li

Key Lab of Environment Friendly Chemistry and Application of Ministry of Education, College of Chemistry, Xiangtan University, Xiangtan 411105, China

Correspondence should be addressed to Taohai Li; hnlth@xtu.edu.cn

Received 6 April 2013; Accepted 8 May 2013

Academic Editors: B. Huang and L. Jing

Copyright © 2013 Jing Yan et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

High crystallinity of ZnWO_4 nanoparticles has been successfully synthesized via a highly effective and environmentally friendly microwave route by controlling the reaction time and temperature. The products were characterized by X-ray powder diffraction (XRD), transmission electron microscopy (TEM), and Fourier infrared spectrum (FT-IR). The crystallinity was enhanced with the increase of the reaction temperature and time. The photocatalytic activities of ZnWO_4 nanocrystals were evaluated by testing the photodegradation of rhodamine B (RhB) dye under ultraviolet (UV) light irradiation. The results indicated that as-prepared ZnWO_4 was highly effective for the degradation of RhB. The degradation rate of RhB reached 98.01% after 6 h of UV illumination.

1. Introduction

Tungsten materials with novel architectures and physical and chemical properties are very useful for many potential applications such as flashing materials, LED [1], magnetic and fluorescent materials [2–8], optical fiber, humidity sensors [9], light emitting materials [10, 11], photocatalytic materials [12–18], scintillator [19], laser host [20], and nanoordered substrate materials [21, 22], so they are considered as an important class of functional materials. As an important photocatalyst, ZnWO_4 has been applied for photocatalytic hydrogen production from water and mineralization of organic pollutants under UV light irradiation [18]. For the formation of tungstate nanomaterials with unique morphology and hierarchical organization, a great number of synthetic techniques, such as hydrothermal method [23, 24], microemulsion, and sol-gel method [25–28], have been developed in the past few years.

However, there are some shortcomings for the traditional synthetic methods: (1) the reaction temperature is too high; (2) the reaction cycle is too long; (3) the procedure is complex [23]. Obviously, the long reaction cycle will waste time. It is worse that the long reaction time may lead to the dendritic growth and increase the particle size. Chen and coworkers have synthesized ZnWO_4 powder by hydrothermal method

and demonstrating that particle aggregation is stimulated by temperature and time increase [2]. Wu et al. have successfully produced ZnWO_4 photocatalyst via the sol-gel process in a temperature range of 450–800°C, but the grain size is difficult to be controlled [25]. Thus, the application of ZnWO_4 photocatalyst has been limited, and an energy saving and environmentally friendly synthesis method of nanoscale tungstate has received extensive attention.

To date, as far as we know, the synthesis of ZnWO_4 photocatalyst by microwave-assisted method is rare. Wu et al. have reported a microwave solvothermal route to synthesize ZnWO_4 nanoparticles at 160°C. However, the route needed longer time (1–3 h) and organic solvent (ethylene glycol) [29]. Therefore, the development of fast and environmentally friendly microwave-assisted methods for the synthesis of ZnWO_4 nanocrystals is of great importance for broadening and improving their industrial applications. In this paper, we first successfully obtained high crystallinity ZnWO_4 photocatalyst with a microwave-assisted process by several minutes and using water as solvent. Compared with the conventional methods, microwave irradiation is preferable due to its unique effects, such as volumetric heating, higher reaction rates, shorter reaction time, selectivity energy saving, and being environmentally friendly. During the degradation of rhodamine B (RhB) under UV light irradiation, the ZnWO_4

FIGURE 1: XRD patterns of ZnWO_4 formed at a different reaction temperature for 5 min.

FIGURE 2: XRD patterns of ZnWO_4 formed for a different reaction time at 180°C .

FIGURE 3: FT-IR spectra of ZnWO_4 formed at 180°C for 15 min.

exhibited high photocatalytic activities. The measurements suggested that photocatalytic property of the sample is related to the crystallinity, surface area, and dimension of particles. Moreover, the catalyst is relatively stable and can be reused.

2. Experimental Section

2.1. Synthesis. All syntheses were performed using a commercial multimode microwave synthesizer coupled with an automation system (Initiator 8 Exp). The reactions were conducted in 20 mL vessels. In a typical synthesis of the ZnWO_4 powder, all the chemicals were of analytical grade and used without further purification. Sodium tungstate ($\text{Na}_2\text{WO}_4 \cdot 2\text{H}_2\text{O}$) and zinc chloride (ZnCl_2) were the starting materials. $\text{Na}_2\text{WO}_4 \cdot 2\text{H}_2\text{O}$ (0.14 g), ZnCl_2 (0.13 g), H_2O (10.0 mL), and poly(ethylene glycol) (0.12 g) were mixed. When the vessel was protected by a sealing cap, it was then transferred into the microwave cavity, and the temperature was increased rapidly to 180°C at a rate of $50^\circ\text{C}/\text{min}$. The reaction was performed at 180°C for several minutes, and the reaction vessel was quickly cooled to room temperature by a forced- N_2 flow. The as-synthesized ZnWO_4 nanocrystals were collected by centrifugation, washed with distilled water and absolute ethanol several times to remove impurities, and finally dried in vacuum at 80°C for 4 h.

2.2. Characterization. The morphology and microstructure of the sample were observed with a JEM-2010 transmission electron microscope operated at 120 kV. Further structural characterization was performed on FEI Tecnai F20 high-resolution field-emission transmission electron microscope (HRTEM) operated at 200 kV. XRD patterns of ZnWO_4 photocatalysts were recorded by a MiniFlex II X-ray diffractometer operated at 40 kV and 40 mA using Cu K radiation ($\lambda = 0.15406 \text{ nm}$). UV-Vis DRS was performed on a Hitachi U-3010, and BaSO_4 was used as a reference. Fourier transform infrared spectra (FT-IR) were recorded on a Perkin-Elmer 1600 FT-IR spectrometer with a KBr disk. BET surface area was determined by nitrogen adsorption isotherm measurements at 77 K on a Micrometrics ASAP 2010.

2.3. Measurements of Photocatalytic Activity. The photocatalytic activity of ZnWO_4 catalysts was evaluated by degradation of RhB under a 300 W UV irradiation. ZnWO_4 photocatalyst (25 mg) was dispersed in RhB solution (10 mg/L). Before UV irradiation, an adsorption-desorption equilibrium was established by ultrasonic and mechanical stirring for 30 min. After that, the solution was exposed to UV light irradiation under magnetic stirring. A little amount of reaction solution for UV-Vis spectroscopy analysis was taken from the photoreactor at appropriate time interval.

3. Results and Discussion

The phase composition of the samples prepared at different temperatures was analyzed by X-ray powder diffraction (XRD). As shown in Figure 1, there was no obvious ZnWO_4 phase formation at 140 and 160°C . A sharpening of the

FIGURE 4: TEM morphologies of ZnWO_4 at 180°C for different reaction times, 5 min (a), 10 min (b), 15 min (c), and HRTEM (d).

peaks is observed at 180°C , and all peaks can be indexed in reference to pure ZnWO_4 , space group $P2_1/c$, and unit cell parameters consistent with those reported in JCPDS 15-0774. Therefore, it is reasonable to deduce that the increase of the microwave temperature improves the crystalline of ZnWO_4 powder. Thus, the temperature increase stimulates effectively the crystallization of ZnWO_4 nanoparticles.

The growth process ZnWO_4 nanocrystals was monitored by investigating the products obtained at different stages of the reaction using XRD techniques. Figure 2 shows the XRD patterns of ZnWO_4 samples irradiated at 180°C at different reaction stages. XRD patterns could be easily identified as a pure monoclinic wolframite structure ZnWO_4 based on a JCPDS Card (no. 15-0774). The results indicated that the intensity of the diffraction peaks strengthens with the increase of reaction time, especially in the (010), (100), (011), (110), (111), and (021) crystal planes of ZnWO_4 . Small intensity (010) peak can be found in XRD patterns with 5 min reaction time. When the reaction time extended to 15 min, the (010) peak appeared. These results show that reaction time has an influence on the phase formation of ZnWO_4 . It also

suggests that microwave method can achieve crystallization of samples in higher kinetics, which economized the energy and shortened the time.

The FT-IR spectrum of ZnWO_4 powders is shown in Figure 3. The bands at 463 cm^{-1} and 585 cm^{-1} are ascribed to the bending vibrations of W-O. The peaks at 702 cm^{-1} and 827 cm^{-1} are ascribed to the stretching vibrations of W-O. There exists a band at 872 cm^{-1} that arises from the bending and stretching vibrations of Zn-O-W [30]. The bands at 1401 cm^{-1} , 1468 cm^{-1} , 1541 cm^{-1} , 1622 cm^{-1} , and 3449 cm^{-1} are assigned to the O-H stretching and the H-O-H bending vibrations [31]. The weak bands at 2850 cm^{-1} and 2920 cm^{-1} are ascribed to the C-O vibration of CO_2 in atmosphere [32]. The characteristic bands of the ZnWO_4 indicated that the ZnWO_4 formed.

The TEM images of ZnWO_4 catalysts prepared at 180°C for various times are shown in Figure 4. The ZnWO_4 sample prepared at 180°C consists of the rodlike particles. The TEM images show that the length of ZnWO_4 nanorods is about 26 nm and diameter is about 12 nm after 5 min of microwave irradiation. With the increase of irradiation time from 5 min

FIGURE 5: UV-visible absorption spectra changes of RhB with different as-prepared ZnWO_4 samples: (a) 140°C , 5 min, (b) 160°C , 5 min, and (c) 180°C , 5 min. (d) Kinetics of degradation of RhB.

to 15 min, the dimension of ZnWO_4 nanorods increased. It can be seen that the reaction time plays a crucial role in diameter of the samples. The selected area electron diffraction (SAED) image recorded from the sample formed by 10 min microwave radiation indicates the single-crystal nature of the particles. This is verified by high-resolution field-emission TEM (HRTEM) image of ZnWO_4 nanocrystals where d -spacing of about 0.586 nm is detected and well related to (010) interplane distance.

ZnWO_4 , as a semiconductor with a bandgap (E_g) around 3.9–4.4 eV, has high photocatalytic activity under UV light. The photocatalytic activities of as-prepared samples were tested via degradation of aqueous RhB under UV irradiation. The UV-visible absorption spectral changes taking place during the photodegradation of RhB for samples and photocatalytic kinetic curves of samples are shown in Figure 5, respectively. The results show that the sample prepared at 140°C has the highest photocatalytic activity, and after 6 hours

FIGURE 6: Typical nitrogen adsorption isotherms of as-prepared ZnWO_4 : (a) 140°C and (b) 160°C . Inset: Effect picture of photocatalytic degradation RhB by ZnWO_4 prepared at 140°C for 5 min.

of irradiation, the degradation rate of RhB can be nearly 98.01%. The kinetics curves of photodegradation of RhB are shown in Figure 5(d) where the curves 1, 2, and 3 are related to samples prepared at 140°C , 160°C , and 180°C , respectively.

The linear relationship between η and time demonstrates that the photocatalytic degradation of RhB follows a pseudo-first-order kinetics:

$$\eta = \ln\left(\frac{C_0}{C}\right) = kt, \quad (1)$$

where C_0/C is normalized RhB concentration, t is the reaction time, and k is the reaction rate constant (min^{-1}). The figure also shows that the degradation rate of samples prepared at 140°C is the best (curve 1), the reaction rate constant of which is calculated to be 0.6798 min^{-1} . The degradation rate of samples prepared at 160°C is center (curve 2), the reaction rate constant of which is calculated to be 0.6760 min^{-1} . The degradation rate of samples prepared at 180°C is the lowest (curve 3), the reaction rate constant of which is calculated to be 0.4133 min^{-1} . The sample prepared at as high temperature as 180°C exhibits the lower ability to transform RhB compared with those prepared at 140 – 160°C . This indicates that the crystallinity structure of photocatalyst is the vital factor that affects the photocatalytic activity of materials.

To obtain the information about the specific surface area of the as-prepared ZnWO_4 samples, BET N_2 adsorption analysis was performed. As shown in Figure 6, the nitrogen adsorption isotherm belongs to type II. The analysis showed that the specific surface areas of the samples prepared at 160°C and 140°C were $25.05 \text{ m}^2/\text{g}$ and $28.10 \text{ m}^2/\text{g}$, respectively. The experimental results revealed that the specific surface area of samples prepared at 140°C is higher than the sample prepared at 160°C . Therefore, these demonstrations indicate that photocatalytic properties of ZnWO_4 can be significantly improved by specific surface areas [33]. Figure 6 inset shows the photocatalytic effect of ZnWO_4 prepared at 140°C for

SCHEME 1: Chemical structure of RhB dye.

SCHEME 2: The photocatalytic mechanism of ZnWO_4 under UV illumination.

5 min. We can see that the color of RhB gradually changes from violet red to shallow. This result coincided with the UV-Vis absorption spectra (Figure 5(a)). To evaluate further the photocatalytic activity, the final RhB solution was tested for the carbonation rate. The carbon content of nondegraded RhB solution was $6.445 \text{ m}^2/\text{g}$, and the presence of carbon was not detected in the final RhB solution, which suggested that the dye almost completely was mineralized into CO_2 and H_2O .

In this work, we also studied the photocatalytic degradation of ZnWO_4 prepared at 180°C for different reaction times. The UV-visible absorption spectrum and dynamics curve of the aqueous solution of RhB with ZnWO_4 under exposure to the ultraviolet light lamp for various durations are shown in Figure 7. The results show that the sample prepared at 180°C for 5 min has the highest photocatalytic activity, and after 6 hours of irradiation, the conversion of RhB can be nearly 92.12%. Figure 7(d) is kinetics analysis of photodegradation of RhB, curves 1, 2, 3, and 4 represent photocatalytic kinetic curve of samples prepared at 180°C for 5, 10, and 15 min and no catalyst, respectively. The figure shows that the degradation rate of samples prepared for 5 min is the best (curve 1), the reaction rate constant of which is calculated to be 0.4133 min^{-1} . The degradation rate of samples prepared by 10 min is intermediate, and the reaction rate constant is calculated to be 0.3762 min^{-1} . The degradation

FIGURE 7: UV-visible absorption spectra changes of RhB with different as-prepared ZnWO_4 samples at 180°C : (a) 5 min, (b) 10 min, and (c) 15 min. (d) Kinetics of degradation of RhB.

rate of samples with reaction time of 15 min is the lowest (curve 2), the reaction rate constant of which is calculated to be 0.1261 min^{-1} . Curve 4 shows almost no degradation of RhB after 6 hours of irradiation. When the reaction time is 5 min, samples have poor crystalline, small particles, and good dispersion, which lead to the higher photocatalytic activity. When the reaction time extended to 15 min, the sample has the best crystalline, large particle size, and large aspect ratio, but its photocatalytic activity is poorer than that

of the sample prepared by 5 min [34]. This is consistent with previous conclusions. From the above analysis, we know that ZnWO_4 nanopowders prepared at 180°C for 5 min have better photocatalytic activity, and its photocatalytic effect is shown in Scheme 1. Therefore, the crystallinity and particle size play important roles in photocatalytic activity of as-prepared ZnWO_4 .

Figure 8 compares the activity of ZnWO_4 for photodegradation of RhB under a different reaction condition. It is

FIGURE 8: The activity of ZnWO_4 for photodegradation of RhB under a different reaction condition.

observed that the ZnWO_4 materials prepared at 140°C for 5 min have the maximal degradation rate. With higher reaction temperature, a decrease in photocatalytic activity is observed. These results can be explained by the poor crystallinity at low temperature, which leads to good catalytic activity. Also, with the extension of reaction time, the photocatalytic activity lets down which can be attributed to the large particle size.

On the basis of the above experimental observation, photocatalytic mechanism for ZnWO_4 photocatalytic degradation RhB is speculated (Scheme 2). ZnWO_4 energy band structure was composed by discrete, full-of-low-energy electron valence band (VB) and empty high-energy conduction band (CB); the valence band and conduction band are separated by the forbidden band. When the energy of absorption light is greater than the band gap, the valence electrons are stimulated to the conduction band, making the conduction band with charge, which has a reduction and the valence band resulting hole (h^+) with oxidation. Simultaneously, the poor crystallinity leads to abundant lattice defects acting as holes [35]. These free electrons and holes migrate to the catalyst surface and react with adsorbed water, dissolved oxygen, which generate the high activity of hydroxyl radical ($\cdot\text{OH}$) and superoxide anion (O_2^-), further react with organics in the dyes, and ultimately degraded to CO_2 and H_2O [36].

In addition, we repeated degradation of dye RhB three times with samples prepared at 180°C for 5 min to further study the stability of photocatalyst ZnWO_4 ; the degradation rate remained at 90%. The experimental results showed that the catalyst was relatively stable and can be reused.

4. Conclusions

In this paper, the ZnWO_4 nanoparticles were successfully synthesized by the microwave process. It is possible to control effectively the particle size and crystallization of ZnWO_4 by adjusting the reaction temperature and reaction time. Comparing the photocatalytic property of ZnWO_4 prepared at a different reaction time and temperature, we conclude that photocatalytic property of the sample is related to

the crystallinity, surface area, and dimension of particles. The photocatalytic activity of samples prepared at reaction temperature of 140°C and reaction time of 5 min is the best. Furthermore, the ZnWO_4 powder products showed stable photocatalytic activity for the degradation of RhB under UV light irradiation.

Acknowledgments

The authors acknowledge the financial support of Scientific Research Fund of Hunan Provincial Education Department, China (11C1205), and Provincial Natural Science Foundation of Hunan, China (13JJ6041).

References

- [1] E. Tomaszewicz, S. M. Kaczmarek, and H. Fuks, "New cadmium and rare earth metal tungstates with the scheelite type structure," *Journal of Rare Earths*, vol. 27, no. 4, pp. 569–573, 2009.
- [2] S. J. Chen, J. H. Zhou, X. T. Chen et al., "Fabrication of nanocrystalline ZnWO_4 with different morphologies and sizes via hydrothermal route," *Chemical Physics Letters*, vol. 375, pp. 185–190, 2003.
- [3] V. B. Mikhailik, H. Kraus, D. Wahl, M. Itoh, M. Koike, and I. K. Bailiff, "One- and two-photon excited luminescence and band-gap assignment in CaWO_4 ," *Physical Review B*, vol. 69, no. 20, Article ID 205110, 9 pages, 2004.
- [4] D. Chen, G. Z. Shen, K. B. Tang, H. G. Zheng, and Y. T. Qian, "Low-temperature synthesis of metal tungstates nanocrystallites in ethylene glycol," *Materials Research Bulletin*, vol. 38, pp. 1783–1789, 2003.
- [5] X. Jiang, J. Ma, J. Liu et al., "Synthesis of ZnWO_4 nano-particles by a molten salt method," *Materials Letters*, vol. 61, no. 23–24, pp. 4595–4598, 2007.
- [6] E. Cavalli, A. Belletti, and M. G. Brik, "Optical spectra and energy levels of the Cr^{3+} ions in MWO_4 ($\text{M} = \text{Mg}, \text{Zn}, \text{Cd}$) and MgMoO_4 crystals," *Journal of Physics and Chemistry of Solids*, vol. 69, no. 1, pp. 29–34, 2008.
- [7] M. Itoh, T. Katagiri, T. Aoki, and M. Fujita, "Photo-stimulated luminescence and photo-induced infrared absorption in ZnWO_4 ," *Radiation Measurements*, vol. 42, no. 4–5, pp. 545–548, 2007.
- [8] A. Kalinko, A. Kuzmin, and R. A. Evarestov, "Ab initio study of the electronic and atomic structure of the wolframite-type ZnWO_4 ," *Solid State Communications*, vol. 149, no. 11–12, pp. 425–428, 2009.
- [9] W. M. Qu, W. Wlodarski, and J. U. Meyer, "Comparative study on micromorphology and humidity sensitive properties of thin-film and thick-film humidity sensors based on semiconducting MnWO_4 ," *Sensors and Actuators B*, vol. 64, pp. 76–82, 2000.
- [10] Q. L. Dai, H. W. Song, X. Bai et al., "Photoluminescence properties of $\text{ZnWO}_4:\text{Eu}^{3+}$ nanocrystals prepared by a hydrothermal method," *The Journal of Physical Chemistry C*, vol. 111, pp. 7586–7592, 2007.
- [11] J. Wu, F. Duan, Y. Zheng, and Y. Xie, "Synthesis of Bi_2WO_6 nanoplate-built hierarchical nest-like structures with visible-light-induced photocatalytic activity," *The Journal of Physical Chemistry C*, vol. 111, no. 34, pp. 12866–12871, 2007.
- [12] J. Lv, Z. Zhao, Z. Li, J. Ye, and Z. Zou, "Preparation and photocatalytic property of $\text{LiCr}(\text{WO}_4)_2$," *Journal of Alloys and Compounds*, vol. 485, pp. 346–350, 2009.

- [13] H. B. Fu, J. Lin, L. W. Zhang, and Y. F. Zhu, "Photocatalytic activities of a novel ZnWO_4 catalyst prepared by a hydrothermal process," *Applied Catalysis A*, vol. 306, pp. 58–67, 2006.
- [14] H. Yan, X. Zhang, S. Zhou, X. Xie, Y. Luo, and Y. Yu, "Synthesis of WO_3 nanoparticles for photocatalytic O_2 evolution by thermal decomposition of ammonium tungstate loading on $\text{g-C}_3\text{N}_4$," *Journal of Alloys and Compounds*, vol. 509, pp. L232–L235, 2011.
- [15] H. Y. He, "Preparation and luminescence property of Sm-doped ZnWO_4 powders and films with wet chemical methods," *Physica Status Solidi B*, vol. 246, pp. 177–182, 2009.
- [16] H. B. Fu, C. S. Pan, L. W. Zhang, and Y. F. Zhu, "Synthesis, characterization and photocatalytic properties of nanosized Bi_2WO_6 , PbWO_4 and ZnWO_4 catalysts," *Materials Research Bulletin*, vol. 42, pp. 696–706, 2007.
- [17] J. X. Liu, X. L. Dong, X. W. Liu, F. Shi, S. Yin, and T. Sato, "Solvothermal synthesis and characterization of tungsten oxides with controllable morphology and crystal phase," *Journal of Alloys and Compounds*, vol. 509, no. 5, pp. 1482–1488, 2011.
- [18] C. L. Yu and J. C. Yu, "Sonochemical fabrication, characterization and photocatalytic properties of Ag/ZnWO_4 nanorod catalyst," *Materials Science and Engineering: B*, vol. 164, pp. 16–22, 2009.
- [19] P. Belli, R. Bernabei, F. Cappella et al., "Radioactive contamination of ZnWO_4 crystal scintillators," *Nuclear Instruments and Methods in Physics Research, Section A*, vol. 626–627, no. 1, pp. 31–38, 2011.
- [20] F. G. Yang, Z. Y. You, and C. Y. Tu, "End-pumping $\text{ZnWO}_4:\text{Tm}^{3+}$ at $\sim 1.9\ \mu\text{m}$ eye-safe laser," *Laser Physics Letters*, vol. 9, pp. 204–206, 2012.
- [21] V. V. Atuchin, E. N. Galashov, A. S. Kozhukhov, L. D. Pokrovsky, and V. N. Shlegel, "Epitaxial growth of ZnO nanocrystals at $\text{ZnWO}_4(010)$ cleaved surface," *Journal of Crystal Growth*, vol. 318, no. 1, pp. 1147–1150, 2011.
- [22] V. V. Atuchin, E. N. Galashov, O. Y. Khyzhun, A. S. Kozhukhov, L. D. Pokrovsky, and V. N. Shlegel, "Structural and electronic properties of $\text{ZnWO}_4(010)$ cleaved surface," *Crystal Growth and Design*, vol. 11, no. 6, pp. 2479–2484, 2011.
- [23] J. Huang and L. Gao, "One-step fabrication of ZnWO_4 hollow spheres by nanoparticle aggregation and ripening in alcohol solution," *Journal of the American Ceramic Society*, vol. 89, no. 12, pp. 3877–3880, 2006.
- [24] H. B. Fu, L. W. Zhang, W. Q. Yao, and Y. F. Zhu, "Photocatalytic properties of nanosized Bi_2WO_6 catalysts synthesized via a hydrothermal process," *Applied Catalysis B*, vol. 66, pp. 100–110, 2006.
- [25] Y. Wu, S. C. Zhang, L. W. Zhang, and Y. F. Zhu, "Photocatalytic activity of nanosized ZnWO_4 prepared by the sol-gel method," *Chemical Research in Chinese Universities*, vol. 23, pp. 465–468, 2007.
- [26] X. Zhao, W. Yao, Y. Wu, S. Zhang, H. Yang, and Y. Zhu, "Fabrication and photoelectrochemical properties of porous ZnWO_4 film," *Journal of Solid State Chemistry*, vol. 179, no. 8, pp. 2562–2570, 2006.
- [27] J. H. Ryu, C. S. Lim, and K. H. Auh, "Synthesis of ZnWO_4 nanocrystalline powders, by the polymerized complex method," *Materials Letters*, vol. 57, pp. 1550–1554, 2003.
- [28] X. C. Song, E. Yang, Y. F. Zheng, and Y. Wang, "Effects of preparation conditions on the morphology and photoluminescence of ZnWO_4 nanocrystals," *Acta Physico-Chimica Sinica*, vol. 23, no. 7, pp. 1123–1126, 2007.
- [29] J. Bi, L. Wu, Z. Ding, X. Wang, and X. Fu, "A facile microwave solvothermal process to synthesize ZnWO_4 nanoparticles," *Journal of Alloys and Compounds*, vol. 480, pp. 684–688, 2009.
- [30] S. Komarneni, R. Roy, and Q. H. Li, "Microwave-hydrothermal synthesis of ceramic powders," *Materials Research Bulletin*, vol. 27, pp. 1393–1405, 1992.
- [31] H. D. Xie, D. Z. Shen, X. Q. Wang, and G. Q. Shen, "Growth and characterization of $\text{KBi}(\text{WO}_4)_2$ single crystals," *Crystal Research and Technology*, vol. 42, no. 1, pp. 18–22, 2007.
- [32] G. B. Kumar, K. Sivaiah, and S. Buddhudu, "Synthesis and characterization of ZnWO_4 ceramic powder," *Ceramics International*, vol. 36, no. 1, pp. 199–202, 2010.
- [33] Z. Y. Liu, X. T. Zhang, S. Nishimoto, T. Murakami, and A. Fujishima, "Efficient photocatalytic degradation of gaseous acetaldehyde by highly ordered TiO_2 nanotube arrays," *Environmental Science & Technology*, vol. 42, pp. 8547–8551, 2008.
- [34] M. Wang, Q. L. Huang, H. X. Zhong, X. T. Chen, Z. L. Xue, and X. Z. You, "Formation of YF_3 nanocrystals and their self-assembly into hollow peanut-like structures," *Crystal Growth and Design*, vol. 7, no. 10, pp. 2106–2111, 2007.
- [35] X. C. Song, Y. F. Zheng, E. Yang et al., "Photocatalytic activities of Cd-doped ZnWO_4 nanorods prepared by a hydrothermal process," *Journal of Hazardous Materials*, vol. 179, no. 1–3, pp. 1122–1127, 2010.
- [36] J. Z. Zhao, C. C. Chen, and W. H. Ma, "Photocatalytic degradation of organic pollutants under visible light irradiation," *Topics in Catalysis*, vol. 35, pp. 269–279, 2005.