

## Research Article

# Nanostructured $\text{TiO}_2$ Doped with Nb as a Novel Support for PEMFC

Edgar Valenzuela,<sup>1</sup> Victor Ramos-Sanchez,<sup>2</sup>  
Alejandro Adolfo Lambert Arista,<sup>1</sup> and Oumarou Savadogo<sup>3</sup>

<sup>1</sup> *Cuerpo Académico de Sistemas Energéticos, Facultad de Ingeniería UABC Mexicali, Boulevard Benito Juárez y Calle de la Normal s/n, Col. Insurgentes Este, 21280 Mexicali, BCN, Mexico*

<sup>2</sup> *Facultad de Ciencias Químicas, Universidad Autónoma de Chihuahua, Circuito Numero 1, Nuevo Campus Universitario, 31125 Chihuahua, CHIH, Mexico*

<sup>3</sup> *Laboratoire de Nouveaux Matériaux pour l'Électrochimie et l'Énergie, École Polytechnique de Montréal, C.P. 6079, Succuraste Centre-Ville, Montréal, QC, Canada H3C 3A7*

Correspondence should be addressed to Victor Ramos-Sanchez; [vramos@uach.mx](mailto:vramos@uach.mx)

Received 17 January 2013; Revised 15 May 2013; Accepted 16 May 2013

Academic Editor: Bengt G. Svensson

Copyright © 2013 Edgar Valenzuela et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Nowadays, one of the major issues of the PEMFC concerns the durability. Historically, carbon has been used as a catalyst support in PEMFC; nevertheless, under the environmental conditions of the cell, the carbon is oxidized, leaving the catalyst unsupported. In order to increase the stability and durability of the catalyst in the PEMFC, a novel nanostructured metallic oxide support is proposed. In this work,  $\text{TiO}_2$  was doped with Nb to obtain a material that combines chemical stability, high surface area, and an adequate electronic conductivity in order to be a successful catalyst support candidate for long-term PEMFC applications. The  $\text{TiO}_2$ -Nb nanostructured catalyst support was physically and electrochemically characterized. According to the results, the  $\text{TiO}_2$ -Nb offers high surface area and good particle dispersion; also, the electrochemical activity and stability of the support were evaluated under high potential conditions, where the  $\text{TiO}_2$ -Nb proved to be much more stable than carbon.

## 1. Introduction

In the last decade, several improvements have been achieved regarding the proton exchange membrane fuel cells (PEMFC). Such advances permitted a significant increase in the energy conversion efficiency at the same time that the production costs were decreased, placing the PEMFC as one of the best candidates for powering electrical mobile applications [1–4]. In a typical PEMFC, hydrogen fuel is oxidized in the surface of a catalyst and split into protons and electrons; the charge of protons is transported by means of complex phenomena through a polymeric electrolyte [5] while the electrons flow by an external circuit towards the cathode where they combine together with oxygen to produce water. In the last years, large improvements have been achieved in the development of new materials for

PEMFC which allowed an important cost reduction and an increase in the energy conversion efficiency [1]. Nevertheless, problems related to durability, particularly of the catalyst support, are some of the major issues that must be solved to achieve a commercial competitive PEMFC technology [6–9]. In this respect, the department of energy has set a target for the PEMFC, in which these devices should achieve a life time of at least 5000 h in order to be commercially attractive [10]. Consequently, the materials of the PEMFC must be able to operate for long periods of time without degradation, maintaining the performance and more important the output voltage unaffected.


*1.1. Catalyst Supports for PEMFC.* Historically, carbon has been used as catalyst support in PEMFC because of their high active area and adequate electronic conductivity [11,

12]; however, it has been proved that under the PEMFC cathode conditions carbon is oxidized, leaving the catalyst unsupported and causing particles agglutination or even its migration out of the electrode [8, 13, 14]. One of the materials that have been proposed as a successful alternative to carbon support is titanium dioxide ( $\text{TiO}_2$ ).  $\text{TiO}_2$  is a relatively affordable and easy to synthesize material that exhibits high surface area, good affinity with catalytic noble metals, and high electrochemical stability even in PEMFC cathode conditions [9, 15–17]. One of the drawbacks of  $\text{TiO}_2$  is its low electronic conductivity [18–20]. To overcome this problem, the  $\text{TiO}_2$  has been doped with a number of elements as an approach to increase its electronic conductivity. It has been observed that the insertion of ions in the  $\text{TiO}_2$  structure has a double positive effect in the material properties. In one hand, the inclusion of pentavalent ions contributes to diminishing the number of trivalent defects in the material, increasing their chemical stability; also, there is evidence that many of these ions occupy substitutional sites by replacing the Ti atoms in the structure; as a consequence, the material attains an excess of electronic charge carriers and exhibits an n-type semiconductor properties with electronic conductivities several orders of magnitude higher than  $\text{TiO}_2$  unmodified [21–23]. In this work, the  $\text{TiO}_2$  was doped with Nb as an approach to obtain a material that combines all the desirable catalyst support properties along with a remarkable electrochemical stability for its utilization in long-term PEMFC applications.


## 2. Material and Methods

The Pt/ $\text{TiO}_2$ -Nb (30 Wt% of Pt) samples were synthesized by the Sol-Gel method using Ti (IV) isopropoxide and Nb (V) ethoxide as precursors. For this procedure, 16.50 mL of Ti (IV) isopropoxide (97%, Sigma-Aldrich) and 1.35 mL of Nb (V) ethoxide (99.95%, Aldrich) were dissolved in 100 mL of 2-propanol at room temperature, in order to obtain a solution with a 10 Wt% of Nb content respecting to the Ti. When the precursors were completely dissolved, 40 mL of deionized water was added to accomplish the following reactions [24]:


Hydrolysis




Condensation



Hydrolysis



Condensation



After the reaction, a white gel is obtained and let under stirring for 12 h, then filtered and dried at 120°C in vacuum

for 10 h. The resulting white powder was thermally treated for 2 h in air at 400°C with a heating rate of 5°C/min.

The Pt nanoparticles were synthesized and directly supported on the  $\text{TiO}_2$ -Nb by the chemical reduction method [26]. To obtain 2.00 g of catalyst powder with 30 Wt% of Pt, 1.50 g of  $\text{H}_2\text{PtCl}_6 \cdot 4\text{H}_2\text{O}$  (99.999%, Alfa-Aesar) was dissolved in 100 mL of deionized water at 50°C; then 2.00 g of  $\text{TiO}_2$ -Nb with a 10 Wt% of Nb content was added and stirred for 40 minutes; after that, the Pt ions were reduced by adding drop by drop 20 mL of  $\text{NaBH}_4$  0.2 M; then the solution was stirred at 50°C during 2 h. The supported catalyst was filtered and rinsed with deionized water and treated at 400°C under 100%  $\text{H}_2$  atmosphere in order to obtain the desired structure and to remove any trace of by-products from the surface of the catalyst.

Then, in order to determine the composition and structure, the Pt/ $\text{TiO}_2$ -Nb was analyzed by XRD and TEM, the surface area of the material was determined by nitrogen absorption, and the electrochemical activity was studied by cyclic voltammetry and compared with the performance of a Pt/C sample.

**2.1. Physical and Electrochemical Characterization.** The Pt/ $\text{TiO}_2$ -Nb powders were analyzed in a Jeol 205 Transmission Microscope in order to determine its dispersion, particle size, and morphology. Also a Pt/C sample prepared under the same conditions was analyzed as reference. The crystallite size and composition of the Pt/ $\text{TiO}_2$ -Nb and Pt/C samples were determined by X-ray diffraction (XRD) in a Philips Analytical X-Ray X'Pert MPD equipment (50 kV and 40 mA) using a Cu  $\text{K}\alpha$  radiation's wavelength of 0.1542 nm. After physical characterization, the electrochemical activity and stability of the catalyst were determined by cyclic voltammetry under the conditions described below.

The electrochemical characterization was performed in  $\text{H}_2\text{SO}_4$  0.5 M at 25°C in a 3 electrodes electrochemical cell with an EG&G Princeton 273 Potentiostat. Prior to any measurement, the electrolyte was deaerated by bubbling  $\text{N}_2$  for 2 h. A catalytic ink was prepared by mixing 20  $\mu\text{g}$  of Pt/ $\text{TiO}_2$ -Nb and 25  $\mu\text{L}$  of liquid Nafion in 0.5 mL of 2-propanol; after that, the mixture was ultrasonically stirred by 20 minutes and the working electrode was prepared by placing 20  $\mu\text{L}$  of this ink over a glassy carbon electrode and dried at 50°C for 20 minutes. A Pt grid was used as counter electrode and the potential was measured against a saturated  $\text{Hg}/\text{Hg}_2\text{Cl}_2$  electrode; nevertheless, all the plots show the potential referred to the standard hydrogen electrode (SHE). All the measurements of cyclic voltammetry were recorded at 10 mV/s for 10 cycles and only the last cycle is presented.

## 3. Results and Discussion

**3.1. Microscopy and XRD.** The TEM micrographs for the Pt/ $\text{TiO}_2$ -Nb are shown in Figure 1, while the results for the Pt/C sample are presented in Figure 2 as reference. The surface area for the Pt/ $\text{TiO}_2$ -Nb obtained by nitrogen absorption was 155  $\text{m}^2/\text{g}$ . This high surface area was correlated with




FIGURE 1: The TEM micrographs of Pt/TiO<sub>2</sub>-Nb at low and high magnification. The nanometric characteristic of support can be observed along with a good distribution of Pt particles on its surface.




FIGURE 2: TEM micrograph of Pt/C as reference. Pt/TiO<sub>2</sub>-Nb and Pt/C exhibit similar characteristics, with spherical Pt particles well dispersed over the support and a particle mean size of 15 nm.

the TEM observations that show a nanometric support with well-dispersed Pt particles on their surface. The mean Pt particle size was calculated and estimated in 15 nm ( $\pm 4$  nm) both for Pt/TiO<sub>2</sub>-Nb and for Pt/C.

The XRD patterns of Pt/TiO<sub>2</sub>-Nb and Pt/C (Figure 3) revealed peaks that clearly match with the (111), (200), (220), (311), and (222) planes indexed for Pt in its face centered cubic structure (JCPDS 04-0802). With respect to the catalyst supports, the Pt/TiO<sub>2</sub>-Nb diffractogram solely permits to identify unequivocally the (101) plane of body centered tetragonal TiO<sub>2</sub> in the form of anatase (JCPDS 21-1272). An additional XRD pattern of the TiO<sub>2</sub>-Nb support exposed also the (200), (105) and (211) planes for anatase, as illustrated in Figure 4. In both Pt/TiO<sub>2</sub>-Nb and TiO<sub>2</sub>-Nb diffractograms, all of the crystallographic planes of Nb (JCPDS 35-0789) are intrinsically convoluted with those of anatase, which

precludes their lone observation. However, Figure 4 allows estimating qualitatively the fraction of Nb that has effectively replaced Ti within the nanocrystalline structure. According to the comparison made with previous work on Nb-doped TiO<sub>2</sub>, [25] the Nb mole fraction is in a range between 0.025 and 0.050. As a matter of fact, the XRD pattern is closely similar to that exhibited by TiO<sub>2</sub> doped with Nb 5.0 mol%. Indeed, the TiO<sub>2</sub>-Nb synthesized support is expected to achieve ca. 6.4 mol%, after an ideally complete replacement of Ti by Nb. Finally, in the case of the carbonaceous support in Pt/C, a broad band ca. 25°, attributed to the (002) plane of turbostratic carbon, is clearly evident in its XRD pattern. Further insight on the crystallographic nature of the Pt-supported catalysts is gained from their transmission electron diffraction patterns, which are shown also in Figure 3. In the case of the Pt/C the diffuse ring diffraction patterns reveal the presence of a material of amorphous nature, such as carbon; although very weak, the three rings correspond to Pt reflections. The Pt/TiO<sub>2</sub>-Nb pattern, on the other hand, exhibits several well-defined rings characteristics of a polycrystalline material; indeed the brightest diffraction ring denotes that (111) is the preferential orientation of Pt. It is worthy to mention that no evidence of NbTi<sub>2</sub>O<sub>7</sub> was found according to the employed diffraction patterns database.

Although most of the XRD features observed within the diffractograms result from the sum of two or more single diffraction peaks, it was possible to isolate individual reflections for Pt (220) and anatase (101). Therefore, these reflections were chosen to estimate the mean crystallite size according to the Debye-Scherrer equation. Peak fitting analysis on the Pt (220) indicated a crystallite size for Pt of 12.9 nm in Pt/C and 13.2 nm in Pt/TiO<sub>2</sub>-Nb, both values in agreement with TEM results.

**3.2. Electrochemical Evaluation.** The Pt/TiO<sub>2</sub> and Pt/C electrodes were evaluated in H<sub>2</sub>SO<sub>4</sub> 0.5 M from -0.4 to 1.2 V versus SHE. The results are shown in Figures 5 and 6.






FIGURE 3: X-ray diffractograms of the Pt-supported catalysts together with their respective transmission electron diffraction patterns: (a) Pt/TiO<sub>2</sub>-Nb; (b) Pt/C. Note: reflections contributed by the sample holder, made of aluminum, are denoted in all XRD patterns with a star above its corresponding peaks (JCPDS 04-0787).




FIGURE 4: (a) X-ray diffractogram of the TiO<sub>2</sub>-Nb synthesized support. (b) Zoom in on the detailed XRD pattern, between 45° and 58° 2θ values, which is shown together with two XRD patterns taken and adapted from Lü et al. [25].

In Figure 5 it is possible to observe from the hydrogen absorption/desorption peaks between  $-0.4$  and  $-0.1$  V an evident higher activity for the Pt/C electrode; nevertheless, when reaching the oxidation potentials, the Pt/TiO<sub>2</sub> exhibits a very low anodic current ( $31.5 \mu\text{A}$  for TiO<sub>2</sub>-Nb and  $1.37 \text{ mA}$  for carbon). Considering that the low anodic current observed for Pt/TiO<sub>2</sub> is a combined result of the low catalyst reactivity

for the oxidation of species and the high electrochemical stability of the electrode, it is possible to say that minimum support degradation was observed in Pt/TiO<sub>2</sub> compared with Pt/C electrodes.

Furthermore, when analyzing the irreversibility of the oxidation and reduction peaks for Pt/C ( $1.2$  and  $0.4$  V), it is possible to see that from the oxidized species at  $1.2$  V, only the




FIGURE 5: Cyclic voltammograms comparing the electrochemical activity of Pt/TiO<sub>2</sub>-Nb and Pt/C in H<sub>2</sub>SO<sub>4</sub> 0.5 M.





FIGURE 6: Even at extreme oxidative potentials the electrochemical performance of Pt/TiO<sub>2</sub>-Nb remains unaffected.

fraction that, corresponds to the Pt oxide is reduced at 0.4 V, while a portion of the C support is gasified according to the following equation [27]:



The same experiment was repeated and the oxidation potential was increased up to +1500 mV versus SHE (Figure 6). The response is very similar; again the catalytic activity of Pt/TiO<sub>2</sub>-Nb remains lower than Pt/C but, in this case, the accelerated degradation of carbon is much more evident.

## 4. Conclusions

The TiO<sub>2</sub>-Nb PEMFC electrocatalytic support was prepared and evaluated. The physical characterizations showed a high active area related to its nanostructured composition. When Pt is deposited, the catalytic nanoparticles exhibit good dispersion and homogeneous size and shape, which are desirable characteristics for PEMFC applications. The XRD results show a predominant anatase phase for the TiO<sub>2</sub>-Nb and a high crystallite catalyst structure. The voltammograms confirm the TiO<sub>2</sub>-Nb outstanding electrochemical stability, even at extreme oxidation conditions; nevertheless, improvements should be made in the support-catalyst electronic contact in order to increase the electrode performance. In the end, the combination of high active area, good Pt affinity, and high electrochemical stability makes the TiO<sub>2</sub>-Nb a suitable candidate for further research in order to be utilized as catalyst support in PEMFC.

## Acknowledgments

The authors would like to thank CONACyT for the support provided for this project through the postdoctoral Grant of the program “Estancias posdoctorales en el extranjero” and the technician Roosevelt Toledo Espinosa (CAIDA-UPCh) for his assistance in this research.

## References

- [1] P. Costamagna and S. Srinivasan, “Quantum jumps in the PEMFC science and technology from the 1960s to the year 2000: part I. Fundamental scientific aspects,” *Journal of Power Sources*, vol. 102, no. 1-2, pp. 242–252, 2001.
- [2] W. Smith, “Role of fuel cells in energy storage,” *Journal of Power Sources*, vol. 86, no. 1, pp. 74–83, 2000.
- [3] E. Middelmann, W. Kout, B. Vogelaar, J. Lenssen, and E. de Waal, “Bipolar plates for PEM fuel cells,” *Journal of Power Sources*, vol. 118, no. 1-2, pp. 44–46, 2003.
- [4] A. Kirubakaran, S. Jain, and R. K. Nema, “A review on fuel cell technologies and power electronic interface,” *Renewable and Sustainable Energy Reviews*, vol. 13, no. 9, pp. 2430–2440, 2009.
- [5] E. Valenzuela, S. A. Gamboa, P. J. Sebastian et al., “Proton change transport in Nafion nanochannels,” *Journal of Nano Research*, vol. 5, no. 1, pp. 31–36, 2009.
- [6] W. Schmittinger and A. Vahidi, “A review of the main parameters influencing long-term performance and durability of PEM fuel cells,” *Journal of Power Sources*, vol. 180, no. 1, pp. 1–14, 2008.
- [7] Z. Wang, P. Zuo, Y. Chu, Y. Shao, and G. Yin, “Durability studies on performance degradation of Pt/C catalysts of proton exchange membrane fuel cell,” *International Journal of Hydrogen Energy*, vol. 34, no. 10, pp. 4387–4394, 2009.
- [8] X. Yu and S. Ye, “Recent advances in activity and durability enhancement of Pt/C catalytic cathode in PEMFC. Part II: degradation mechanism and durability enhancement of carbon supported platinum catalyst,” *Journal of Power Sources*, vol. 172, no. 1, pp. 145–154, 2007.
- [9] N. Rajalakshmi, N. Lakshmi, and K. S. Dhathathreyan, “Nano titanium oxide catalyst support for proton exchange membrane fuel cells,” *International Journal of Hydrogen Energy*, vol. 33, no. 24, pp. 7521–7526, 2008.

- [10] U.S. Department of Energy, "Hydrogen, Fuel Cells, and Infrastructure Technologies Program," Progress Report FY 2002, U.S. Department of Energy, Washington, DC, USA, 2002.
- [11] S. M. Haile, "Fuel cell materials and components," *Acta Materialia*, vol. 51, no. 19, pp. 5981–6000, 2003.
- [12] S. Litster and G. McLean, "PEM fuel cell electrodes," *Journal of Power Sources*, vol. 130, no. 1-2, pp. 61–76, 2004.
- [13] Y. Shao, G. Yin, and Y. Gao, "Understanding and approaches for the durability issues of Pt-based catalysts for PEM fuel cell," *Journal of Power Sources*, vol. 171, no. 2, pp. 558–566, 2007.
- [14] K. J. J. Mayrhofer, J. C. Meier, S. J. Ashton et al., "Fuel cell catalyst degradation on the nanoscale," *Electrochemistry Communications*, vol. 10, no. 8, pp. 1144–1147, 2008.
- [15] D. Kim, E. F. A. Zeid, and Y. Kim, "Additive treatment effect of  $\text{TiO}_2$  as supports for Pt-based electrocatalysts on oxygen reduction reaction activity," *Electrochimica Acta*, vol. 55, no. 11, pp. 3628–3633, 2010.
- [16] S. von Kraemer, K. Wikander, G. Lindbergh, A. Lundblad, and A. E. C. Palmqvist, "Evaluation of  $\text{TiO}_2$  as catalyst support in Pt- $\text{TiO}_2$ /C composite cathodes for the proton exchange membrane fuel cell," *Journal of Power Sources*, vol. 180, no. 1, pp. 185–190, 2008.
- [17] F. Leroux, P. J. Dewar, M. Intissar, G. Ouvrard, and L. F. Nazar, "Study of the formation of mesoporous titania via a template approach and of subsequent Li insertion," *Journal of Materials Chemistry*, vol. 12, no. 11, pp. 3245–3253, 2002.
- [18] P. Leroy, C. Tournassat, and M. Bizi, "Influence of surface conductivity on the apparent zeta potential of  $\text{TiO}_2$  nanoparticles," *Journal of Colloid and Interface Science*, vol. 356, no. 2, pp. 442–453, 2011.
- [19] M. Afuyonia, G. Nasheda, and I. Nasser, " $\text{TiO}_2$  doped with  $\text{SnO}_2$  and studying its structural and electrical properties," *Energy Procedia*, vol. 6, pp. 11–20, 2011.
- [20] L. B. Modesto-Lopez and P. Biswas, "Role of the effective electrical conductivity of nanosuspensions in the generation of  $\text{TiO}_2$  agglomerates with electrospray," *Journal of Aerosol Science*, vol. 41, no. 8, pp. 790–804, 2010.
- [21] J. Gautron, J. F. Marucco, and P. Lemasson, "Reduction and doping of semiconducting rutile ( $\text{TiO}_2$ )," *Materials Research Bulletin*, vol. 16, no. 5, pp. 575–580, 1981.
- [22] O. Meyer, I. Khubeis, R. Fromknecht, and S. Massing, "Ions implanted into  $\text{TiO}_2$  rutile single crystals: Lattice disorder, lattice site occupation and conductivity," *Nuclear Instruments and Methods in Physics Research*, vol. 127-128, pp. 624–628, 1997.
- [23] Q. Zhao, P. Wu, B. L. Li, and E. Y. Jiang, "The effect of additional doping with Nb, Al or Cu on ferromagnetism and conductivity in V-doped  $\text{TiO}_2$  powders," *Physica B*, vol. 407, no. 1, pp. 171–174, 2012.
- [24] S. Mahshid, M. Askari, and M. S. Ghamsari, "Synthesis of  $\text{TiO}_2$  nanoparticles by hydrolysis and peptization of titanium isopropoxide solution," *Journal of Materials Processing Technology*, vol. 189, no. 1-3, pp. 296–300, 2007.
- [25] X. Lü, X. Mou, J. Wu et al., "Improved-performance dye-sensitized solar cells using Nb-doped  $\text{TiO}_2$  electrodes: efficient electron injection and transfer," *Advanced Functional Materials*, vol. 20, no. 3, pp. 509–515, 2010.
- [26] E. Valenzuela, P. J. Sebastian, S. A. Gamboa, S. Joseph, U. Pal, and I. Gonzalez, "Characterization of self-assembled electrodes based on Au-Pt nanoparticles for PEMFC application," *Journal of New Materials for Electrochemical Systems*, vol. 13, no. 1, pp. 47–55, 2010.
- [27] K. Kinoshita, *Carbon: Electrochemical and Physicochemical Properties*, John Wiley & Sons, New York, NY, USA, 1988.



